C₂₀: Fullerene, Bowl or Ring? New Results from Coupled-Cluster Calculations

Peter R. Taylor

San Diego Supercomputer Center, P. O. Box 85608, San Diego, CA 92186-9784

Eric Bylaska and John H. Weare

Department of Chemistry, University of California, San Diego, La Jolla, CA 92093

Ryoichi Kawai

Department of Physics, University of Alabama at Birmingham, Birmingham, AL 35294

(October 30, 2018)

Contrary to recent experimental evidence suggesting that the monocyclic ring is the most stable 20-atom carbon species, highly accurate calculations convincingly predict that the smallest fullerene, the dodecahedron C_{20} , has the lowest energy. A related corannulene-like bowl is nearly degenerate in energy to the fullerene. Thermodynamic considerations suggest that at formation temperatures of around 700 K the bowl should be the dominant species. The recent application of gradient corrections to LDA which supported the ring structure is qualitatively in error.

PACS number:

The 20-atom carbon cluster is the smallest size that can form a closed fullerene molecule. Since small fullerenes have been proposed as possible intermediates to C_{60} or larger fullerenes [1] and because of the relevance of this molecule to the general question of the stability of fullerenes, this cluster has received a great deal of attention [2–9]. Formation experiments by Bowers and co-workers [2,7] and by Jarrold and co-workers [8] have probed the structure of carbon clusters over a wide range of sizes, including C_{20} . In these experiments monocyclic rings are dominant for sizes between 11 and 30 atoms. There is no evidence for species with a fullerene structure for sizes less than 32 atoms. This suggests that rings rather than fullerenes are the most stable isomers below n=32. However, in these experiments the systems are far from equilibrium. It may be difficult to anneal the systems to produce the most stable species, therefore missing the fullerene.

Many theoretical calculations of varying sophistication have been performed to try to predict stability [3-7,9]. It is well known from calculations on smaller clusters, C₂- C_{10} that in order to predict the relative energies of carbon isomers, very high accuracy methods (few kcal/mol) are required. On the other hand, the highest level calculations that have been reported on the C_{20} molecule are based on many-body perturbation theory (MP2). Prior calculations using these methods for smaller systems have shown that for carbon clusters the convergence of perturbation theory is slow, with reliability of the order of 50 kcal/mol [4]. Isomerization energies in C_{20} and other carbon clusters can be much less than this (roughly 10 kcal/mol), so higher accuracy methods are necessary to make definitive assignments of stability. Methods with such accuracy are commonly applied to small molecules, but rapidly become computationally intractable as the system sizes increases. As we discuss in this letter, they are just feasible for the C_{20} molecule.

Because of the expense of even low-level calculations on systems of this size, attention in previous work and in our calculations has focused on three structures which appear to be candidates for the most stable configuration, (Fig. 1): a monocyclic ring structure (the ring I structure dominant in the experiment by von Helden etal. [2]), a polycyclic corannulene-like bowl comprising five fused hexagons which forms part of the C_{60} cage, and a small fullerene of near dodecahedral structure. Some earlier estimates of the energies of these structures are summarized in Table I. Lowest level first-principles calculations (Hartree-Fock self-consistent field, SCF) [4] support experimental observations [2] by assigning the ring as the lowest energy form. However, perturbational improvements (MP2) [4] reverse these predictions, giving the fullerene structure the lowest energy. On the other hand, local density approximation (LDA) calculations for C_{20} support the fullerene as the lowest energy structure [6,9]. However, when gradient corrections [9] are made to the LDA calculations, the order is reversed, predicting the ring as the lowest energy geometry in agreement with experiments. The change in the ring/fullerene separation on going from SCF to the inclusion of correlation at the MP2 level is roughly 150 kcal/mol. A similar large energy difference is present between the gradient corrected LDA and uncorrected LDA. Given the uncertainties inherent in all the computational methods, none of the calculations can be considered definitive [10]. We note that the reliability of the gradient corrections is a question of considerable relevance since this method has been suggested as a relatively tractable way to obtain results within chemical accuracy (1 kcal/mol).

We present here results from theoretical calculations on C_{20} at a much higher accuracy than previous work (of the order of a few kcal/mol). Since electron correlation effects can have a very large influence on the energetics of the isomers, we have performed coupled-cluster calculations using the CCSD(T) method [11]. This method includes correlation effects of single and double replacements of Hartree-Fock orbitals to infinite order, and in addition a perturbative estimate of triple replacements. Extensive series of calibration calculations have established that the CCSD(T) method is the most accurate SCF-based treatment of electron correlation that can feasibly be applied to a molecule of this size.

The coupled-cluster method provides an almost exact description of the electronic structure of molecules that we are interested in here (see below and in Parasuk and Almlöf [10]) provided a sufficiently flexible orbital basis is provided. Unfortunately, the increase of the computational load with number of orbital functions is so large that completeness of the orbital basis is a source of error. The calculations here were performed using Dunning's cc-pVDZ basis [12] on each carbon atom. This is a contracted set containing three s functions, two p functions, and a d function, obtained from a $(9s \ 4p \ 1d)$ primitive set. It provides a "double zeta" description of the valence electrons (two functions per shell) and a minimal description of the 1s core electrons, plus a higher angular momentum function to describe polarization and correlation effects. This level of basis set is the smallest capable of yielding reliable results in correlated molecular calculations. Studies (see e.g., Ref. [13]) have shown that this basis set, optimized for treating correlation, performs better than other sets of the same size. Correlation effects involving the carbon 1s electrons were not included because this is expected to have a negligible effect on the predicted energetics. 19.5 million parameters were optimized iteratively in the fullerene CCSD(T) calculation and another 29 billion were estimated perturbatively. The computational effort is near the limit of the capabilities of present day supercomputers even for a fixed geometry. Therefore, it is not feasible to search for the optimum structure at this level of calculation. To define input geometries for the CCSD(T) calculations, we have determined C_{20} structures at two levels: SCF and LDA [14]. The calculations were carried out on the CRAY C90 computer at SDSC using the programs MOLECULE-SWEDEN [15] and TITAN [16]. Some of the C_6 results discussed in this work were obtained with ACES II [17].

We should note some points about the symmetry of the various C_{20} isomers. The putative dodecahedral fullerene undergoes a Jahn-Teller distortion: previous SCF optimization produced a structure with C_2 symmetry, whereas the LDA optimization yields a structure with C_i symmetry. Both optimized structures are close to a dodecahedron. The monocyclic ring is found to have C_{10h} symmetry, with alternating bonds and angles, in both SCF and LDA optimizations. For computational reasons, this was treated within the subgroup C_{2h} in the coupled-cluster calculations. The bowl is found to have C_{5v} symmetry at the SCF level, and is very close to this symmetry at the LDA level. Only the C_s subgroup of C_{5v} was used in the calculations. All calculations were done for the singlet spin state: SCF calculations demonstrate that all three structures have a closed-shell ground state [18].

Energies relative to the fullerene are given in Table I. In agreement with previous results [9], at the SCF level, the ring is predicted to be the most stable isomer, by at least 50 kcal/mol. The bowl is intermediate between two other isomers but closer to the ring in energy. The situation is quite different using LDA energies, where the fullerene is predicted to be most stable, with the bowl closer to the fullerene. The MP2 results are similar to those of LDA. Note that the bowl in all these calculations is well separated from the fullerene.

The most important entry in Table I are the CCSD(T) results. These results agree with the LDA results, also predicting the fullerene to be more stable than the ring. *However, at this level, the fullerene and bowl are pre-dicted to be essentially degenerate at the LDA geometry* and the bowl is predicted to be lower in energy at the SCF geometries. This ordering is sensitive to the remaining error in the correlation energy, but the near degeneracy of the bowl and the fullerene will remain.

The CCSD(T) results clearly predict that the fullerene and bowl are more stable than the ring. But we still need to assess the accuracy of the method. Other calculations have shown that for systems for which the Hartree-Fock determinent dominates the configuration expansion, CCSD(T) recovers essentially all the correlation energy available with a given basis set. The scaled norm of the single replacements (\mathcal{T}_1) as calculated by CCSD(T) may be used as a guide to the accuracy of a single determinent description [19]. If \mathcal{T}_1 is less than 0.02 the CCSD(T) approach yields results whose reliability depends almost entirely on the accuracy of the atomic basis. In these calculations, \mathcal{T}_1 was found to be 0.0153, 0.0136, and 0.0151 for the fullerene, bowl and the ring respectively. Thus, in a complete basis, the accuracy will be of the order of a few kcal/mol. However, the cc-pVDZ basis used is still quite far from complete. For example, it recovers only about 75% of the valence-shell correlation energy of the carbon atom. Presumably, since we are looking for energy differences, much of this error would be shared by the three structures and would cancel in the energy difference calculation, but it is desirable to provide some calibration for this. The present calculations have the largest basis that we could conceivably use in a CCSD(T) calculation for C_{20} , so we can hardly perform the calibration on this system. Instead, in order to ascertain the accuracy of the results we have performed similar calculations on the smaller system C_6 , which we can treat with higher accuracy basis sets. The principal problem is the slow convergence of the dynamical correlation energy (that treated accurately by CCSD(T)) with angular quantum number l of the orbital basis: the behavior is as l^{-4} . Our cc-pDVZ basis includes up to d atomic orbitals only. Including higher terms such as f and g functions increases the computational load very quickly. Nevertheless, for the C₆ molecule it is possible to explore basis sets up to g functions (using again Dunning's correlation-consistent sets) [12]. The results are summarized in Table II. More detailed results will be presented elsewhere. [20] For C₆ we have examined three structures: a linear triplet state, a D_{6h} ring and a D_{3h} ring (lowest energy). The relative energies of the two ring isomers do not change with increasing basis. However, the relative energy of the linear structure changes by a few kcal/mol as the basis is increased.

The first thing to note is that the corrections in Table II are of the order of a few kcal/mol. Similar behavior with basis set has been observed in C_{10} . [21] From this we can confidently assert that increasing the size of the basis used for C_{20} certainly would be unlikely to change the order of the fullerene vs. the ring structures, since this is already at least 40 kcal/mol.

The relative stability of the bowl and the fullerene is a more difficult question. At the present level CCSD(T) calculation, there is a considerable difference between the correlation energy for the different structures ($-2.773 E_h$ for the fullerene, -2.699 for the bowl and -2.629 for the ring, at the SCF geometries). Since the main error in the calculation is in the correlation energy, this implies that there is probably a larger energy error in the fullerene calculation than in the bowl or the ring.

Recently, it has been suggested by Martin [22] that the angular basis dependence of the energy can be extrapolated to convergence by a three-term extrapolation formula based on the broad characteristics of the occupied orbitals for a particular molecule. Assuming that the majority of the correlation energy available with a given basis for a particular system is recovered by a CCSD(T)calculation, the additional basis set corrections can be estimated by first identifying the types of orbitals, i.e. σ , π or lone pairs, and then making corrections which have been established for each level of basis set by comparison with accurately measured properties for a test set of molecules. This scheme is qualitatively consistent with the present results. The results in Table II show that the isomerization energy from the D_{3h} to D_{6h} ring changes very little with basis, because the orbital character in the two molecules is basically the same. On the other hand, there are major changes in the number of σ and π bonds in going from the linear to the cyclic forms, giving a significant correction in the Martin approach. The direction of this calculated correction is consistent with the changes observed by explicitly expanding the basis sets used (see Table II). Unfortunately we cannot calculate the isomerization energy between the linear and ring structures with the very largest basis set, because the calculation on the (triplet spin state) linear form is not feasible with this large a basis.

As an additional check on the Martin approach, we can

refer to the total atomization energy of the C_3 molecule using the *cc*-pDVZ basis (see also Ref. [23]). In this case a 30kcal/mol basis set error in the atomization energy is predicted by the Martin formula: applying this correction brings the predicted atomization energy within the error bars of the measured value.

The stabilities of the C_{20} isomers estimated via the Martin approach are included as the last line in Table I. For both the SCF and the LDA geometries, the fullerene is now more stable than the bowl. We note, however, that at the SCF geometries the separation is only 5 kcal/mol, which is roughly the accuracy of the calculation. Therefore, these calculations only weakly support the fullerene as the most stable form.

Another source of error is the lack of CCSD(T) geometry optimization for each isomer. In the calculations, the ring and the bowl had lower CCSD(T) energies at the SCF optimized geometries, while the fullerene was lower at the LDA geometry. This is naively consistent with the greater importance of electron correlation in the fullerene, compared to the other isomers. It is difficult to say with any certainty what would be the results of a CCSD(T) geometry optimization, but if we accept the proposition that correlation affects the fullerene more than the other isomers, we would expect geometry optimization to further stabilize the fullerene relative to the other isomers.

The relative stabilities we have presented are all for hypothetical vibrationless states at absolute zero. The zero-point vibrational energies for the three isomers are 69.8, 73.3, and 76.8 kcal/mol for ring, bowl, and fullerene, respectively, using published SCF frequencies [9]. Still the fullerene is most stable. However, experimental data is taken at high temperature. Therefore, it is desirable to explore finite-temperature effects. While there is no doubt that these effects will favour the ring isomer due to its higher vibrational entropy, the relative energy of the ring versus the fullerene is so large that these effects alone cannot explain the nonappearance of the fullerene in a fully equilibrated system at temperatures less than 1500 K (estimated from the SCF frequencies). On the other hand, even with extrapolations the fullerene and the bowl are quite close in energy. Using an average separation of 9kcal/mol between the bowl and the fullerene, we estimate that above approximately 700 K the bowl is more stable. Below these temperatures the fullerene will be progressively more stable. However, it is easy to believe that the transition state between any of these structures is very high and dynamically difficult to achieve, making it very unlikely for the transition from fullerene to bowl to occur. This is supported by our dynamical calculations which show these molecules to be stable even at very high temperatures.

Finally, our CCSD(T) calculations clearly show that a gradient correction to LDA, at least as implemented in Raghavachari *et al.*, is incorrect (by 165 kcal/mol!) for

this problem. This is unfortunate, since the gradient correction approach has been widely advertised as a solution to the well-known energetics problems of LDA, and is relatively easy to implement. We note, however, that the uncorrected LDA gives predictions that are semiquantitatively correct and much better than SCF for a similar computational cost.

This work was supported in part by National Science Foundation Cooperative Agreement DASC-8902825, by Office of Naval Research (grant number NOO14-91-J-1835), and by a grant of computer time from the San Diego Supercomputer Center. We would particularly like to acknowledge the contributions of C. W. Bauschlicher, T. J. Lee, and A. P. Rendell to MOLECULE-SWEDEN and TITAN that made these calculations possible, and the assistance of M. Vildibill in running the C₂₀ calculations.

- R. F. Curl, Philos. Trans. R. Soc. London, Ser. A 343, 19 (1993).
- [2] G. V. Helden, M. T. Hsu, P. R. Kemper, and M. T. Bowers, J. Chem. Phys. 95, 3835.
- [3] D. Tomanek and M. A. Schluter, Phys. Rev. Lett. 67, 2331 (1991).
- [4] V. Parasuk and J. Almlöf, Chem. Phys. Lett. 144, 187 (1991).
- [5] Z. Slanina and L. Adamowicz, Thermochimica Acta 205, 299 (1992).
- [6] C. J. Brabec et al., Phys. Rev. B 46, 7326 (1992).
- [7] G. V. Helden, N. G. Gotts, and M. T. Bowers, Nature 363, 60 (1993); G. V. Helden, N. G. Gotts, and M. T. Bowers, J. Am. Chem. Soc. 115, 4363 (1993);G. von Helden *et al.*, Chem. Phys. Lett. 204, 15 (1993).
- [8] J. N. Hunter, J. L. Fey, and M. F. Jarrold, J. Phys. Chem.
 97, 3460 (1993); Science 260, 784 (1993); J. Chem. Phys.
 99, 1785 (1993).
- [9] K. Raghavachari *et al.*, Chem. Phys. Lett. **214**, 357 (1993).
- [10] V. Parasuk and J. Almlöf, Theor. Chim. Acta 83, 227 (1992).
- [11] K. Raghavachari, G. W. Trucks, J. A. Pople, and M. Head-Cordon, Chem. Phys., Lett. 157, 479 (1989).
- [12] T. H. Dunning, J. Chem. Phys. **90**, 1007 (1989).
- [13] T. Helgaker and P. R. Taylor, in *Modern Electronic Structure Theory*, edited by D. R. Yarkony (in print).
- [14] R. Kawai and J. H. Weare, J. Chem. Phys. 95, 1151 (1991).
- [15] MOLECULE-SWEDEN is an electronic structure program system written by J. Almlöf, C. W. Bauschlicher, M. R. A. Blomberg, D. P. Chong, A. Heiberg, S. R. Langhoff, P.-Å. Malmqvist, A. P. Rendell, B. O. Roos, P. E. M. Siegbahn, and P. R. Taylor.
- [16] TITAN is a set of electronic structure programs written by T. J. Lee, A. P. Rendell, and J. E. Rice.
- [17] ACES II is a coupled-cluster and MBPT electronic struc-

ture program. Written mainly by J. F. Stanton, J. Gauss, J. D. Watts, W. J. Lauderdale, and R. J. Bartlett, it also includes contributions from J. Almlöf, T. Helgaker, H. J. Aa. Jensen, P. Jørgensen, and P. R. Taylor.

- [18] The LDA and SCF optimized geometries, energies, etc., can be obtained by anonymous FTP from the site ftp.sdsc.edu, in the directory /pub/sdsc/chemistry/structures/C20.
- [19] T. J. Lee and P. R. Taylor, Int. J. Quantum Chem. S23, 199 (1989).
- [20] E. Bylaska, P. R. Taylor, R. Kawai, and J. Weare, in preparation.
- [21] J. D. Watts and R. J. Bartlett, Chem. Phys. Lett. 190, 19 (1992).
- [22] J. M. L. Martin, J. Chem. Phys, 100, 8186 (1994).
- [23] J. M. L. Martin and P. R. Taylor, J. Phys. Chem. 98, 6105 (1994).

TABLE I. C_{20} energies (eV) relative to the fullerene

	LDA g	eometi	ries	SC	SCF geometries		
Method	fullerene	bowl	ring	fulle	rene bowl	ring	
SCF^a				0	. –	-4.6	
$MP2^{a}$				0	. —	3.7	
LDA^{b}				0	. 1.0	3.8	
$\operatorname{GC-LDA}^{c}$				0	-2.4	-3.4	
SCF	0.	-2.0	-2.2	0	-2.5	-3.4	
LDA	0.	0.8	2.3	0	. 0.8	3.3	
MP2	0.	1.1	2.8	0	. 0.8	3.9	
CCSD(T)	0.	0.0	1.7	0	0.6	2.2	
$estimate^{c}$	0.	0.7	2.4	0	. 0.2	2.6	

 a Parasuk and Almlof [4]

- ^b Raghavachari *et al.* [9]
- c Gradient corrected LDA [9]

 d See text.

TABLE II. C_6 Convergence of isomerization energies with basis set size. (kcal/mol)

	spd	spdf	spdfg	estimate
D_{3h}	0.00	0.00	0.00	0.00
D_{6h}	8.2	8.2	7.9	$8. \pm .2$
linear	5.0	9.4	—	14. \pm 1.



FIG. 1. C_{20} structures: ring, bowl, and fullerene)