Phase-Sensitive Tetracrystal Pairing-Symmetry Measurements and Broken Time-Reversal Symmetry States of High T_c Superconductors

M. B. Walker

Department of Physics, University of Toronto, Toronto, Ont. M5S 1A7

(November 15, 2018)

A detailed analysis of the symmetric tetracrystal geometry used in phase-sensitive pairing symmetry experiments on high T_c superconductors is carried out for both bulk and surface time-reversal symmetry-breaking states, such as the d + id' and d + is states. The results depend critically on the substrate geometry. In the general case, for the bulk d + id' (or d + is) state, the measured flux quantization should in general not be too different from that obtained in the pure d-wave case, provided $|d'| \ll |d|$ (or $|s| \ll |d|$). However, in one particular high symmetry geometry, the d + id' state gives results that allow it to be distinguished from the pure d and the d + is states. Results are also given for the cases where surface d + is or d + id' states occur at a [110] surface of a bulk d-wave superconductor. Remarkably, in the highest symmetry geometry, a number of the broken time-reversal symmetry states discussed above give flux quantization conditions usually associated with states not having broken time-reversal symmetry.

PACS numbers: 74.25.Fy

This article describes the use of the symmetric tetracrystal geometry in phase-sensitive pairingsymmetry experiments designed to investigate broken time-reversal symmetry superconducting states. The advantages of the symmetric tetracrystal geometry for such experiments will be outlined, and results will be given for a number of specific cases.

All of the hole-doped high temperature superconductors (such as $YBa_2Cu_3O_{6+x}$) measured up to the present in phase sensitive pairing symmetry experiments have exhibited the behavior expected of a superconducting state with $x^2 - y^2$ symmetry (see Ref. 1). However, interesting questions related to the symmetry of the superconducting state of the high T_c superconductors still remain, and a number of investigations of possible deviations from a pure $x^2 - y^2$ symmetry have been and are being undertaken. For example, it has been suggested² that at low temperatures, an interaction with magnetic impurities can cause the *d*-wave state to become unstable with respect to the formation of a d + id' state. (Here d is used to denote a state of $x^2 - y^2$ symmetry, and d' to denote a state of xy symmetry.) Also, the anyon mechanism for high T_c superconductivity is known³ to give superconducting states of d + id' symmetry. Attempts to interpret^{2,4} anomalies observed^{5,6} in the thermal conductivity of certain bismuth superconductors in terms of d + id' superconductivity has further heightened interest in broken time-reversal symmetry states. Bulk d + is superconductivity has also been noted as a possibility⁷. [It is known that because the d + id' state (and the d + isstate) involves order parameters (d and d') with two different symmetries, the phase transition to a superconducting d + id' state can not occur at a single continuous phase transition.] Also, the possible existence of surface d + is or d + id' states at a [110] surface of a bulk dwave superconductor has been explored theoretically in Refs. 8,10–13, particularly with reference to the possible splitting of the zero bias conductance peak observed in NIS (normal to insulator to superconductor) tunneling experiments. Experimental evidence for such a splitting has been found, at low temperatures, in Ref. 14.

Very recently, evidence¹⁵ of the half integral flux quantum effect in tricrystal experiments on the electron-doped superconductors $Nd_{2-x}Ce_{x}CuO_{4}$ and $Pr_{2-x}Ce_{x}CuO_{4}$ has been presented indicating that the superconducting state of these materials also has *d*-wave symmetry. This result should be contrasted with one other recent experimental result, namely a thermal conductivity study¹⁶ on $Pr_{2-x}Ce_xCuO_4$ indicating that there are no propagating low-energy quasiparticle excitations in this material. These results (in which a material displays both a gapless d-wave state and the absence of propagating low energy excitations) are extremely unusual, and while perhaps not necessarily contradictory, require further study if they are to be understood. One possibility is that the absence of propagating low energy states implied by the thermal conductivity measurements could be accounted for if the low energy quasiparticle excitations were localized by disorder in $Pr_{2-x}Ce_xCuO_4$, as pointed out in Ref. 16 (see also Ref. 17).

A question that might be raised about these results is to what extent the observations of a half integral flux quantum in a tricrystal experiment could, rather than implying a pure *d*-wave state, be consistent with a d+id'state (which has a gap and therefore no low energy quasiparticle excitations). The reason that this question might be asked is that there is at present no detailed analysis indicating what the signature of a d + id' superconductor would be in a tricrystal experiment. Furthermore, as noted above, theoretical arguments have been made that the broken time-reversal symmetry d + id' state could play a role in high T_c superconductivity. Clearly some analysis of the signature of d + id' superconductivity in phase-sensitive pairing symmetry experiments would be useful in resolving these questions.

The above discussion indicates considerable current interest in, and motivation for, the study of various types of broken time-reversal symmetry states. The main objective of this article is therefore to study how broken time-reversal symmetry superconducting states of d + id'and d+is symmetry, in both their bulk and surface forms. would manifest themselves in phase-sensitive pairingsymmetry experiments of the tetracrystal type¹. (For reasons discussed in the following paragraph, the focus will be on the tetracrystal geometry only, and no discussion will be given of the tricrystal geometry, which is the geometry that has been used in most of the phase sensitive pairing symmetry experiments carried out to date¹.) Some aspects related to the bulk d+is state have already been discussed¹⁸. The details of the d+id' case are somewhat different, however. As a result, the d + id' and the d + is states give quite different results for an appropriately chosen experimental geometry and these differences provide a method of experimentally identifying a state of d + id' symmetry.

The symmetric tetracrystal configuration proposed in Ref. 18 and realized experimentally in Refs. 19,20 is shown in Fig. 1. This is called a symmetric geometry because the x axis of the figure is an axis of reflection symmetry, and this symmetry plays an essential role both in simplifying the analysis, and in allowing an unambiguous interpretation of the experimental results. The reason for choosing to analyze the tetracrystal geometry (rather than the tricrystal geometry) in this article is that this geometry allows a determination to be made of order parameter symmetry from the observed flux quantization (say half integral) based on symmetry arguments only. In the tricrystal experiment, symmetry arguments can not be used because the experimental arrangement has no useful symmetry elements (such as a plane of reflection symmetry). It is therefore necessary to appeal to a phenomenological model for the dependence of the Josephson critical current on the misorientation angles Θ_1 and Θ_2 of the two grains on either side of the grain boundary Josephson junction. For example, an appropriate model accounting for the known experimental results on cuprate superconductors would be

$$J_c(\Theta_1, \Theta_2) = C(\Theta_1, \Theta_2) f_{sym}(\Theta_1, \Theta_2).$$
(1)

Here $C(\Theta_1, \Theta_2)$ is a positive factor taking account of the changes in grain boundary microstructure with increasing misorientation angle²¹; this effect is expected to dominate the overall magnitude of the Josephson critical current, which is found experimentally to vary roughly as $\exp[-(\Theta_1 + \Theta_2)/\Theta_0]$ where $\Theta_0 \approx 5^\circ$ for holedoped superconductors²² and $\Theta_0 \approx 2^\circ$ for electron-doped superconductors²³. The factor f_{sym} can change sign and reflects the pairing symmetry of the superconducting state. For the case of *d*-wave symmetry the simplest choices are $f_{sym} = cos(2\Theta_1)cos(2\Theta_2)^{24}$ and the maximum disorder limit $f_{sym} = cos(2\Theta_1 + 2\Theta_2)^{25}$. A systematic study of a variety of different tricrystal geometries has established the reliability of this approach (see Ref. 1 for a review). In addition, the results of the tricrystal experiments are in agreement with those obtained using the symmetric tetracrystal geometry^{1,19,20} which, as noted above, does not refer to a detailed model of the angular dependence of the Josephson critical current.

The exploration of various broken time-reversal symmetry states carried out in this article is more complex than testing for d-wave versus s-wave symmetry, since both the d + id' and d + is states involve linear combinations of order parameters of two different symmetries. Determining a quantitative formula for the angular dependence of the Josephson critical current sufficiently accurate for use with the tricrystal geometry is thus even more difficult than for the purely d-wave and s-wave cases. The symmetric tetracrystal geometry presents no such difficulties, as accurate predictions can be made on the basis of symmetry arguments only provided the cuprate under study is tetragonal.



FIG. 1. The tetracrystal geometry^{18,19}. The substrate is made from two tetragonal crystals of the same material (e.g. $SrTiO_3$), S1 and S2, with their c-axes normal to the plane of the paper, and their tetragonal a and b axes oriented at 45 degrees to each other, as indicated by the cross ruling in the figure. For technical reasons, the configuration in the figure is easiest to manufacture if the crystals S1 and S2 are each composed of two separate crystals that are fused together along the line that is the x-axis in the figure. For this reason, this is called the tetracrystal geometry. A superconducting layer is deposited epitaxially on the substrate, and the grain boundary A'AVBB' forms a Josephson junction. The dashed circle is not part of the experimental setup, but its arcs give the paths of a contour integrals described in the text.

In fact, for the special case of $\alpha = 45^{\circ}$ in the symmetric tetracrystal geometry, an additional symmetry comes into play resulting in predictions of remarkable simplicity (see Table I below). Thus the symmetric tetracrystal geometry, which has certain advantages relative to the tricrystal geometry even in the cases where no broken time-reversal symmetry is envisaged^{1,19,20}, should be the geometry of choice for the investigation of differences between broken-time reversal symmetry states.

The nature of the spontaneous flux generated at the vertex V in Fig. 1 can be determined by using Ginzburg-Landau theory, as described in Refs. 18,26,27. The superconducting order is characterized by an order parameter having two components ψ_d and $\psi_{d'}$. (This is for the d + id' case; for the d + is case the two components are called ψ_d and ψ_s .) Also, the value of the λ 'th component (λ is d or d') of the order parameter at the point J (J is A or B) in the j'th superconductor (j is 1 or 2 for S1 or S2) is denoted by $\psi_{\lambda J}^{(j)}$.

The free energy per unit length of the grain boundary Josephson junction at point J is

$$F_J = \sum_{\lambda,\lambda'} C_{\lambda\lambda'J} \left[\psi_{\lambda J}^{(1)*} \psi_{\lambda'J}^{(2)} exp\left(i\frac{2\pi}{\Phi_0} \int_{J1}^{J2} \mathbf{A} \cdot d\ell\right) + c.c. \right],$$
(2)

which is consistent with gauge invariance and timereversal symmetry. The line integral from point J1 to J2 in this equation is across the grain boundary at point J from superconductor S1 to S2. The fact that the x-axis is an axis of reflection symmetry imposes the conditions $C_{\lambda\lambda A} = -C_{\lambda\lambda B}$ and $C_{\lambda\lambda' A} = C_{\lambda\lambda' B}$ for $\lambda \neq \lambda'$. (For the d + is case the corresponding relations are $C_{ddA} = -C_{ddB}, C_{ssA} = C_{ssB}, C_{sdA} = C_{sdB}$, and $C_{dsA} = -C_{dsB}$.) It is these symmetry relations that allows a definitive interpretation of experiments performed in the tetracrystal geometry to be made without recourse to a detailed model of the angular dependence of the Josephson junction current¹⁸.

The assumption of a d + id' state is implemented by taking the order parameters to have the form

$$\psi_{dJ}^{(j)} = |\psi_{dJ}^{(j)}| e^{i\phi_{Jj}}, \quad \psi_{d'J}^{(j)} = \sigma_{Jj} i |\psi_{dJ}^{(j)}| e^{i\phi_{Jj}}.$$
 (3)

Note the additional factor of i (which characterises the d + id' state) in the definition of $\psi_{d'J}^{(j)}$. Also, σ_{Jj} can have the values ± 1 corresponding to the two possible variants $d \pm id'$, each of which has the same free energy. For a bulk broken time-reversal symmetry state in, say, superconductor S1, this state would be expected to be characterized by either the order parameter d + id' or d - id' throughout the entire crystal S1 because a change from one variant to the other would cost energy. Thus we would have $\sigma_{A1} = \sigma_{B1}$, i.e. that same state of super-conductor S1 at both junctions.

On the other hand, it is also interesting to consider the case of a superconductor that has pure *d*-wave symmetry

in the bulk, but in which the *d*-wave superconductivity is suppressed at the junction interface with the simultaneous appearance of a d' order parameter there, so that at the junction interface one has $d \pm id'$ superconductivity. In this case one might have d+id' surface superconductivity in superconductor S2 at junction A and d-id' surface superconductivity in superconductor S2 at junction B, so that σ_{A2} and σ_{B2} are not necessarily equal.

Now put the above expressions for the order parameter into the junction free energy of Eq. 2, and define a critical current per unit length along the grain boundary, I_A , and a phase θ_A , characteristic of the grain boundary Josephson junction at A by

$$\frac{\Phi_0}{4\pi c} I_A e^{i\theta_A} \equiv g_{dd} + \sigma_{A1} \sigma_{A2} g_{d'd'} + i(\sigma_{A2} g_{dd'} - \sigma_{A1} g_{d'd}),$$
(4)

where

$$g_{\lambda\lambda'} \equiv C_{\lambda\lambda'A} |\psi_{\lambda A}^{(1)}| |\psi_{\lambda'A}^{(2)}|.$$
(5)

Similarly, for point B on the grain boundary, define I_B and θ_B by

$$\frac{\Phi_0}{4\pi c} I_B e^{i\theta_B} \equiv g_{dd} + \sigma_{B1} \sigma_{B2} g_{d'd'} - i(\sigma_{B2} g_{dd'} - \sigma_{B1} g_{d'd}).$$
(6)

The fact that the x axis of Fig. 1 is a line of reflection symmetry has the important consequence that the same coefficients $g_{\lambda\lambda'}$ that appear in Eq. 4 also appear in Eq. 6. The grain boundary junction free energies per unit length at points A and B can now be written

$$F_A = \frac{\Phi_0}{2\pi c} I_A \cos(\phi_A + \theta_A),\tag{7}$$

and

$$F_B = \frac{\Phi_0}{2\pi c} I_B \cos(\phi_B + \theta_B + \pi). \tag{8}$$

where

$$\phi_J = \phi_{J2} - \phi_{J1} + \frac{2\pi}{\Phi_0} \int_{J1}^{J2} \mathbf{A} \cdot d\ell.$$
(9)

Note that the values of σ_{Jj} in Eqs. 4 and 6 have not yet been chosen. These should be chosen so that the critical currents I_A and I_B have their maximum possible magnitudes, thus leading ultimately to the lowest possible free energy for the system.

A measurement of the spontaneous magnetic flux through the grain-boundary Josephson junction of Fig. 1 in a direction normal to the page shows that the flux is concentrated in the neighborhood of the vertex V, and falls exponentially to zero as one proceeds along the grain boundary in the direction of either A or B¹. The characteristic length scale of this fall off is the Josephson penetration depth. It is assumed that the points A and B are many Josephson penetration depths away from the vertex V so that there is no flux through the grain boundary at points A and B, nor is there any current flowing across the grain boundary at these points. The free energies F_A and F_B will therefore have their minimum values at these points, leading to the results

$$\phi_A + \theta_A + \pi = 0, \quad \phi_B + \theta_B = 0, \quad (mod2\pi). \tag{10}$$

Next note that since the dashed circle is many penetration depths from the vertex V, there are no currents flowing in the superconductor in its vicinity. It follows that

$$\phi_{Aj} - \phi_{Bj} + \frac{2\pi}{\Phi_0} \int_{Bj}^{Aj} \mathbf{A} \cdot d\ell = 0.$$
 (11)

where the line integral follows an arc of the dashed circle in Fig. 1. Finally, combining Eqs. 9, 10, and 11 leads to the result that the spontaneous flux through the grain boundary junction at the vertex V is

$$\Phi_{spont} = \left[n + \frac{1}{2} - \frac{\theta_B - \theta_A}{2\pi} \right] \Phi_0.$$
 (12)

For the sake of definiteness, choose θ_A and θ_B (which previously have been defined mod 2π) such that $0 < (\theta_B - \theta_A) \le 2\pi$. Also, up to now the magnetic energy $\Phi^2/(2L)$ has been assumed to be small in comparison with the free energies of Eqs. 7 and 8, and has been left out of the problem. Since the magnetic free energy is a positive definite function of the flux Φ , the state (i.e. the value of n in Eq. 12) giving the lowest value of the total free energy is the one for which the flux is

$$\Phi_{min} = \left[\frac{1}{2} - \frac{\theta_B - \theta_A}{2\pi}\right] \Phi_0.$$
(13)

This minimum flux is such that $-\Phi_0/2 < \Phi_{min} \le \Phi_0/2$. Thus the state corresponding to n = 0 in Eq. 12 is the ground state, and the states corresponding to n a nonzero integer are possible metastable states.

In discussing the bulk $d \pm id'$ states, the requirements $\sigma_{Aj} = \sigma_{Bj}$ (see above) are inserted into Eqs. 4 and 6, yielding $\theta_B = -\theta_A$. An interesting limit is that in which the *d* component of the order parameter is assumed to be much greater than the d' component. An examination of Eqs. 4 and 6 in this case shows that, so long as α is not too close to 45°, the term in g_{dd} is expected to dominate on the right hand side, and hence $|\theta_A| = |\theta_B|$ will be much less than π . This results in an approximately half integral flux quantum effect, which is not very different from what is expected for a pure d state. The departure of the spontaneously generated flux from $\Phi_0/2$ will grow as the magnitude of $\psi_{d'}$ grows relative to that of ψ_d . Thus, to detect broken time-reversal symmetry with $|\psi_{d'}| \ll |\psi_d|$ requires a high precision measurement of the spontaneous flux, because the signature of the presence of a small d' component of the order parameter is a small departure of the spontaneous flux from

 $\Phi_0/2$. For $\alpha = 45^\circ$ however, an additional symmetry of the Josephson junctions requires that $g_{dd} = g_{d'd'} = 0$. This yields $\theta_A = -\theta_B = \pm \pi/2$ and a spontaneous flux $\Phi = n\Phi_0$, which is precisely the same result as would be obtained for a classical s-wave superconductor. The result that the broken time-reversal symmetry d + id' state has $\Phi = n\Phi_0$ as its flux quantization condition for this geometry is quite remarkable since broken time-reversal symmetry states are generally believed to have the flux quantization condition $\Phi = (n+f)\Phi_0$, where the fraction f satisfies $-1/2 < f \leq 1/2$ and is neither precisely 0 nor precisely 1/2. In summary note that, for the d+id' state, the geometries with $\alpha \sim 22^{\circ}$ and $\alpha = 45^{\circ}$ lead to completely different flux quantization conditions, and that these different conditions give a way of experimentally identifying a d + id' state.

The introduction to this article cites several theoretical studies that suggest a bulk d-wave superconductor will tend to exhibit a suppressed *d*-wave order parameter at a [110] surface, possibly accompanied by the presence of a d' or s component at this surface, and with these components phased in such a way that the overall state at the surface has d + id' or d + is symmetry. An appropriate geometry in which to study such states is to take the angle α in Fig. 1 to be 45 degrees. There is then the possibility of a surface d+id' or surface d+is state in the superconductor S2 (but not S1) along the grain boundaries A'AV and VBB'. There are two inequivalent possibilities for the surface states of the two grain boundary segments: A'AV can be $d \pm id'$ while VBB' is also $d \pm id'$, or A'AV can be $d \pm id'$ while VBB' is $d \mp id'$ (here take only the upper signs, or only the lower signs). There is an interaction energy at the vertex V which should give these two inequivalent possibilities different free energies, but this interaction energy will be much smaller than the Josephson energy of the entire grain boundary and therefore the assumption will be made below that both possibilities can occur for the same sample.

From the work already done above, it follows that the case of purely *d*-wave symmetry in the bulk, with $d \pm id'$ surface superconductivity at the [110] surface of superconductor S2 for the case of $\alpha = 45^{\circ}$ also yields a flux quantization condition $\Phi = n\Phi_0$ for the case $\sigma_{A2} = \sigma_{B2}$, but with the new feature that there is the possibility of a states of the same sample having the flux quantization condition $\Phi = (n + \frac{1}{2})\Phi_0$ for $\sigma_{A2} = -\sigma_{B2}$. Of all of these states, the ground state is the one with zero flux. Again, it is remarkable that the broken time-reversal symmetry surface states for this geometry lead to flux quantization conditions usually thought to be characteristic of states without broken time reversal symmetry.

The analysis of the d + is case is similar, except that the defining equations for the critical currents and characteristic phases, Eqs. 4 and 6, are replaced by

$$\frac{\Phi_0}{4\pi c} I_A e^{i\theta_A} \equiv g_{dd} - \sigma_{A1} \sigma_{A2} g_{ss} + i(-\sigma_{A1} g_{sd} + \sigma_{A2} g_{ds}),$$
(14)

and

$$\frac{\Phi_0}{4\pi c} I_B e^{i\theta_B} \equiv g_{dd} + \sigma_{B1} \sigma_{B2} g_{ss} + i(\sigma_{B1} g_{sd} + \sigma_{B2} g_{ds}).$$
(15)

Arguments similar to those given above lead to the result that the spontaneous flux at the vertex V in Fig. 1 is again given by Eq. 12.

Now consider the limit of the bulk $d \pm is$ case in which the magnitude of the *d* component of the order parameter is much greater than that of the s component. An examination of Eqs. 14 and 15 in this case shows that, so long as α is not too close to 45°, the term in g_{dd} is expected to dominate the right hand side, and hence $|\theta_A|$ and $|\theta_B|$ will be much less than π . This results in an approximately half integral flux quantum effect, which is not very different from what is expected for a pure d state, nor from the d + id' case for the corresponding values of α . Now note that for $\alpha = 45^{\circ}$, the additional symmetry of the Josephson junctions requires that $g_{dd} = g_{sd} = 0$. (Also, $|g_{ss}| \ll |g_{ss}|$.) This yields $\theta_A \simeq \theta_B \simeq \pi/2$ or $\theta_A \simeq \theta_B \simeq -\pi/2$. Hence for $\alpha = 45^\circ$ also the approximate half integral flux quantum effect is preserved, which is very different from what was predicted above for the bulk d + id' case. Thus, the symmetric tetracrystal geometry for $\alpha = 45^{\circ}$ can in principle distinguish between the bulk d + id' and d + is states.

The case of purely *d*-wave symmetry in the bulk, with $d \pm is$ surface superconductivity at the [110] surface of superconductor S2 for the case of $\alpha = 45^{\circ}$ yields the flux quantization conditions of $\Phi = n\Phi_0$ for $\sigma_{A2} = \sigma_{B2}$ and $\Phi = (n + \frac{1}{2})\Phi_0$ for $\sigma_{A2} = -\sigma_{B2}$. These and other results are summarized in Table I.

The grain boundaries that occur in Fig. 1 for $\alpha = 45^{\circ}$ are called 45° [001] tilt grain boundaries. Scanning SQUID microscope imaging of such grain boundaries in YBa₂Cu₃O_{6+x} reveals very weak spontaneously generated delocalized flux along these grain boundaries²⁸. This is thought to be due to either grain-boundary

TABLE I. The flux quantization conditions for the tetracrystal geometry of Fig. 1 with the angle $\alpha = 45^{\circ}$ for a number of different broken time-reversal symmetry states. For the surface case, the two states given represent the surface states in superconductor S2 on grain boundaries A and B, respectively, of Fig. 1. Also, f satisfies $-\frac{1}{2} < f < \frac{1}{2}$, but is not zero; although f can not be precisely $\frac{1}{2}$, it is expected to be close to $\frac{1}{2}$ if the time-reversal symmetry breaking is weak.

state ($\alpha = 45^{\circ}$ in all cases)	flux quantization
bulk $d + id'$	$n\Phi_0$
bulk $d + is$	$(n+f)\Phi_0$
surface $d + id'$, $d + id'$	$n\Phi_0$
surface $d + id', d - id'$	$(n+\frac{1}{2})\Phi_0$
surface $d + is$, $d + is$	$(n+rac{1}{2})\Phi_0 \ (n+rac{1}{2})\Phi_0$
surface $d + is$, $d - is$	$n\Phi_0$

faceting²⁸, or the existence of orthorhombic twins²⁹ in the YBa₂Cu₃O_{6+x}, or both. To avoid this effect (which can be detected using scanning SQUID microscopy as just mentioned) the material studied should be tetragonal and not orthorhombic (thus avoiding twinning) and the grain boundaries should be as straight as possible. In the case of d+is and d+id' states, the additional component of the order parameter (in addition to the *d*-wave component) provides an additional coupling which, if large enough, will overcome the effects giving rise to the spontaneous delocalized grain boundary flux (which results from the fact that usual *d*-wave Josephson coupling is zero for an ideally flat 45° [001] tilt grain boundary).

This article has considered measurements of the pairing symmetry made using the tetracrystal geometry. For the bulk d+id' and d+is states, and for the value $\alpha \sim 22^{\circ}$ (see Fig. 1) advocated in Refs. 18 and 19, the flux quantization condition is $\Phi = (n+f)\Phi_0$, where f is a fraction satisfying -1/2 < f < 1/2; also $f \neq 0$. If the magnitude of the symmetry breaking is small, f is expected to be close to 1/2, and the measurements must be relatively high precision to detect the small differences of the spontaneous flux from the value of $\Phi_0/2$. However, striking differences between the bulk d+id' and d+is states occur in the highest symmetry case where the angle $\alpha = 45^{\circ}$. In this case, the d+id' state should exhibit a spontaneous flux of zero while the d + is state should exhibit a spontaneous flux of approximately $\Phi_0/2$. This should provide a way of experimentally identifying a state with d + id'symmetry. For bulk superconductivity that is purely dwave, and surface superconductivity of the type d+id' or d+is at junctions A and B in superconductor S2 of Fig. 1 with $\alpha = 45^{\circ}$, the flux quantization may be either of the type $\Phi = n\Phi_0$ or of the type $\Phi = (n + \frac{1}{2})\Phi_0$, depending on whether the surface states on the two differently oriented grain boundaries in Fig. 1 are the same, or are time-reversed conjugates. Interestingly, in this highest symmetry geometry, flux quantization conditions usually expected for states without broken time-reversal symmetry [i.e. $\Phi = \Phi_0$ or $\Phi = (n + \frac{1}{2})\Phi_0$] are also found for several broken time-reversal symmetry states.

I would like to thank J. Y. T. Wei and C. C. Tsuei for the discussions that led to this article, C. C. Tsuei and L. Taillefer for useful comments on the manuscript, and the Natural Sciences and Engineering Research Council for support.

¹ C. C. Tsuei and J. R. Kirtley, "Pairing symmetry in cuprate superconductors," to appear in Rev. Mod. Phys.

² A. V. Balatsky, Phys. Rev. Lett. **80**, 1972 (1998).

³ D. S. Rokhsar, Phys. Rev. Lett. **70**, 493 (1993).

⁴ R. B. Laughlin, Phys. Rev. Lett. **80**, 5188 (1998).

⁵ R. Movshovich, M. A. Hubbard, M. B. Salamon, A. V.

Balatsky, R. Yoshizaki, J. L. Sarrao, and M. Jaime, Phys. Rev. Lett. **80**, 1968 (1998).

- ⁶ K. Krishana, N. P. Ong, q. Li, G. D. Gu, and N. Koshizuka, Science **277**, 83 (1998).
- ⁷ Q.P. Li, B. E. C. Koltenbah, and R. Joynt, Phys. Rev. B **48**, 437 (1993).
- ⁸ M. Matsumoto and H. Shiba, J. Phys. Soc. Japan **64**, 3384, 4867 (1995).
- ⁹ M. I. Salkola and J. R. Schrieffer, Phys. Rev. 58, R5952 (1998).
- ¹⁰ K. Kashiwaya, Y. Tanaka, M. Koyanagi, H. Takashima and K. Kajimura, J. Phys. Chem. Solids 56, 1721 (1995).
- ¹¹ M. Fögelstrom, D. Rainer, and J. A. Sauls, Phys. Rev. Lett 80, 4763 (1998).
- ¹² J.-X. Zhu and C. S. Ting, Phys. Rev. B **57**, 3038 (1998).
- ¹³ J.-X. Zhu, B. Friedman and C. S. Ting, Phys. Rev. B 59, 3353 (1999).
- ¹⁴ M. Covington, M. Aprili, E Paraoanu, L. H. Greene, F. Xu, J. Zhu, and C. A. Mirkin, Phys. Rev. Lett. **79**, 277 (1977).
- 15 C. C. Tsuei and J. R. Kirtley, cond-mat/0002341.
- ¹⁶ L. Taillefer, reported at the M2S-HTSC-VI Conference on Superconductivity in Houston, February 2000.
- ¹⁷ N. E. Hussey, K. Behnia, H. Takagi, C. Urano, S. Adachi, and S. Tajima, cond-mat/0004094
- ¹⁸ M. B. Walker and J. Luettmer-Strathmann, Phys. Rev. B 54, 588 (1996).
- ¹⁹ C. C. Tsuei, J. R. Kirtley, Z. F. Ren, J. H. Wang, H. Raffy, and Z. Z. Li, Nature **387**, 481 (1997).
- ²⁰ R. R. Schulz, B. Chesca, B. Goetz, C. W. Schneider, A. Schmehl, H. Bielefeldt, H. Hilgenkamp, J. Mannhart and C. C. Tsuei, App. Phys. Lett. **76**, 912 (2000).
- ²¹ H. Hilgenkamp, C. W. Schneider, B. Goetz, R. R. Schulz, A. Schmehl, H. Bielefeldt and J. Mannhart, Supercond. Sci. Technol. **12**, 1043 (1999).
- ²² H. Hilgenkamp and J. Mannhart, App. Phys. Lett. **73**, 265 (1998).
- ²³ U. Schoop, S. Kleefisch, S. Meyer, A. Marx, L. Alff and R. Gross, IEEE Trans. on Appl. Supercond. 9, 3409 (1999).
- ²⁴ M. Sigrist and T. M. Rice, J. Phys. Soc. Japan **61**, 4283 (1992).
- ²⁵ C. C. Tsuei, J. R. Kirtley, C. C. Chi, L. S. Yu-Jahnes, A. Gupta, T. Shaw, J. Z. Sun and M. B. Ketchen, Phys. Rev. Lett. **73**, 593 (1994).
- ²⁶ A. F. Andreev, JETP Lett. **46**, 584 (1987).
- ²⁷ M. Sigrist and T. M. Rice, Rev. Mod. Phys. **65**, 503 (1995).
- ²⁸ J. Mannhart, H. Hilgenkamp, B. Mayer, Ch. Gerber, J. R. Kirtley, K. A. Moler, and M. Sigrist, Phys. Rev. Lett. **77**, 2782, (1996).
- ²⁹ M. B. Walker, Phys. Rev. B **54**, 13269, (1996).