Optical studies of charge dynamics in the optimally-doped $Bi_2Sr_2CaCu_2O_{8+\delta}$ and the non-superconducting $(Bi_{0.5}Pb_{0.5})_2Ba_3Co_2O_{\delta}$ single crystals

J.J. Tu¹, C.C. Homes¹, G.D. Gu¹, D.N. Basov², S.M. Loureiro³, R.J. Cava³, and M. Strongin^{1,*}

¹Department of Physics, Brookhaven National Laboratory, Upton, New York 11973

²Physics Department, University of California at San Diego, La Jolla, California 92093-0319

³Department of Chemistry and Materials Institute, Princeton University, Princeton, New Jersey 92093-0319

(November 16, 2018)

An analysis of the frequency-dependent scattering rate $\tau^{-1}(\omega)$ reveals signatures of the superconducting gap as well as the pseudogap in high- T_c cuprates. These features can be identified in the temperature-dependent spectral function $W(\omega)$, inverted from the optical data of the optimallydoped Bi₂Sr₂CaCu₂O_{8+ δ} (Bi2212) using an experimentally unambiguous method that shows the behavior of both the maxima and minima in the spectral function.

PACS: 74.25.Gz, 74.72.Hs, 74.25.Nf

For superconductors of the type described by the Bardeen-Cooper-Schrieffer (BCS) theory, the spectral function $\alpha^2 F(\omega)$ contains all the relevant information concerning superconductivity [1]. Experimentally, $\alpha^2 F(\omega)$ is commonly obtained from tunneling I-V curves. These measurements reveal features in the quasiparticle density of states that are the results of electron-phonon interaction and with the well developed Eliashberg theory can lead to the determination of $\alpha^2 F(\omega)$ [2]. In principle the optical conductivity and the frequency-dependent scattering rate can also be used to determine the spectral function, $\alpha^2 F(\omega)$, for BCS superconductors [3–5]. Recently it has been recognized the same kind of analysis can be used to determine a spectral function $W(\omega)$ for dwave high- T_c superconductors [6] from the optical data. This has lead to the conclusion that charge coupling to the spin resonance [7] found in neutron scattering is the analogue to the common electron-phonon interaction in BCS superconductors. We will, however, avoid addressing directly the question of whether high- T_c cuprates are BCS superconductors. Instead, we will take a more empirical approach to discuss the common features in the spectral functions of different high- T_c cuprates and how they move with temperature, especially around T_c .

In this Letter, we report an analysis of the temperature-dependent spectral function $W(\omega)$, obtained from an inversion of new optical data for optimally-doped Bi2212 using an experimentally unambiguous technique that examines the maxima and minima in $W(\omega)$ simultaneously. A comparison with the spectral function of optimally-doped YBa₂Cu₃O_{6.95} (YBCO) suggests that a pseudogap exists in optimallydoped Bi2212 above T_c at 100 K, but not in optimally-doped YBCO and that the pseudogap can co-exist with the superconducting gap in optimallydoped Bi2212 below T_c . The spectral function of the metallic non-superconducting (non-SC) cobaltate $(Bi_{0.5}Pb_{0.5})_2Ba_3Co_2O_{\delta}$ single crystals, which are isomorphic to Bi2212 in terms of crystal structure [8–10], is included as a potential application of the spectral function

analysis showing that strong spin-charge coupling does not necessarily lead to superconductivity.

The *ab*-plane optical reflectance of optimally-doped Bi2212 single crystals has been measured extensively [11,12]. Furthermore, a number of cobaltates Bi₂M₃Co₂O_{δ}, (M=Ca, Sr, and Ba) have been studied optically at room temperature [8,9]. However, with much improved signal-to-noise ratio, our detailed temperature-dependent studies of optimally-doped Bi2212 and metallic (Bi_{0.5}Pb_{0.5})₂Ba₃Co₂O_{δ} have revealed a number of new features. For this study, large optimally-doped Bi2212 single crystals are grown using the traveling-surface-floating-zone (TSFZ) method. The single crystal metallic cobaltate samples (Bi_{0.5}Pb_{0.5})₂Ba₃Co₂O_{δ} are prepared using a flux technique [10].

The crystals are mounted on an optically-black cone, and the temperature-dependent reflectance from 6 K to 295 K is measured in a near-normal incidence arrangement from ≈ 100 to over 15 000 cm⁻¹ on a Bruker IFS 66v/S. The absolute reflectance is determined by evaporating a gold film (≈ 100 nm in thickness) in situ in a high vacuum ($\approx 1 \times 10^{-8}$ Torr) over the sample at the end of the reflectivity measurements at 295 K, and then measuring the reflectance again [13]. The optical properties are determined from a Kramers-Kronig analysis of the reflectance. The conductivity data is analyzed in the extended-Drude formalism [14] with a frequencydependent scattering rate $\tau^{-1}(\omega)$ defined as

$$\tau^{-1}(\omega) = \frac{\omega_p^2}{4\pi} \Re\left[\frac{1}{\tilde{\sigma}(\omega)}\right],\tag{1}$$

where ω_p is the classical plasma frequency.

In Fig. 1, temperature-dependent *ab*-plane optical data are shown for an optimally-doped Bi2212 single crystal with *E*-vector parallel to the *a*-axis. Two optic phonons at 477 and 630 cm⁻¹ have been observed for the first time in conductivity measurements. The temperaturedependent reflectance is given in Fig. 1(a) from about 100 to 2000 cm⁻¹, $\sigma_1(\omega)$ in Fig. 1(b), and the scattering rate



FIG. 1. The temperature-dependent ab-plane optical data of an optimally-doped Bi2212 single crystal with the $E \parallel a$ from 100 to 2000 cm⁻¹. (a) the temperature-dependent reflectance; (b) the temperature-dependent $\sigma_1(\omega)$; (c) the temperature-dependent $\tau^{-1}(\omega)$.

 $\tau^{-1}(\omega)$ calculated from Eq. (1) in Fig. 1(c). The value of $\omega_p = 16\,000 \text{ cm}^{-1}$ is derived from the optical conductivity sum rule at 295 K. The temperature dependence of the scattering rate $\tau^{-1}(\omega)$ is of interest here. Above 200 K, the scattering rate $\tau^{-1}(\omega)$ is a monotonically increasing function with frequency as shown in Fig. 1(c). As the temperature approaches T_c (about 91 K), abrupt curvature changes start to appear below 100 K, most noticeably as a suppression of $\tau^{-1}(\omega)$ for frequencies less than about 600 cm⁻¹. There are two positions where such changes in curvature can be clearly identified at the lowest temperature, 6 K. These two positions are marked with two vertical lines in Fig. 1(c). Similar behavior is observed in the temperature-dependent reflectance in Fig. 1(a), and $\sigma_1(\omega)$ in Fig. 1(b).

Carbotte *et al.* [6] and Abanov *et al.* [7] analyzed the features in $\tau^{-1}(\omega)$ by using an estimated spectral function:

$$W(\omega) = \frac{1}{2\pi} \frac{d^2}{d\omega^2} \left[\frac{\omega}{\tau(\omega)} \right].$$
 (2)

In the case of BCS superconductors, $W(\omega)$ is closely related to the electron-phonon spectral function $\alpha^2 F(\omega)$ [3–5], and Carbotte *et al.* [6] argued that for high T_c cuprates, $W(\omega)$ can be directly associated with the spincharge excitation spectral density, $I^2\chi''(\omega)$, derived from spin-polarized inelastic neutron scattering. In particular, the peak in $W(\omega)$ is correlated to $\Delta + \Delta_s$ below T_c . In a more recent theoretical paper, Abanov *et al.* [7] also studied $W(\omega)$ in cuprates by examining the singularities in the optical response function. However, they argued



FIG. 2. An unambiguous method of extract the spectral function $W(\omega)$. (a) The experimentally measured quantity ω/τ at 6 K for optimally-doped Bi2212, together with the smoothed experimental data and three polynomial fits to the data; (b) the first derivatives of the five curves in (a); (c) the second derivatives of the three polynomial fits to ω/τ , and the second derivative of the smoothed ω/τ .

that the deep minimum in $W(\omega)$, which in their picture is located at $2\Delta + \Delta_s$, is more relevant to superconductivity. They also identified two weaker high frequency singularities at 4Δ and $2\Delta + 2\Delta_s$.

In Fig. 2 an unambiguous way of extracting the spectral function $W(\omega)$ from the experimental data is demonstrated. The measured quantity ω/τ at 6 K is plotted for optimally-doped Bi2212 in Fig. 2(a), together with the smoothed experimental data and three polynomial fits to the data. In Fig. 2(b), the first derivatives of the curves shown in Fig. 2(a) are presented. The first derivative of the experimental data (the two optic phonons at 477 and 630 cm^{-1} are removed) is included to illustrate that it has the same trend as the other curves. In Fig. 2(c), the spectral function $W(\omega)$ derived from different methods are plotted for T = 6 K. The $W(\omega)$ determined from the smoothed ω/τ is still very noisy, but gives the same maximum and minimum as the polynomial fits. Because there are too many different ways of smoothing the experimental data that do not always give consistent results, fitting the experimentally measured quantity ω/τ with a highorder polynomial is adopted as the unambiguous method of extracting the spectral function $W(\omega)$ from the optical data in this study.

The temperature dependence of the spectral function $W(\omega)$ calculated using the procedure outlined in the preceding paragraph is shown in Figs. 3(a) and 3(b) for a optimally-doped Bi2212 single crystal and a untwinned



FIG. 3. The temperature dependence of the spectral function $W(\omega)$ of an optimally-doped Bi2212 single crystal, and a untwinned optimally-doped YBCO single crystal with $E \parallel a$ in the *ab*-plane (20 term polynomial fits are used). (a) $W(\omega)$ of an optimally-doped Bi2212 single crystal at four different temperatures; (b) $W(\omega)$ of a optimally-doped YBCO single crystal at three different temperatures.

optimally-doped YBCO single crystal [15], respectively. For the optimally-doped Bi2212, there is a well defined maximum in $W(\omega)$ at around 70 meV, a deep minimum at around 110 meV, and a weak high-energy maximum at around 150 meV at 6 K. According the two theoretical pictures [6,7] that rely on spin-charge coupling in high T_c cuprates, these maxima and minima positions correspond to $\Delta + \Delta_s$, $2\Delta + \Delta_s$ and $2\Delta + 2\Delta_s$, respectively. One can therefore uniquely determine the averaged values of the superconducting gap $\Delta = 33 \pm 3$ meV and the spin resonance $\Delta_s = 41 \pm 3$ meV from the optical data. These optically obtained values agree very well with the directly measured values of $\Delta = 30 \text{ meV} [16]$ and $\Delta_s = 43 \text{ meV}$ [17] for optimally-doped Bi2212. As the temperature increases to 80 K, the maximum in $W(\omega)$ seems to split into two peaks while the position of the minimum shows little change. At a temperature of T = 100 K, just above T_c , the maximum in $W(\omega)$ has shifted to 40 meV which is precisely Δ_s for optimally-doped Bi2212 [17], and the minimum has disappeared completely into the noise.

The temperature-dependent $W(\omega)$ for a untwinned optimally-doped YBCO single crystal is shown in Fig. 3(b). The general features of $W(\omega)$ at the lowest temperature T = 10 K is very similar to that of the optimally-doped Bi2212, showing a maximum at around 67 meV, a minimum at around 105 meV and a weaker maximum at around 145 meV. One can again determine the averaged values of the superconducting gap $\Delta = 30 \pm 4$ meV and the spin resonance $\Delta_s = 40 \pm 4$ meV from the optical data. These optically obtained values



FIG. 4. The temperature-dependent unpolarized *ab*-plane optical data of a $(Bi_{0.5}Pb_{0.5})_2Ba_3Co_2O_\delta$ single crystal. (a) The temperature-dependent reflectance; (b) the temperature-dependent $\tau^{-1}(\omega)$; (c) the temperature-dependent spectral function $W(\omega)$ (20 term polynomial fits are used).

also agree very well with the directly measured values of $\Delta = 27 \text{ meV} [18] \text{ and } \Delta_s = 41 \text{ meV} [19] \text{ for optimally-}$ doped YBCO. The main difference between the Bi2212 and YBCO data is the fact that while there is a weak maximum at Δ_s in $W(\omega)$ above T_c for optimally-doped Bi2212 at 100 K, it is absent in optimally-doped YBCO [20]. This observation agrees with the suggestion that the phase diagrams for Bi2212 and YBCO are different [21]; namely there is a pseudogap in optimally-doped Bi2212 above T_c , but there is no pseudogap in optimally-doped YBCO. Furthermore, the lineshape of the spectral function at 80 K for optimally-doped Bi2212 indicates that the pseudogap and the superconducting gap can coexist below T_c adding support to the idea that the two may have the same microscopic origin [21]. We have also made some preliminary measurements on an $La_{2-x}Sr_xCuO_4$ (x = 0.17) (LSCO) sample $(T_c = 38 \text{ K})$ which does not show any prominent features in the spectral function $W(\omega)$ that can be associated with superconductivity. This is consistent with the neutron scattering results that do not show any prominent spin resonance peaks in this system [22]. Therefore, the theoretical picture of spin-charge coupling is in good agreement with the optical data for all three high- T_c cuprates.

As a potential application the spectral function $W(\omega)$ analysis, a temperature-dependent optical study is carried out on a cobaltate, $(Bi_{0.5}Pb_{0.5})_2Ba_3Co_2O_{\delta}$. No T_c is observed and this sample is shown to be metallic down to 30 mK [10]. The temperature dependent optical data for $(Bi_{0.5}Pb_{0.5})_2Ba_3Co_2O_{\delta}$ is shown in Fig. 4. Because of the low carrier density in this crystal, four sharp phonon peaks are observed in reflectance and $\tau^{-1}(\omega)$ in the region between 450 and 650 $\rm cm^{-1}$. These phonon features are removed from the conductivity data before fitting ω/τ with polynomials. The resulting temperature dependent $W(\omega)$ is shown in Fig. 4(c). At the lowest temperature T = 10 K, there is a well defined maximum in $W(\omega)$ centered at around 500 $\rm cm^{-1}$, or about 62 meV. This maximum is detectable to about 200 K. However, there is no well defined minimum observed in $W(\omega)$ at any temperature. While there is no superconductivity, these observations indicate that there is also strong spin-charge coupling in this cobaltate. If the analysis of $W(\omega)$ is valid here, there should be a spin resonance peak at around 60 meV below 200 K in this material and this should be verifiable by inelastic neutron scattering.

In view of the temperature-dependent behavior of the spectral function $W(\omega)$ of optimally-doped Bi2212, YBCO and metallic $(Bi_{0.5}Pb_{0.5})_2Ba_3Co_2O_{\delta}$ single crystals, it is clear that both the maxima and minima in $W(\omega)$ should be examined at the same time. As one can see from our analysis of $W(\omega)$, the behavior of the strong maximum in $W(\omega)$ is well described by the theory developed by Carbotte et al. [6]. However, by strictly comparing $W(\omega)$ to $I^2 \chi''(\omega)$ obtained from neutron scattering, one ignores the negative part of $W(\omega)$ because $I^2 \chi''(\omega)$ is a positive quantity. Thus the well defined minimum in $W(\omega)$ is neglected. In the more complete picture presented recently by Abanov et al. [7], both the maxima and the minima in $W(\omega)$ are examined. In general, their calculated spectral function $W(\omega)$ agrees quite well with our experimentally extracted $W(\omega)$ except that there is no indication of the weak singularity at 4Δ in the experimental $W(\omega)$. On the other hand, the physically intuitive interpretation of the maximum in $W(\omega)$ as being directly related to $I^2 \chi''(\omega)$ is somewhat obscured. Further theoretical study is underway [23] to bridge the gap between these two different approaches. A comment should be made here that even though our experimental data and its analysis presented here are consistent with the theoretical pictures of Carbotte et al. [6] and Abanov et al. [7], the spectral function analysis alone does not exclude other coupling mechanisms, e.g. charge-phonon coupling, and there is much evidence that nanoscale charge inhomogeneities may also play an important role in these systems. One example of this is the stripe picture [24]. In particular, the lack of experimental evidence for strong spin-charge coupling in LSCO systems poses some problems for spin-mediated superconductivity in high T_c cuprates [6,7] and the data on the metallic (but non-SC) cobaltate indicates that strong spin-charge coupling maybe a necessary but not exclusive condiction for high- T_c superconductivity.

dependent analysis of the spectral function $W(\omega)$ for the optimally-doped Bi₂Sr₂CaCu₂O_{8+ δ}, YBa₂Cu₃O_{6.95} and the metallic (Bi_{0.5}Pb_{0.5})₂Ba₃Co₂O_{δ} single crystals. The behavior of the maxima and minima in $W(\omega)$ is consistent with the picture of spin-charge coupling in high- T_c cuprates. More experimental studies in the under-doped and over-doped regions of Bi2212 as well as in the metallic and insulating regions of cobaltates are now underway to further our understanding of these systems.

We would like to thank J.P. Carbotte, G.L. Carr, A.V. Chubukov, V.J. Emery, P.D. Johnson, A. Millis, T. Timusk, T. Valla, and Z. Yusof for helpful discussions. The work was supported by the U.S. Department of Energy under Contract No. DE-AC02-98CH10886. Research undertaken at NSLS was supported by the U.S. DOE, Division of Materials and Chemical Sciences.

Electronic address: myron@bnl.gov

- [1] J.P. Carbotte, Physics in Canada 56, 257 (2000).
- [2] W.L. McMillian and J. M. Rowell, Phys. Rev. Lett. 14, 108 (1965).
- [3] P.B. Allen, Phys. Rev. B **3**, 305 (1971).
- [4] B. Farnworth and T. Timusk, Phys. Rev. B 10, 5119 (1976).
- [5] F. Marsiglio, T. Startseva, and J. P. Carbotte, Phys. Lett. A 245, 172 (1998).
- [6] J.P. Carbotte, E. Schachinger, and D.N. Basov, Nature (London) 401, 354 (1999).
- [7] A. Abanov, A. V. Chubukov, and J. Schmalian, condmat/0101220, (2001).
- [8] Y. Watanabe et al., Phys. Rev. B 43, 3026 (1991).
- [9] I. Terasaki, T. Nakahashi, A. Maeda, and K. Uchinokura, Phys. Rev. B 47, 451 (1993).
- [10] S.M. Loureiro et al., Phys. Rev. B 63, 094109 (2001).
- M.A. Quijada *et al.*, Physica C 235-240, 141123 (1994);
 A.V. Puchkov *et al.*, Phys. Rev. Lett. 77, 3212 (1996);
 M.A. Quijada *et al.*, Phys. Rev. B 60, 14917 (1999).
- [12] N.L. Wang, A. W. McConnell, and B. P. Clayman, Phys. Rev. B 59, 576 (1999).
- [13] C.C. Homes, M. Reedyk, D. Crandles, and T. Timusk, Appl. Opt. **32**, 2972 (1993).
- [14] A.V. Puchkov, D. N. Basov, and T. Timusk, J. Phys. C 8, 10049 (1996).
- [15] C.C. Homes et al., Phys. Rev. B 60, 9782 (1999).
- [16] T. Valla *et al.*, Phys. Rev. Lett. **85**, 828 (2000).
- [17] H.F. Fong et al., Nature (London) 398, 588 (1999).
- [18] M.F. Limonov, A.I. Rykov, S. Tajima, and A. Yamanaka, Phys. Rev. B 61, 12412 (2000).
- [19] P. Bourges *et al.*, in High Temperature Superconductors, edited by S. E. Barnes (American Institute of Physics, Amsterdam, 1999), p. 202.
- [20] E. Schachinger, J.P. Carbotte, and D.N. Basov, Europhys. Lett. (in press).
- [21] Ch. Renner *et al.*, Phys. Rev. Lett. **80**, 149 (1998); Ø.
 Fischer, Bull. Amer. Phys. Soc. **46**, 925 (2001).
- [22] J.M. Tranquada (private communication).
- [23] J.P. Carbotte (private communication).
- [24] V.J. Emery, S.A. Kivelson, and O. Zachar, Phys. Rev. B 56, 6120 (1997).

In conclusion, we have carried out temperature-