Anisotropic properties of MgB_2 by torque magnetometry

M. Angst^{a,b}, D. Di Castro^a, R. Puzniak^c, A. Wisniewski^c, J. Jun^b, S. M. Kazakov^b,

J. Karpinski^b, S. Kohout^a, H. Keller^a

^aPhysik-Institut, Universität Zürich, 8057 Zürich, Switzerland

^bSolid State Physics Laboratory ETH, 8093-Zürich, Switzerland

^cInstitute of Physics, Polish Academy of Sciences, Aleja Lotnikow 32/46, 02-668 Warsaw, Poland

Abstract

Anisotropic properties of superconducting MgB₂ obtained by torque magnetometry are compared to theoretical predictions, concentrating on two issues. Firstly, the angular dependence of H_{c2} is shown to deviate close to T_c from the dependence assumed by anisotropic Ginzburg-Landau theory. Secondly, from the evaluation of torque vs angle curves it is concluded that the anisotropy of the penetration depth γ_{λ} has to be substantially higher at low temperature than theoretical estimates, at least in fields higher than 0.2 T.

Key words: MgB₂, anisotropy, upper critical field, penetration depth, torque PACS: 74.20.De, 74.70.Ad, 74.25.Ha, 74.25.Op

Superconductivity in two bands of different dimensionality leads to a temperature dependent anisotropy of the upper critical field $\gamma_H = H_{c2}^{\|ab}/H_{c2}^{\|c}$ [1] in MgB₂, observed, e.g., by torque magnetometry [2]. Both torque results [2] and calculations [3] of $H_{c2}(\theta)$ indicate systematic deviations from the angular dependence expected within anisotropic Ginzburg-Landau theory (AGLT). However, the deviations found experimentally are most pronounced near T_c , while the calculations [3] predict pronounced deviations at low temperature T only. Recently, new calculations of $H_{c2}(\theta)$ were carried out for the (intra-band) dirty limit [4,5]. We will show that there is good agreement in the form of the deviations of $H_{c2}(\theta)$ from AGLT between our torque results and the calculations of Ref. [5]. Calculations [6] also predicted an anisotropy of the penetration depth $\gamma_{\lambda} \ll \gamma_{H}$ at low T. A field H dependence of an effective anisotropy [2] may be taken as an indication of such a difference between γ_{λ} and γ_{H} [7]. A recent calculation of torque $\tau(\theta)$ dependences in the London regime for the case of different γ_{λ} and γ_{H} led to the prediction of a sign reversal of the torque at

low T in MgB₂ [8]. From the comparison of the $\tau(\theta)$ dependence with the predictions of Ref. [8], we find a lower limit for γ_{λ} at low temperatures, considerably higher than theoretical estimates [6].

For details concerning measurement apparatus and procedure, samples, and the determination of H_{c2} see Refs. [2,7]. $H_{c2}(\theta)$, determined from $\tau(\theta)$ curves measured in various fields at 33 K $\simeq 0.87 T_c$, is shown in Fig. 1a). By definition, τ is 0 for $H \parallel c$ or $\parallel ab$, and small for field directions close. This is why there are no data close to 0° and 90°. In AGLT, $H_{c2}(\theta)$ is described by

$$H_{c2}^{AGL}(\theta) = H_{c2}^{\parallel c} (\cos^2 \theta + \sin^2 \theta / \gamma_H^2)^{-1/2}.$$
 (1)

The best fit of Eq. (1) to the data is indicated by the full line. Small, but systematic deviations can be seen, especially when plotting the difference between experimental data and best fit vs θ (inset): at 0.87 T_c , $H_{c2}(\theta)$ is not (accurately) described by Eq. (1). Deviations from Eq. (1) were not observed at lower T (cf. Fig. 2 of Ref. [2]). Deviations most pronounced in the region of 0.9-0.95 T_c were also found in a recent calculation [5] assuming high intraband scattering (*dirty limit*). In order to compare experimentally observed deviations to the predictions of Ref. [5], we calculated "AGLT

Email address: angst@physik.unizh.ch (M. Angst).

Preprint submitted to Physica C Proceedings



Fig. 1. a) Upper critical field H_{c2} vs angle θ of a MgB₂ single crystal, at $0.87 T_c$ (symbols). Free fit of AGLT angular dependence (full line; $\mu_0 H_{c2}^{\parallel c} = 0.456$ T, $\gamma_H = 3.28$) shows clear systematic deviations, highlighted in the inset. AGLT dependence with the same parameters as used in panel b) is also shown (dotted line, $\mu_0 H_{c2}^{\parallel c} = 0.475$ T, $\gamma_H = 3.47$). b) "AGLT deviation" $\alpha(\theta)$ (see text) of the data of panel a) (symbols) and a recent calculation [5] (full line).

deviations" $\alpha(\theta) \equiv H_{c2}(\theta)/H_{c2}^{AGL}(\theta)$. For $\mu_{\circ}H_{c2}^{\parallel c} = 0.475 \text{ T}$ and $\gamma = 3.47$, $\alpha(\theta)$ has form and magnitude [Fig. 1b)] very similar to deviation functions for *calculated* [5] $H_{c2}(\theta)$ (full line) at the same temperature [9]. Although the theoretically predicted [5] $\gamma_H \simeq 4.86$ is higher than our data indicate, the similarity of the AGLT deviation suggests that (intraband) scattering cannot be neglected in theoretical descriptions of H_{c2} .

Figure 2a) shows a $\tau(\theta)$ curve measured (on a different crystal) in the mixed state close to $T_c \simeq 38.5 \,\mathrm{K}$. Near T_c , the difference between γ_{λ} and γ_H is small, in agreement with theoretical predictions [3,8]. The $\tau(\theta)$ curve measured at low T [Fig. 2b)] has the same sign as the one measured close to T_c , i.e., there is no sign change as expected [8] for $\gamma_{\lambda} \ll \gamma_{H}$. For γ_{λ} moderately lower than γ_H , Ref. [8] predicts a sign change only in an angular region close to 90° , illustrated with a dashed line in Fig. 2b). Such a partial sign change is also not observed, the maximum angular region where it could occur given by the irreversible region (the slight asymmetry in the irreversibility is due to thickness variations of the crystal). Comparing the data with curves calculated according to Ref. [8], with $\mu_0 H_{c2}^{\parallel c} = 3 \text{ T}$, $\gamma_H = 6$ [2] and various γ_λ , we conclude that γ_λ has to be at least 2.6, considerably higher than currently available theoretical estimates [6]. Alternatively, if γ_H in 0.2 T is much smaller than in $H \approx H_{c2}$ [1], the absence of a sign reversal is compatible with smaller γ_{λ} . However, we should mention that the best description of the data is given by $\gamma_{\lambda} \approx \gamma_{H} \approx 3.3$.

The discrepancy may be explained by the influence of the magnetic field, depressing superconductivity in the more isotropic π bands. This should lead to anisotropies (γ_{λ} and/or γ_{H}) increasing with increasing field [2]. An anisotropy increasing with H has also been postulated based on specific heat measurements (mostly sensitive to the coherence length, i.e., γ_{H} [1])



Fig. 2. a) Torque τ vs angle θ measured close to T_c . Dashed line: $\tau(\theta)$ calculated [8] with $\gamma_{\lambda} = \gamma_H = 2$. b) τ vs θ at low T. Dashed line: $\tau(\theta)$ calculated [8] with $\gamma_{\lambda} = 2$, $\gamma_H = 6$.

[10]. Furthermore, recent neutron scattering results indicate an increasing $\gamma_{\lambda}(H)$ [11]. The calculations of Ref. [6] are valid for the low field limit, which is difficult to accurately probe due to irreversibility (no sign reversal was found in $\tau(\theta)$ measured at low T for $0.03 \text{ T} \leq \mu_{\circ} H \leq 1.5 \text{ T}$, but for the curves measured in the lowest fields, it may be hidden by irreversibility).

In conclusion, deviations of the $H_{c2}(\theta)$ dependence from the AGLT dependence near T_c are well approximated by recent calculations [5]. While there is good agreement between experiment and theory on H_{c2} , the penetration depth anisotropy is still associated with open questions. Especially the issue of the field influence on γ_{λ} and γ_{H} [1] deserves theoretical attention.

We thank A. A. Golubov for providing calculated $H_{c2}(\theta)$ data for 0.87 T_c . This work was supported by the Swiss National Science Foundation, the European Community (ICA1-CT-2000-70018) and the Polish State Committee for Scientific Research (5 P03B 12421).

References

- [1] For $H < H_{c2}$, γ_H is generalized to mean the anisotropy of the coherence lengths ξ .
- M. Angst *et al.*, Phys. Rev. Lett. **88**, 167004 (2002); Physica C **385**, 143 (2003).
- [3] P. Miranović et al., J. Phys. Soc. Jpn. 72, 221 (2003) and private communication.
- [4] A. Gurevich, Phys. Rev. B in print, cond-mat/0212129.
- [5] A.A. Golubov and A.E. Koshelev, cond-mat/0303237.
- V.G. Kogan, Phys. Rev. B 66, 020509(R) (2002); A.A.
 Golubov et al., Phys. Rev. B 66, 054524 (2002).
- [7] J. Karpinski *et al.*, Supercond. Sci. Technol. **16**, 221 (2003).
- [8] V.G. Kogan, Phys. Rev. Lett. 89, 237005 (2002).
- [9] We note that the parameter values for which best agreement with Ref. [5] is seen are 4-5% higher than those of the AGLT "best fit".
- [10] F. Bouquet *et al.*, Phys. Rev. Lett. **89**, 257001 (2002);
 Physica C **385**, 192 (2003).

[11] M.R. Eskildsen, private communication.