Orbital-selective Mott transitions in the degenerate Hubbard model

Akihisa Koga^{1,2}, Norio Kawakami¹, T. M. Rice² and Manfred Sigrist²

¹Department of Applied Physics, Osaka University, Suita, Osaka 565-0871, Japan

² Theoretische Physik, ETH-Hönggerberg, Zürich 8093, Switzerland

(Dated: November 1, 2018)

We investigate the Mott transitions in two-band Hubbard models with different bandwidths. Applying dynamical mean field theory, we discuss the stability of itinerant quasi-particle states in each band. We demonstrate that separate Mott transitions occur at different Coulomb interaction strengths in general, which merge to a single transition only under special conditions. This kind of behavior may be relevant for the physics of the single-layer ruthenates, $Ca_{2-x}Sr_xRuO_4$.

Strongly correlated multi-orbital electron systems are among the most active topics in condensed matter physics. In the Mott insulators the addition of orbital to localized spin degrees of freedom leads to complex ordered phase diagrams. In itinerant electron systems multiple Fermi surface sheets appear with very distinct properties. Subtleties occur when localized and itinerant electrons coexist, as is well known in the case of itinerant d- and localized f-electrons which give rise to the rich physics of heavy Fermion compounds. In view of their very different character this is not so surprising. We may ask, however, whether it is possible to find coexistence of itinerant and localized electrons for degenerate nonhybridizing orbitals with small bandwidth difference.

A nearly degenerate d-electron system where multiorbital properties obviously play an important role is the single-layer isovalent ruthenate alloy $Ca_{2-x}Sr_{x}RuO_{4}$. The end-member Sr_2RuO_4 is a well-known unconventional superconductor [1, 2], while Ca₂RuO₄ is a Mottinsulating S = 1 antiferromagnet [3, 4]. The relevant 4*d*-orbitals belong to the t_{2q} -subshell. The planar structure leads to very weak hybridization between orbital which have even (d_{xy}) and odd parity (d_{yz}, d_{zx}) under the reflection $z \to -z$. The complex evolution between these different end-members has led to various theoretical investigations [4, 5], and among others to the proposal that some of the *d*-orbitals display localized spin and orbital degrees of freedom, and others provide itinerant electrons. This orbital-selective Mott transition (OSMT) could explain the experimental observation of a localized spin S = 1/2 in the metallic system at $x \sim 0.5$ which is difficult to obtain from the entirely itinerant ab initio description [3, 5, 6].

The concept of the OSMT was recently challenged, in particular, by Liebsch whose dynamical mean field theory (DMFT) calculations suggested that two bands of different width coupled by electron-electron interactions would always undergo a common Mott transition [7]. The aim of this paper is to revisit this problem and to analyze the Mott transition in the degenerate two-orbital Hubbard model with different bandwidths. Using another form of DMFT, we find a different result and an OSMT. In addition, we show also that correlations can stabilize a commensurate filling of one band even when the total electron count is fractional.

We consider the following Hubbard Hamiltonian with two orbitals,

$$H = \sum_{\substack{\langle i,j\rangle \\ \alpha,\sigma}} \left(t_{ij}^{(\alpha)} - \mu_{\alpha} \delta_{ij} \right) c_{i\alpha\sigma}^{\dagger} c_{j\alpha\sigma} + U \sum_{i\alpha} c_{i\alpha\uparrow}^{\dagger} c_{i\alpha\uparrow} c_{i\alpha\downarrow}^{\dagger} c_{i\alpha\downarrow} + U' \sum_{i\sigma\sigma'} c_{i1\sigma}^{\dagger} c_{i1\sigma} c_{i2\sigma'}^{\dagger} c_{i2\sigma'} - J \sum_{i} c_{i1\sigma}^{\dagger} c_{i1\sigma'} c_{i2\sigma'}^{\dagger} c_{i2\sigma} - J \sum_{i} \left[c_{i1\uparrow}^{\dagger} c_{i1\downarrow}^{\dagger} c_{i2\uparrow} c_{i2\downarrow} + H.c. \right]$$
(1)

where $c_{i\alpha\sigma}^{\dagger}(c_{i\alpha\sigma})$ creates (annihilates) an electron with spin $\sigma(=\uparrow,\downarrow)$ and orbital index $\alpha(=1,2)$ at the *i*th site. We restrict ourselves to the case of non-hybridizing orbitals, relevant to the ruthenates, and $t_{ij}^{(\alpha)}$ denotes the hopping integral for orbital α , μ the chemical potential, U(U') the intraband (interband) Coulomb interaction and J the Hund coupling. In the following, we restrict our discussions to the condition U = U' + 2J, obtained by symmetry arguments for degenerate orbitals.

We examine the stability of the metallic ground state of this model by means of DMFT which maps the lattice model to the problem of a single impurity connected dynamically to a "heat bath" [8]. The electron Green's function is obtained via the self-consistent solution of this impurity problem. We represent the two electron bands by semi-circular density of states (DOS), $\rho_{\alpha}(x) = 2/\pi D_{\alpha}\sqrt{1 - (x/D_{\alpha})^2}$ where $2D_{\alpha}$ is the bandwidth. For the case of identical hopping integrals for the two bands, $t_{ij}^{(\alpha)} = t_{ij}$ $(D_1 = D_2)$, the role of orbital fluctuations has been discussed by means of DMFT [9, 10]. There are various methods to solve the effective impurity problem. We use here the exact diagonalization method proposed by Caffarel and Krauth [11], since the quantum Monte Carlo (QMC) simulations used by Liebsch [7] suffer from sign problems at low temperatures, in particular, if the Hund coupling is included. Additionally, we apply the linearized version of DMFT (two-site DMFT) [12], which allows us to discuss electronic properties well even in the vicinity of the critical point. We restrict our discussions to the paramagnetic case to clarify the nature of the Mott transition.

We first consider the case $\mu_1 = \mu_2 = U/2 + U' - J/2$,

i.e. both bands are half filled. The quasiparticle weight Z_{α} , defined by $Z_{\alpha}^{-1} = 1 - d \operatorname{Re}[\Sigma_{\alpha}(\omega)]/d\omega$ in terms of the self energy $\Sigma_{\alpha}(\omega)$ of each band, will be used to characterize the stability of the metallic state of the two bands. The results obtained with fixed ratios U'/U and J/U are shown in Fig. 1 for half-filled bands. We first fo-



FIG. 1: The quasiparticle weights Z_1 and Z_2 at half filling as a function of the Coulomb interaction U: (a) U'/U = 1.0(J = 0) and (b) U'/U = 0.5 (J/U = 0.25). The bandwidth is set as $D_1 = 1.0$ and $D_2 = 2.0$. Open (closed) circles represent the results for orbital $\alpha = 1(2)$ obtained by solving the DMFT impurity problem by means of the exact diagonalization of a small cluster (N = 6). Solid triangles represent the Mott-transition points obtained by the two-site DMFT method, which produce the values quite consistent with those of the numerical diagonalization. Insets show the same plot for bandwidths $D_1 = 1.0$ and $D_2 = 5.0$.

cus on the case of U = U' and J = 0 [shown in Fig. 1 (a)] with bandwidths $D_1 = 1.0$ and $D_2 = 2.0$. When the Coulomb interaction is turned on, the quasiparticle weights Z_1 and Z_2 decrease from unity in slightly different ways reflecting the difference of the bandwidth. A strong reduction of the quasiparticle weight appears initially in the narrower band. However, when the system approaches the Mott transition, the quasiparticle weights merge again displaying a very similar dependence on U, and eventually reach zero at the same critical point. The inset shows the more extreme case of $D_1 = 1.0$ and $D_2 = 5.0$ (very wide band). The common Mott transition originates from the enlarged symmetry inherent in U = U' and J = 0, which will be discussed below. This result is in agreement with the conclusion by Liebsch [7]. For small interaction strengths the decrease of the quasiparticle weight reflects the effective Coulomb interactions U/D_{α} which are different for two bands of different width, D_{α} . The dependence of the initial decrease in Z_{α} on U/D_{α} reflects the general difference in Z_{α} . On the other hand, in the vicinity of the quantum critical point at the Mott transition the effect of the bare bandwidth is diminished due to the strong renormalization of the effective quasiparticle bandwidth allowing Z_1 and Z_2 to vanish together [13, 14].

The introduction of a finite Hund coupling J makes $U \neq U'$ and leads to a qualitatively different behavior, as seen in Fig. 1 (b). With increasing U keeping the ratio U'/U = 0.5 fixed, the quasi-particle weights decrease differently and vanish at different critical points: $U_{c1} \approx 2.6$ for Z_1 and $U_{c2} \approx 3.5$ for Z_2 . Therefore, we observe an intermediate phase with one orbital localized and the other itinerant, though strongly renormalized ($Z_2 \ll 1$). The analogous behavior is observed for different choices of the bandwidths, if J takes a finite value [inset of Fig. 1 (b)]. Although it is difficult to precisely determine the second critical point U_{c2} , this result certainly suggests the existence of the OSMT with $U_{c2} > U_{c1}$.

In Fig. 2 we show how the quasiparticle states evolve and then disappear inside of the Mott-Hubbard gap. The DOS is computed by the two-site DMFT scheme [12]. In both cases the Mott-Hubbard gap develops as U increases and is accompanied by narrow quasiparticle midgap bands. For case (a) with J = 0, these quasiparticle bands disappear simultaneously, whereas for case (b) with finite J, they have different critical points, consistent with the results mentioned above.

Repeating similar DMFT calculations for various choices of the parameters, we derive the ground-state phase diagram shown in Fig. 3, which displays some remarkable features. First, the metallic phase (I) remains stable up to surprisingly large Coulomb interaction Uwhen $U \to U'$ (small J). Here the Mott transitions merge to a single transition. This behavior originates from the high symmetry when U = U' (J = 0) with six degenerate two-electron onsite configurations: four spin configurations with one electron in each orbital and two spin singlets with both electrons in one of the two orbitals. The additional symmetry in orbital/spin degrees of freedom enlarges the phase space for charge fluctuations and leads to a decrease of the Mott-Hubbard gap E_q at large U. A rough estimate of E_q can be obtained from the second moment of the hopping Hamiltonian for a state $|a\rangle$ with an extra electron (or hole). In $\langle a|H^2|a\rangle = T^2$ all possible configurations with the same onsite energies are considered as intermediate states [15]. Because all charge excitations mix with each other, there is only one gap. Assuming a staggered spin or orbital configuration as the most dominant local correlation for neighboring two-electron sites we obtain for the effective hopping matrix element of an extra carrier $T = \sqrt{t_1^2 + t_2^2}$. This allows us to estimate the Mott-Hubbard gap at large U:

$$E_g = U - 2zT = U - 2z\sqrt{t_1^2 + t_2^2}$$
(2)



FIG. 2: The density of states $\rho_{\alpha}(\omega)$ at half filling: left (right) panel for $\alpha = 1$ (2). (a) U'/U = 1.0 (J = 0) and (b) U'/U = 0.5 (J/U = 0.25). It is clearly seen that the Mott transitions occur simultaneously in (a), while the orbital selective transitions occur in (b).



FIG. 3: Phase diagram for two-orbital Hubbard model with $D_1 = 1$ and $D_2 = 2$. In the phase (I) [phase (II)], both bands are in metallic (insulating) state. The phase (III) is induced by the orbital-selective Mott transition, where the metallic state coexists with the Mott insulating state. Since we are concerned with the ferromagnetic Hund coupling, J > 0, the relevant region in the diagram is U > U'.

where z is the coordination number. We can get a simple estimate of U_c by setting $E_g \rightarrow 0$ leading to values $U_c = 2D_1\sqrt{2}$ (for $D_1 = D_2$) and $U_c = 2D_1\sqrt{5}$ (for $2D_1 = D_2$). Both estimates are enhanced relative to the single-band case $U_c = 2D$ [10].

Away from the symmetric limit, i.e. U > U' (2J =

U - U') orbital fluctuations are suppressed and the spin sector is reduced by the Hund coupling to three onsite spin triplet components as the lowest multiplet for twoelectron sites. Applying the same scheme as above, we recognize that charge excitations with two electrons in one or the other of the orbitals do not mix, since all hopping processes included in (1) preserve orbital configurations in the lowest multiplet sector. The effective hopping for each orbital is now $T_{\alpha} = t_{\alpha}/\sqrt{2}$ assuming a staggered spin-1 state at half-filling. The reduction compared to the single band case occurs due to the locking of the spins into an onsite spin triplet. If we consider again the case $2D_1 = D_2$ we find two separate Mott transitions with critical values

$$U_{c1} = \frac{1}{\sqrt{2}}D_1 + \frac{U'}{2}$$
 and $U_{c2} = \sqrt{2}D_1 + \frac{U'}{2}$. (3)

In between the two transitions we find the metallic intermediate phase (III) with one band localized and Mottinsulating and one band itinerant. Within our DMFT scheme we have also confirmed that various choices of bandwidths give rise to the qualitatively same structure of the phase diagram as shown in Fig. 3.

Our result for the Mott transitions is different from that of both Anisimov et al. and Liebsch [6, 7]. The former group derived an OSMT for a special model which includes only the intraband Coulomb repulsion U within the DMFT approach, and drops effects due to coupling between the orbitals. This scheme was criticized by Liebsch, who took into account U, U' and J. He claimed based on a DMFT analysis that only a single Mott transition occurs in the generic case. Liebsch's solution of the single-impurity problem within DMFT is based on QMC and iterative perturbation methods. The former suffers from sign problems which limit its validity at low temperatures, while the latter is an extrapolation from the small-U regime. Our DMFT analysis which uses the exact diagonalization of the impurity problem on a finite cluster is valid at zero-temperature and is not restricted to weak coupling. Our results show separate Mott transitions occurring generically except for the special case with high symmetry U = U' (J = 0), for which the transitions merge irrespective of the different bandwidths.

We have so far treated the case of two individually half-filled bands. We now address the question what will happen when the electron count is non-stoichiometric. This problem may provide another key to understand the orbital selective Mott transitions in $Ca_{2-x}Sr_{x}RuO_{4}$ [3], since each of the three original metallic bands possesses fractional fillings. In order to study this kind of system, we introduce a finite hole doping, and observe how commensurability can emerge due to interactions.

In Fig. 4 (a) we show the DOS which is computed by using the two-site DMFT. With increasing interactions quasiparticle states with large DOS appear around the Fermi energy in both bands. Enhancing the interactions further we drive the first band insulating. This is in contrast to the single band system, where finite hole doping obscures the Mott transition and always gives metallic behavior. In the two-band system, however, commensurability in one of the bands gradually emerges, as is clearly seen in Fig. 4 (b). The electron number for the first band n_1 is plotted here. When U = 0, n_1 and $n_2(= 1 - \delta - n_1)$ are smaller than 0.5 because of finite hole-doping ($\delta = 0.1$). Coulomb interaction causes electron transfer from one orbital to the other, giving rise to one half-filled band at a certain interaction strength, thereby causing an OSMT.



FIG. 4: (a) The density of states $\rho_1(\omega)$ and $\rho_2(\omega)$ for finite hole doping, $\delta = 0.1$. The Coulomb interaction is chosen as U = 0, 2.0, 3.0 and 4.0 (U' = 0.5U and J = 0.25U) from the top to the bottom. (b) The number of electrons in the orbital ($\alpha = 1$) as a function of U when U' = 0.5U and J = 0.25U.

In conclusion we have discussed the Mott transitions in the degenerate Hubbard model with non-hybridizing orbitals which have different bandwidths by means of DMFT. Our analysis has shown that a single Mott transition occurs when the Hund coupling is absent (U = U'), rendering the different bandwidth essentially irrelevant at the transition point, as discussed by Liebsch. In the more generic situation with finite Hund coupling, however, we find the OSMT. This is also true for non-stoichiometric systems. We believe that our study resolves the apparent contradictions on this issue. Moreover it sheds light on the nature of such Mott transitions, which may be relevant for the physics of the ruthenates.

We would like to thank V.I. Anisimov, Z. Fang, S. Nakatsuji, Y. Maeno and M. Troyer for useful discussions. This work was partly supported by a Grant-in-Aid from the Ministry of Education, Science, Sports and Culture of Japan and the Swiss National Science Foundation. A part of computations was done at the Supercomputer Center at the Institute for Solid State Physics, University of Tokyo and Yukawa Institute Computer Facility.

- Y. Maeno, T.M. Rice and M. Sigrist, Physics Today, 54, 42 (2001).
- [2] A.P. Mackenzie and Y. Maeno, Rev. Mod. Phys. 75, 657 (2003).
- [3] S. Nakatsuji and Y. Maeno, Phys. Rev. Lett. 84, 2666 (2000).
- [4] T. Hotta and E. Dagotto, Phys. Rev. Lett. 88, 017201 (2001).
- [5] Z. Fang and K. Terakura, Phys. Rev. B 64, R020509 (2001); Z. Fang, N. Nagaosa and K. Terakura, unpublished.
- [6] V.I. Anisimov, I.A. Nekrasov, D.E. Kondakov, T.M. Rice and M. Sigrist, Eur. Phys. J. B 25, 191 (2002).
- [7] A. Liebsch, Europhys. Lett., 63, 97 (2003); Phys. Rev. Lett., 91, 226401 (2003).
- [8] A. Georges, G. Kotliar, W. Krauth and M. J. Rozenberg, Rev. Mod. Phys. 68, 13 (1996).
- [9] G. Kotliar and H. Kajueter, Phys. Rev. B 54, R14221 (1996); M. J. Rozenberg, Phys. Rev. B 55, R4855 (1997);
 K. Held and D. Vollhardt, Eur. Phys. J. B 5, 473 (1998);
 J. E. Han, M. Jarrell and D. L. Cox, Phys. Rev. B 58, R4199 (1998); T. Momoi and K. Kubo, Phys. Rev. B 58, R567 (1998); V. S. Oudovenko and G. Kotliar, Phys. Rev. B 65, 075102 (2002); Y. Ono, M. Potthoff and R. Bulla, Phys. Rev. B 67, 035119 (2003).
- [10] A. Koga, Y. Imai and N. Kawakami, Phys. Rev. B 66, 165107 (2002); A. Koga, T. Ohashi, Y. Imai, S. Suga and N. Kawakami, J. Phys. Soc. Jpn. 72, 1306 (2003).
- [11] M. Caffarel and W. Krauth, Phys. Rev. Lett. 72, 1545 (1994).
- [12] M. Potthoff, Phys. Rev. B 64, 165114 (2001).
- [13] M. C. Gutzwiller, Phys. Rev. 137, A1726 (1965).
- [14] W. F. Brinkman and T. M. Rice, Phys. Rev. B 2, 4302 (1970).
- [15] E. Koch, O. Gunnarsson and R.M. Martin, Phys. Rev. B 60, 15714 (1999).