## An organometallic chimie douce approach to new Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub> phases

Christian Helbig, Rudolf Herrmann, Franz Mayr, Ernst-Wilhelm Scheidt, Klaus Tröster, Jan Hanss, Hans-Albrecht Krug von Nidda and Wolfgang Scherer\*

## $Re_xW_{1-x}O_3H_2O$ and $Re_xW_{1-x}O_3$ phases are prepared by a new organometallic *chimie douce* concept employing the organometallic precursor methyltrioxorhenium.

Crystalline WO<sub>3</sub> has found widespread interest as electrochromic material, applied *e.g.* as thin film for "smart windows",<sup>1</sup> and as gas sensor.<sup>2</sup> At room temperature monoclinic  $\gamma$ -WO<sub>3</sub> (P2<sub>1</sub>/n) represents the thermodynamically most stable phase and consists of tilted WO<sub>6</sub> octahedra. Its structure is therefore related via group subgroup relationships with cubic  $\text{ReO}_3$  (*Pm*-3*m*), which represents the aristotype of the BO<sub>3</sub> perovskite family. Accordingly, it should be possible to form solid solutions of mixed Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub> phases due to the structural resemblance of both parent oxides and the similar ionic radii of Re<sup>VI</sup> and W<sup>VI.3</sup> While WO<sub>3</sub> represents an insulator, ReO<sub>3</sub> displays metallic behaviour with a specific conductivity in the same range as crystalline copper.<sup>4</sup> Hence, solid solutions of both oxides might lead to new phases with interesting electronic properties like the related Na<sub>x</sub>WO<sub>3</sub> phases, which are benchmark systems to study chemically-induced metal-to-insulator transitions.<sup>5</sup> However, up to now mixed  $Re_r W_{1,r}O_3$  phases were only accessible in small quantities under extreme conditions at high pressure and high temperatures (65 kbar, 1200°C).<sup>6</sup> Here, we propose a new organometallic chimie douce method which allows to synthesise  $Re_x W_{1-x}O_3$  phases in large quantities by a low temperature process at ambient pressure.

A convenient aqueous synthesis of WO<sub>3</sub>·yH<sub>2</sub>O (y = 1, 2, 1/3) from tungstates via tungstic acid has been reported and discussed earlier.7-9 We found that mixed hydrated WO3/ReO3 phases are formed from sodium metatungstate containing the Keggin ion  $[H_2W_{12}O_{40}]^{6-}$  and the organometallic precursor, CH<sub>3</sub>ReO<sub>3</sub>, (methyltrioxorhenium; MTO) in diluted HCl at 100°C.<sup>10</sup> The new Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>H<sub>2</sub>O phases are obtained as dark green to black microcrystalline platelets, in contrast to WO3·H2O which shows a bright yellow colour when prepared under the same conditions (Fig. 1). The choice of the precursors is crucial; no mixed WO<sub>3</sub>/ReO<sub>3</sub> phases are obtained from sodium tungstate Na2WO4·2H2O which consists of isolated WO<sub>6</sub> octahedra. We interpret these observations as a kinetic effect: acidification of sodium tungstate initiates a fast condensation process<sup>8</sup> leading to WO<sub>3</sub>·H<sub>2</sub>O precipitates. This process, however, is apparently delayed when  $\alpha$ -metatungstate is used instead as precursor. In this case, hydrolysis of the [H<sub>2</sub>W<sub>12</sub>O<sub>40</sub>]<sup>6-</sup> ion to release the neutral monooxo precursor [WO(OH)<sub>4</sub>(OH<sub>2</sub>)] provides the sufficient time span for the preconditioning of our organometallic precursor (e. g. CH<sub>3</sub>ReO<sub>2</sub>(OH)<sub>2</sub> formation)<sup>11</sup> to take part in the following oxolation process. Once incorporated, MTO looses the methyl group, accompanied by reduction of Re<sup>VII</sup> to Re<sup>VI.11</sup> We note that only pure WO3·H2O is precipitated when other inorganic ReVII species like perrhenate salts are added to the reaction mixture instead of



**Fig. 1** IR spectra (KBr) of WO<sub>3</sub>·H<sub>2</sub>O and Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>·H<sub>2</sub>O with x = 0.025. The right hand side shows photographs of tungstite and a mixed phase (x = 0.014).

MTO. Hence, the salient capability of our organometallic precursor to form  $\text{Re}^{\text{VI}}$  oxide species by methane elimination in water appears to be crucial for the successful tungsten/rhenium substitution.<sup>12</sup> The composition and homogeneity of the samples was ascertained by ICP, SEM-EDX, X-ray diffraction and microanalysis up to a Re content of 12%. For *x* larger than 0.12 phase separation via ReO<sub>3</sub> formation is observed.

IR spectroscopic studies (KBr pellets; Fig. 1) show a characteristic band at 940 cm<sup>-1</sup> in the parent tungstite,WO<sub>3</sub>·H<sub>2</sub>O, which shifts to lower frequency in our new  $\text{Re}_x W_{1-x}O_3$ ·H<sub>2</sub>O samples with increasing rhenium content. This mode can be assigned by the stretching mode of the W=O bond (see structural motif in Fig. 5) which appears to become softened by stepwise substitution of W(d<sup>0</sup>) by the less Lewis-acidic Re(d<sup>1</sup>) centres.<sup>9,13</sup> Hence, substitution of only 2.5% of tungsten atoms by rhenium lowers the corresponding W/Re=O stretching frequency by 11 cm<sup>-1</sup>. Stretching vibrations of the O-W-O or mixed O-W/Re-O units give rise to a broad signal around 700 cm<sup>-1</sup> (680 and 730 cm<sup>-1</sup> have been reported for undoped tungstite<sup>13</sup>) which appears to be less effected by the substitution of tungsten *vs*. Re.

A further indication of electronic changes induced by the rhenium content of the mixed phases can be found in the dehydration behaviour as studied by TGA using a temperature ramp from 25 to 230°C during 45 minutes. As shown in Fig. 2, all phases loose a total of one molecule of water per formula unit (7%), but the ease of dehydration depends on the rhenium content. While significant water loss (5% of the total loss) of WO<sub>3</sub>·H<sub>2</sub>O starts only above 180°C,<sup>9</sup> the mixed phases with x = 0.025 (0.053) of rhenium content loose water already at 140°C (90°C). Hence, replacement of the W(d<sup>0</sup>) atoms by the more electron-rich and less Lewis-acidic Re(d<sup>1</sup>) centres facilitates the dehydration of water molecules which are interconnecting corner-sharing WO<sub>6</sub> layers via hydrogen bonding. The samples with rhenium contents x > 0.12, which show phase separation, loose water in two clearly distinguishable steps at different temperatures. The inflection points

<sup>\*</sup> wolfgang.scherer@physik.uni-augsburg.de



**Fig. 2** TGA dehydration curves of selected  $\text{Re}_x W_{1,x} O_3 \cdot H_2 O$  phases (right axis) and the respective temperature profile (left axis). The inset displays a typical SEM image for the sample x = 0.014 revealing a morphology typical for layered compounds.

of the dehydration curve of the sample with 15% rhenium content are marked by arrows in Fig. 2.

Magnetisation measurements were performed for all Re<sub>r</sub>W<sub>1</sub>. <sub>x</sub>O<sub>3</sub>·H<sub>2</sub>O samples presented in this paper. In Fig. 3 the inverse susceptibility  $\chi^{-1}(T) = B/M$  is pictured, representatively for x =0.025. Below 100 K  $\chi(T)$  is well accounted for by a Curie-Weiss law  $\chi(T) = C/(T-\theta) + \chi_0$  with a marginal itinerant contribution  $\chi_0 \approx$ 0.03 memu/mol and  $\theta \approx 0$  K. The vanishing Curie-Weiss temperature  $\theta$  indicates no correlations between the residual localised d<sup>1</sup> electrons at the Re atoms. The effective paramagnetic moment  $\mu_{\rm eff} = 0.06 \,\mu_{\rm B}$  obtained from the Curie constant C indicates that 0.1% of the metal sites carry a d<sup>1</sup> moment, which correspond to an amount of 4% of the Re atoms. In the inset of Fig. 3 the magnetisation M(B) at 2 K is displayed. The fitted Brillouin function (solid line) takes into account a d<sup>1</sup> state with a quenched orbital moment (L = 0). The saturation magnetisation  $M_{\rm sat}$  is proportional to the quantity of the aligned local spins. The observed small saturation value of  $M_{\rm sat} \approx 10^{-3} \,\mu_{\rm B}$  / f.u. corresponding to an amount of 0.1% d1 moments at the metal sites corroborates our susceptibility results (for a single d<sup>1</sup> moment  $M_{sat} = 1 \mu_{\rm B} / \text{f.u.}$ ).



**Fig. 3** The inverse magnetic susceptibility  $\chi^{-1}$  of Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>·H<sub>2</sub>O (x = 0.025) measured in an external magnetic field B = 1 T. A diamagnetic core electron contribution  $\chi_{Dia} = -68 \mu \text{emu/mol}$  was subtracted from the data. The solid line is a linear fit with a Curie-Weiss law. The inset displays the field dependence of the magnetic moment *M* per formula unit at 2 K together with a fitted Brillouin function (solid line).

As one would expect from the marginal  $\chi_0$  value, the resistivity  $\rho$  of pressed powder samples of Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>·H<sub>2</sub>O is generally high (about 10  $\Omega$ cm) and reveals an insulating temperature dependence  $(d\rho/dT < 0)$ .

ESR spectra (9.35 GHz, 4 K) confirm the presence of localised d<sup>1</sup> moments at the Re atoms: a signal at g = 2 is observed, showing a hyperfine coupling (six lines) to rhenium (I = 5/2 for <sup>185</sup>Re and <sup>187</sup>Re), with an average coupling constant  $A \sim 620$  Oe (0.058 cm<sup>-1</sup>; see Fig. 4).<sup>14</sup>



**Fig. 4** An ESR spectrum of  $\text{Re}_x W_{1-x} O_3$  (x = 0.025) at 4 K. The six lines indicate the hyperfine coupling of electron spins localised at  $\text{Re}(d^1)$  centres.

Finally, a strong indication for the change in the WO<sub>3</sub>·H<sub>2</sub>O lattice due to rhenium doping is found by X-ray powder diffractometry. The mixed hydrated phases are isotypic to the orthorhombic WO<sub>3</sub>·H<sub>2</sub>O tungstite structure (*Pmnb*). Fig. 5 (b) shows an overlay of the diffraction pattern of WO<sub>3</sub>·H<sub>2</sub>O and the phase with 2.5% rhenium content. Both patterns confirm the high crystallinity of our samples and do not hint for any parasitic phase. Since tungsten and rhenium atoms have about the same scattering cross-section for X-rays and due to the isotypic relationship between the pure WO<sub>3</sub>·H<sub>2</sub>O and mixed Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>·H<sub>2</sub>O the position and therefore possible ordering of the Re and W atoms could not be disclosed yet.

However, closer inspection of the diffraction pattern (Fig. 5 (a)) reveals that some Bragg peaks of the rhenium substituted samples are slightly but significantly shifted to smaller angles (Bragg peaks (002) and (022) in Fig. 5 (a)) in comparison with the pattern of the parent compound WO<sub>3</sub>·H<sub>2</sub>O. Accordingly, Rietveld refinements reveal a widening of the WO<sub>3</sub>·H<sub>2</sub>O lattice by 1.5 pm in *c* direction (from 5.1264(4) Å to 5.1416(1) Å) after Re doping (x = 0.025).

Analysis of the diffraction pattern of dehydrated  $\text{Re}_x W_{1,x} O_3 \cdot H_2 O$ samples, however, was complicated due to the partial amorphous character of the products (Fig. 6 (a)). The resulting pattern closely resembles the ones found earlier for dehydrated WO<sub>3</sub>·H<sub>2</sub>O phases which were reported to represent the hitherto unknown metastable form of cubic WO<sub>3</sub>.<sup>15</sup> However, a direct comparison with the cubic diffraction pattern of highly crystalline  $\text{Re}_{0.25}W_{0.75}O_3$  powder obtained by bulk synthesis at 7.5 GPa and 1100°C (a = 3.7516(2)Å; Fig. 6 (c))<sup>16</sup> clearly reveals that the new  $\text{Re}_x W_{1,x}O_3$  phases obtained by dehydration should be indexed rather by a monoclinic than by a cubic unit cell. Precise lattice parameters for the new



**Fig. 5** (b) X-ray powder diffraction pattern of WO<sub>3</sub>·H<sub>2</sub>O (tungstite) and Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>·H<sub>2</sub>O (x = 0.025). (a) The upper part is an enlargement of the diffraction range between 32 and 40°. The inset shows the structural motif of tungstite representing layers of corner-sharing polyhedra which are interconnected in the third dimension along the crystallographic *a* axis via W=O"H-O-H"O=W hydrogen bonding.

monoclinic Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub> phase (x = 0.025, a = 7.3165(4) Å, b = 7.5131(4) Å, c = 7.6911(5) Å,  $\beta = 90.521(6)^{\circ}$ ,  $P2_1/n$ ) could be obtained by Rietveld analysis of the annealed samples (720°C, 1 day) (Fig. 6 (b)). Furthermore, a single crystal diffraction study on Re<sub>0.02</sub>W<sub>0.98</sub>O<sub>3</sub> (a = 7.305(3) Å, b = 7.534(2) Å, c = 7.691(2) Å,  $\beta = 90.88(3)^{\circ}$ ) which was alternatively synthesised by chemical transport methods at 1000°C clearly reveals the isotypic relationship between monoclinic Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub> phases obtained by *chimie douce* and classical ceramic methods.

Hence, at this stage we can demonstrate that we succeeded to obtain pure  $\text{Re}_x W_{1-x} O_3$  phases by an organometallic *chimie douce* approach. An organometallic compound, methyltrioxorhenium, was found to be the only successful precursor suitable for the rhenium doping of WO<sub>3</sub> at low temperatures and ambient pressure. Diffraction studies reveal that the new  $\text{Re}_x W_{1-x} O_3$  phases obtained by our *chimie douce* approach are not cubic but isotypic to monoclinic  $\gamma$ -WO<sub>3</sub>. We could hence demonstrate that cubic phases of mixed Re/W trioxides still appear to remain a domain of high pressure high temperature methods. As a result of our studies a fast and simple *chimie douce* pathway to mixed Re/W trioxides has



**Fig. 6** (a) X-ray powder diffraction pattern of dehydrated  $\text{Re}_x W_{1-x} O_3 \cdot H_2 O$ (x = 0.025) and (b) the annealed sample; (c) diffraction pattern of the cubic high pressure modification of  $\text{Re}_{0.25} W_{0.75} O_3$ .

been opened as an alternative to ceramic routes which warrants further exploitation with respect to electronic design (*e.g.* electrochromic and gas sensing properties) and chemical behaviour (*e.g.* intercalation chemistry, oxidation catalysis).

Christian Helbig, Rudolf Herrmann, Franz Mayr, Ernst-Wilhelm Scheidt, Klaus Tröster, Jan Hanss, Hans-Albrecht Krug von Nidda and Wolfgang Scherer

Institut für Physik, Universität Augsburg, Universitätsstr. 1, D-86135 Augsburg, Germany. Fax:+49-(0)821-598-3227; Tel:+49(0)821-598-3350; E-mail: wolfgang.scherer@physik.uni-augsburg.de

## Acknowledgement:

This work was supported by the SFB 484 of the Deutsche Forschungsgemeinschaft (DFG).

## Notes and references

- C. G. Granqvist, Handbook of Electrochromic Materials, Elsevier, Amsterdam 1995; C. G. Granqvist, Solar Energy Materials & Solar Cells, 2000, 60, 201.
- 2 I. Jiménez, J. Arbiol, G. Dezanneau, A. Cornet and J. R. Morante, Sensors Actuators B 2003, 93, 475.
- 3 The effective ionic radius for W and Re (coordination number 6; oxidation state 6) is reported as 0.6 and 0.55 Å, respectively; see R. D. Shannon, *Acta Cryst.* 1976, A32, 751.
- 4 C. N. King, H. C. Kirsch and T. H. Geballe, *Solid State Commun.* 1971, **9**, 907.
- 5 H. Dücker, W. von Niessen, T. Kolowski, M. A. Tusch and D. E. Logan, *Phys. Rev. B*. 1999, **59**, 871.
- 6 A. W. Sleight and L. Gillson, Solid State Commun. 1966, 4, 601.
- 7 M. Figlarz, Chem. Scr. 1988, 28, 3.
- 8 J. Livage and G. Guzman, Solid State Ionics 1996, 84, 205.
- 9 M. Gotic, M. Ivanda, S. Popovic and S. Music, *Mat. Sci. Eng. B*, 2000, **77**, 193.
- 10 Typical procedure for the preparation of mixed hydrated WO<sub>3</sub>/ReO<sub>3</sub> phases: To a solution of 792.0 mg of sodium metatungstate (2.652 mmol) and 195.8 mg of MTO (0.7856 mmol) in 40 ml of water 12 ml of HCl (37%) are added with stirring. The mixture is heated to reflux for 24 h. After cooling to room temperature, the precipitate is filtered off, washed with 30 ml of diluted HCl (0.4%) (three times) and dried for two hours at 120°C. The yield is 739.9 mg, the rhenium content being x = 0.025.
- 11 Elimination of the methyl group is one of the known decomposition pathways of MTO in acidic aqueous solution and is also the crucial step in the formation of polymeric MTO in water. See, for example W. A. Herrmann, W. Scherer, R. W. Fischer, J. Blümel, M. Kleine, W. Mertin, R. Gruehn, J. Mink, H. Boysen, C. C. Wilson, R. Ibberson, L. Bachmann and M. Mattner, J. Am. Chem. Soc. 1995, 117, 3231.
- 12 Only a residual content of carbon at the detection limit of the microanalysis (0.1%) was found in the Re<sub>x</sub>W<sub>1-x</sub>O<sub>3</sub>·H<sub>2</sub>O samples.
- 13 M. F. Daniel, B. Desbat, J. C. Lassegues, B. Gerand and M. Figlarz, J.Solid State Chem. 1987, 67, 235.
- 14 J. F. Gibson, G. M. Lack, K. Mertis and G. Wilkinson, J. Chem. Soc., Dalton Trans. 1976, 1492.
- 15 Cs. Balazsi, M. Farkas-Jahnke, I. Kotsis, L. Petras and J. Pfeiffer, Solid State Ionics 2001, 141-142, 411.
- 16 G. Heymann, H. Huppertz, C. Helbig and W. Scherer, unpublished results. Similar cubic lattice parameters (a = 3.7719(4) Å, Pm-3m) were found in a recent high pressure and high temperature study on undoped WO<sub>3</sub>; (W. A. Crichton, P. Bouvier A. Grzechnik, Mat. Res. Bull. 2003, **38**, 289.)