Valence changes associated with the metal-insulator transition in $Bi_{1-x}La_xNiO_3$

H. Wadati, M. Takizawa, T. T. Tran, K. Tanaka, T. Mizokawa, and A. Fujimori

Department of Physics and Department of Complexity Science and Engineering,

University of Tokyo, Kashiwanoha 5-1-5, Kashiwa, Chiba 277-8561, Japan

A. Chikamatsu, H. Kumigashira, and M. Oshima

Department of Applied Chemistry, University of Tokyo, Bunkyo-ku, Tokyo 113-8656, Japan

S. Ishiwata, M. Azuma, and M. Takano

Institute for Chemical Research, Kyoto University, Uji, Kyoto 611-0011, Japan

(Dated: October 24, 2018)

Perovskite-type BiNiO₃ is an insulating antiferromagnet in which a charge disproportionation occurs at the Bi site. La substitution for Bi suppresses the charge disproportionation and makes the system metallic. We have measured the photoemission and x-ray absorption (XAS) spectra of Bi_{1-x}La_xNiO₃ to investigate how the electronic structure changes with La doping. From Ni 2p XAS, we observed an increase of the valence of Ni from 2+ toward 3+. Combined with the core-level photoemission study, it was found that the average valence of Bi remains ~ 4+ and that the Ni valence behaves as ~ (2 + x)+, that is, La substitution results in hole doping at the Ni sites. In the valence-band photoemission spectra, we observed a Fermi cutoff for x > 0, consistent with the metallic behavior of the La-doped compounds. The Ni 2p XAS, Ni 2p core-level photoemission, and valence-band photoemission spectra were analyzed by configuration-interaction cluster-model calculation, and the spectral line shapes were found to be consistent with the gradual Ni²⁺ \rightarrow Ni³⁺ valence change.

PACS numbers: 71.28.+d, 71.30.+h, 79.60.-i, 78.70.Dm

I. INTRODUCTION

Perovskite-type 3d transition-metal oxides exhibit various interesting physical properties, such as metalinsulator (MI) transition, colossal magnetoresistance (CMR), and ordering of spin, charge, and orbitals [1]. Among them, the charge-transfer-type $RNiO_3$ (R = rare earth) forms a prototypical system in which an MI transition occurs in a systematic manner, namely, as a function of the radius of the R ion and hence of the one-electron bandwidth [2, 3]. The least distorted LaNiO₃ is a paramagnetic metal, whereas more distorted $RNiO_3$ with a smaller R ion becomes an antiferromagnetic insulator. Some $RNiO_3$ with an R ion of intermediate size shows a metal-insulator transition as a function of temperature, too.

In this context, BiNiO₃ had been expected to be metallic, if synthesized, because the ionic radius of Bi³⁺ is larger than that of La³⁺. Recently, Ishiwata *et al.* succeeded in synthesizing BiNiO₃ under a high pressure of 6 GPa [4]. Contrary to the above expectation, BiNiO₃ was found to be an insulating antiferromagnet with localized spins of S = 1. X-ray powder diffraction (XRD) study revealed that the Bi ions were charge-disproportionated into "Bi³⁺" and "Bi⁵⁺". Thus the oxidation state of the Ni ion was concluded to be 2+ rather than 3+. To the authors' knowledge, such a charge disproportionation at the A-site in the perovskite structure has never been reported so far. Since Bi has a deep 6s level, and such a high valence state as "Bi⁵⁺" at A-site would not be stable from the viewpoint of the Madelung potential [5], the realistic charge configuration of Bi⁵⁺ may be expressed as $\operatorname{Bi}^{3+}\underline{L}^2$, where \underline{L} denotes a hole in the O 2p band. Subsequently, it was reported that the substitution of La for Bi suppressed the charge disproportionation and made the system conducting [6]. Therefore, an interesting question for this system is how the electronic structure changes from the charge-disproportionated insulating $BiNiO_3$ to the metallic LaNiO₃ with La substitution. One possible senario is that the La substitution suppresses the charge disproportionation and changes the average valence of Bi from 4+ to 3+. If so, the valence of Ni would become 3+, and the Ni atoms become responsible for the metallic conductivity. Another senario is that the La substituion suppresses the charge disproportionation but the average valence of Bi remains 4+. If so, the valence of Ni becomes (2+x)+, and both the Bi and Ni sites contribute to the metallic conductivity. To settle this question, we have investigated the electronic structure of $Bi_{1-x}La_xNiO_3$ by photoemission and x-ray absorption spectroscopy (XAS). Our result seems to support the latter scenario.

II. EXPERIMENT

Preparation and characterization of polycrystalline $Bi_{1-x}La_xNiO_3$ (x = 0, 0.05, 0.1, 0.2) are described elsewhere [4, 6]. Figure 1 shows the electrical resistivity of $Bi_{1-x}La_xNiO_3$ [6]. For x = 0 ($BiNiO_3$), the system is insulating. Electrical resistivity decreases with La substitution. For x = 0.05, 0.075, and 0.1, a broad MI transition occurs as a function of temperature. For x = 0.2



FIG. 1: Electrical resistivity of $Bi_{1-x}La_xNiO_3$ [6].

and 0.5, the system is metallic. All the experiments except for ultraviolet photoemission spectroscopy (UPS) were performed at BL-2C of Photon Factory (PF), High Energy Accelerators Research Organization (KEK). UPS measurements were performed using a high-flux discharging lamp with a troidal grating monochromator. The photoemission and x-ray absorption measurements were performed under an ultrahigh vacuum of $\sim 10^{-10}$ Torr at room temperature. The photoemission spectra were measured using a Scienta SES-100 electron-energy analyzer. At KEK-PF, the total energy resolution was about 200-500 meV depending on the photon energy, whereas for UPS measurments it was set to about 10 meV and 50 meV for the He I (21.2 eV) and He II (40.8 eV) light sources, respectively. The Fermi level (E_F) position was determined by measuring gold spectra. The XAS spectra were measured by the total-electron-yield method. Clean surfaces of the samples were obtained by repeated *in-situ* scraping with a diamond file.

III. RESULTS AND DISCUSSION

A. Ni 2p x-ray absorption and Ni 2p core-level photoemission spectra

Figure 2 (a) shows the Ni 2p XAS spectra of $\operatorname{Bi}_{1-x}\operatorname{La}_x\operatorname{NiO}_3$. The Ni $2p_{3/2}$ peak overlaps the La $3d_{3/2} \to 4f$ absorption peak. As reported previously [7], the Ni 2p XAS spectra of $R\operatorname{NiO}_3(\operatorname{Ni}^{3+})$ are very different from that of NiO (Ni²⁺): The $2p_{3/2}$ spectrum consists of two peaks labelled as A and B, as shown in Fig. 2 (a). The lower energy peak A is stronger than the higher energy one B for NiO, whereas the two peaks have similar intensities in $R\operatorname{NiO}_3$ (as shown in Fig. 2(b)). The spectrum of x = 0 is similar to that of Ni²⁺, which is consistent with the report that the valence of Ni is 2+ in BiNiO₃ [4]. With increasing x, the relative intensity of the higher energy peak increases, indicating that the valence of Ni gradually increases from Ni²⁺ toward



FIG. 2: (Color online) Ni 2p XAS spectra and their CI clustermodel analyses. (a) Ni 2p XAS spectra of Bi_{1-x}La_xNiO₃. The calculated spectra assuming Ni²⁺ and Ni³⁺ are presented at the bottom. The dashed lines represent the La $3d_{3/2}$ absorption peaks. (b) Ni 2p XAS spectra of NiO and $RNiO_3$ from Ref [7].



FIG. 3: (Color online) Ni 2p core-level photoemission spectra of Bi_{1-x}La_xNiO₃ and their CI cluster-model analyses. The calculated spectra assuming Ni²⁺ and Ni³⁺ are presented at the bottom.

Ni³⁺. Figure 3 shows the Ni 2p photoemission spectra of Bi_{1-x}La_xNiO₃. As in the case of XAS, the Ni $2p_{3/2}$ core level overlaps the La $3d_{3/2}$ core level. The Ni 2p photoemission spectra do not change with x, consistent with the reports that the line shapes of the Ni 2p photoemission spectra of $RNiO_3$ (Ni³⁺ or Ni²⁺ \underline{L}) [8, 9] are almost the same as that of La₂NiO₄ (Ni²⁺) [10].

In order to confirm that the Ni 2p XAS and photoemission spectra are consistent with the Ni²⁺ \rightarrow Ni³⁺ va-

lence change with La substitution, we have performed a configuration-interaction (CI) cluster-model calculation [11, 12]. Here, we considered a $[NiO_6]^{10-}$ octahedral cluster in the case of Ni^{2+} and a $[NiO_6]^{9-}$ one in the case of Ni^{3+} . In this model, parameters to be fitted are the charge-transfer energy from the O 2p orbitals to the empty Ni 3d orbitals denoted by Δ , the 3d - 3d on-site Coulomb integration energy denoted by U, and the hybridization strength between the Ni 3d and O 2p orbitals denoted by Slater-Koster parameters denoted by $(pd\sigma)$ and $(pd\pi)$ [13]. The ratio of $(pd\sigma)/(pd\pi)$ is fixed to be -2.2 [14, 15]. The configuration dependence of the transfer integrals has been taken into account [16]. Racah parameters B and C are fixed at 0.142 and 0.527 eV, 80% of the atomic Hartree Fock values [17, 18]. We took into account the intra-atomic multiplet coupling for the Ni 2p XAS spectrum and the valence band spectrum, whereas the multiplet coupling between the core hole and the valence d electrons was not taken into account for the Ni 2p photoemission spectrum as in the case of Ref. [12]. The Slater integrals between the Ni 2p and 3d orbitals are $F^2 = 6.68$, $G^1 = 5.07$, and $G^3 = 2.88$ eV. The multiplet-averaged 2p-3d Coulomb interaction $Q \equiv F^0 - \frac{1}{15}G^1 - \frac{3}{70}G^3$ is ~ 9.3 eV in the case of Ni²⁺ and $\sim 10 \text{ eV}$ in the case of Ni³⁺, satisfying the relationship $U/Q \sim 0.7$.

The calculated Ni 2p XAS spectra have been broadened by a Gaussian and a Lorentzian. The full width at half maximum (FWHM) of the Gaussian is ~ 1.0 eV, which is determined by the instrumental resolution and the effect of electron-phonon coupling [19] and that of the Lorentzian is ~ 0.5 eV, which is determined from the natural width [20]. The calculated Ni 2p corelevel photoemission spectra have been broadened with an energy-dependent Lorentzian with a FWHM $2\Gamma =$ $2\Gamma_0(1 + \alpha \Delta E)$, where ΔE denotes the energy separation from the main peak. We adopted the values $\alpha = 0.15$ and $\Gamma_0 = 1.2$ eV. We then used a Gaussian broadening of 1.0 eV to simulate the instrumental resolution and broadening due to the core hole-3d multiplet coupling.

Figure 3 shows that the Ni 2p photoemission spectra thus calculated reproduce the experimental Ni 2p photoemission spectra very well both in the cases of Ni²⁺ and Ni³⁺. These calculated spectra have been obtained with $\Delta = 4.5$ eV, U = 6.5 eV, and $(pd\sigma) = -1.5$ eV in the case of Ni²⁺ and $\Delta = 1.0$ eV, U = 7.0 eV, and $(pd\sigma) = -1.1$ eV in the case of Ni³⁺. These values are close to those previously reported : $\Delta = 4.5$ eV, U = 7.0eV, and $(pd\sigma) = -1.2$ eV in the case of La₂NiO₄ (Ni²⁺) [10] and $\Delta = 1.0$ eV, U = 7.0 eV, and $(pd\sigma) = -1.5$ eV in the case of $PrNiO_3$ (Ni³⁺ or Ni²⁺ \underline{L}) [9]. On the other hand, Fig. 2 shows that the calculated Ni 2p XAS spectrum for Ni^{2+} is very different from that for Ni^{3+} . It should be noted that we have used the same parameter sets as in the case of Ni 2p photoemission spectra. The result thus explains why the Ni 2p XAS spectra change with the Ni valence, whereas the Ni 2p photoemission spectra do not.



FIG. 4: (Color online) Ni 2p XAS spectra and the estimation of the valence of Ni. (a) Ni 2p XAS spectra after the subtraction of background and the La $3d_{3/2}$ contribution. (b) Valence of Ni in Bi_{1-x}La_xNiO₃.

In order to evaluate the Ni valence more quantitatively from Ni 2p XAS, we have subtracted the contribution of La $3d_{3/2}$ XAS and compared the spectra with those of $BiNiO_3$ (Ni²⁺) and PrNiO₃ (Ni³⁺). Figure 4 (a) shows the Ni 2p XAS spectra after the subtraction of the background and the La $3d_{3/2}$ contribution. From the relative intensities of the two peaks, one can estimate the Ni valence as a function of x as shown in Fig. 4. Here, we have assumed that the spectrum of x = 0 represents pure Ni^{2+} , and adopted that of $PrNiO_3$ as a reference of Ni^{3+} . Figure 4 shows that the valence of Ni behaves approximately as (2 + x)+, rather than 3+, the value expected when the average valence of Bi becomes 3+ upon La substitution. The result indicates that La substitution does not change the average valence of Bi, while suppressing the charge disproportionation at the Bi site, and the valence of Ni becomes $\sim (2+x)+$. The valence of Bi shall be discussed below.

B. O 1s and Bi 4f core-level photoemission spectra

Figure 5 shows the core-level photoemission spectra of O 1s and Bi 4f. Each O 1s spectrum consists of a single peak with negligible amount of contamination signals on the higher-binding-energy side, meaning that the surfaces of the samples became clean by scraping. The Bi 4f spectrum of BiNiO₃ does not show two components corresponding to Bi^{3+} and Bi^{5+} , suggesting that the spectrum reflects the average valence of the Bi atom. The absence of a splitting into Bi^{3+} and Bi^{5+} components has been reported for $BaBiO_3$ [21], too, which was also thought to exhibit a charge disproportionation into Bi^{3+} and Bi^{5+} . The peak positions of both core-level spectra change with x. In Fig. 6 (a), we have plotted the positions of the O 1s and Bi 4f core levels and their differences as functions of x. Both core levels are shifted downward up to $x \leq 0.1$ and then shifted upward from $x \sim 0.1$ to x = 0.2.

The shift ΔE_B of a core-level binding energy with

4



FIG. 5: (Color online) Core-level photoemission spectra of $Bi_{1-x}La_xNiO_3$. (a) O 1s (b) Bi 4f.

chemical composition measured from the chemical potential μ is given by

$$\Delta E_B = \Delta \mu + K \Delta Q + \Delta V_M + \Delta E_R, \tag{1}$$

where $\Delta \mu$ is the change in the chemical potential, ΔQ is the change in the number of valence electrons on the atom considered, ΔV_M is the change in the Madelung potential, and ΔE_R is the change in the core-hole screening [22]. The similar shifts of the O 1s and Bi 4f core levels indicate that the change in the Madelung potential (ΔV_M) is negligibly small because it would shift the core levels of anions and cations differently. Core-hole screening by conduction electrons is also considered to be negligibly small in transition-metal oxides [23, 24, 25]. Therefore, the result indicates that the chemical potential moves downward with increasing x, that is, hole doping takes place with La substitution from $x \sim 0.1$ to x = 0.2. For $x \leq 0.1$, however, the core levels are shifted in the opposite direction, probably reflecting the change of the band structure caused by the considerable change in the lattice constants between x = 0 and 0.05 [6]. The O 1s - Bi 4f difference is free from the chemical potential shift and is considered to reflect the valence change of Bi called "chemical shift" denoted by $K\Delta Q$ in Eq. (1). From Fig. 6 (a), the energy difference remains almost the same for all values of x, indicating that the valence of Bi does not change appreciably. Figure 6 (b) shows that the valence of Bi calculated from the valence of Ni in Fig. 4 (b) and the valence of La (3+) also does not show obvious x dependence. Therefore, we consider that the valence of Bi remains almost unchanged, 4+. Combining these results with the result of Ni 2p XAS, we conclude that the valence of Ni increases with increasing x, while the average valence of Bi remains constant, meaning that La substitution donates holes to the Ni sites. Charge transport in this system is therefore attributed to holes at both the Ni site (Ni³⁺ or Ni²⁺ \underline{L}) and the Bi site (Bi⁴⁺ or $\operatorname{Bi}^{3+}L$).



FIG. 6: (Color online) Estimation of the valence of Bi in $Bi_{1-x}La_xNiO_3$. (a) Binding energy shifts of the O 1s and Bi 4f core levels and their differences. (b) Valence of Bi calculated from the Ni valence deduced above.

C. Valence-band photoemission spectra

The valence-band spectra of $Bi_{1-x}La_xNiO_3$ taken at 600 eV are shown in Fig. 7 (a). Considering the photoionization cross-sections [26], most of the contributions come from Ni 3d and contributions from O 2p and Bi 6s are very small. (The relative photoionization cross-sections of the Ni 3d, O 2p, and Bi 6s orbitals are $\sim 19:1:1$ [26].) One can observe three main structures labeled as A ($\sim -1.7 \text{ eV}$), B ($\sim -3.3 \text{ eV}$), and C ($\sim -6 \text{ eV}$) and the satellite structure at ~ -11 eV. Figure 7 (c) shows the photon energy dependence of the valence-band spectrum of x = 0.2, including the spectra taken at $h\nu = 21.2$ eV and 40.8 eV. According to the photon-energy dependence of the photoionization cross-sections, the He I spectrum is dominated by the O 2p contribution (Ni 3d : O 2p: Bi $6s \sim 0.37$: 1 : 0.003.) and the Ni 3d contribution increases with increasing photon energy. Structure A, which is most pronounced at 600 eV, is therefore attributed to the contributions for Ni 3d. On the other hand, structures B and C are due to the O 2p band. This assignment is in agreement with other Ni oxides like NiO [11] and $RNiO_3$ [9]. We also performed CI clustermodel calculation by using the same parameters as in the case of Ni 2p XAS and photoemission. At the bottom of Fig. 7 (a) are shown the calculated spectra for the $[NiO_6]^{10-}$ cluster (Ni^{2+}) and the $[NiO_6]^{9-}$ cluster (Ni^{3+}) . The calculated valence-band spectra have been broadened with a Gaussian of 0.8 eV FWHM to account for the combined effects of the instrumental resolution and the d band dispersion, and an energy-dependent Lorentzian (FWHM = $0.2|E - E_F|$) (Ref. [27]) to account for the lifetime broadening of the photohole. Considering the photoionization cross-sections, the Ni 3d emission overwhelms the O 2p emission at $h\nu = 600$ eV, where three main structures and the satellite structure are well reproduced in the calculation for both Ni^{2+} and Ni^{3+} .

Spectra in the vicinity of E_F are shown in Fig. 7 (b). There is no E_F cutoff for the x = 0 sample, consistent with the insulating behavior. Upon La substitution,



FIG. 7: (Color online) Valence-band spectra of $\text{Bi}_{1-x}\text{La}_x\text{NiO}_3$. (a) $h\nu = 600$ eV. The calculated spectra assuming Ni^{2+} and Ni^{3+} are presented at the bottom. (b) $h\nu = 600$ eV (near E_F). (c) x = 0.2 taken at 21.2 eV, 40.8 eV, and 600 eV.

emission appears at E_F and increases with increasing x, indicating the insulator-to-metal transition induced by La substitution.

IV. CONCLUSION

In conclusion, we have measured the photoemission and x-ray absorption spectra of $\text{Bi}_{1-x}\text{La}_x\text{NiO}_3$. From Ni 2p XAS, we observed the change of the valence of Ni. Combined with core-level photoemission studies, it was found that the average valence of Bi remains $\sim 4+$ with increasing x, and La substitution causes hole doping into the Ni sites. These results mean that both the Bi and Ni sites contribute to the metallic conductivity. From the valence-band spectra, we observed a Fermi-level cutoff for x > 0. The spectra of the Ni 2p XAS, the Ni 2p photoemission, and the valence band have been analyzed by configuration-interaction cluster-model calculation, and good agreement between experiment and calculation was obtained.

Acknowledgment

The authors would like to thank K. Ono and A. Yagishita for their support at KEK-PF. This work was supported by a Grant-in-Aid for Scientific Research (S17105002) from the Ministry of Education, Culture, Sports, Science and Technology, Japan. This work was done under the approval of the Photon Factory Program Advisory Committee (Proposal No. 2003G149). H. W. acknowledges support from the Japan Society for the Promotion of Science for Young Scientists.

- M. Imada, A. Fujimori, and Y. Tokura, Rev. Mod. Phys. 70, 1039 (1998).
- [2] J. B. Torrance, P. Lacorre, A. I. Nazzal, E. J. Ansaldo, and C. Niedermayer, Phys. Rev. B 45, R8209 (1992).
- [3] M. Medarde, J. Phys.: Condens. Mat. 9, 1679 (1997).
- [4] S. Ishiwata, M. Azuma, M. Takano, E. Nishibori, M. Takata, M. Sakata, and K. Kato, J. Mater. Chem. 12, 3733 (2002).
- [5] M. Yoshimura, T. Nakamura, and T. Sata, Bull. Tokyo Inst. Technol. 120, 13 (1974).
- [6] S. Ishiwata, M. Azuma, M. Hanawa, Y. Motiromo, Y. Ohnishi, K. Kato, E. Nishibori, M. Takata, M. Sakata, I. Terasaki, and M. Takano, cond-mat/0502066.
- [7] M. Medarde, A. Fontaine, J. L. Garcia-Munoz, J. Rodriguez-Carvajal, M. de Santis, M. Sacchi, G. Rossi, and P. Lacorre, Phys. Rev. B 46, 14975 (1992).
- [8] S. R. Barman, A. Chainani, and D. D. Sarma, Phys. Rev. B 49, 8475 (1994).
- [9] T. Mizokawa, A. Fujimori, T. Arima, Y. Tokura, N. Mori, and J. Akimitsu, Phys. Rev. B 52, 13865 (1995).
- [10] H. Eisaki, S. Uchida, T. Mizokawa, H. Namatame, A.

Fujimori, J. van Elp, P. Kuiper, G. A. Sawatzky, S. Hosoya, and H. Katayama-Yoshida, Phys. Rev. B 45, 12513 (1992).

- [11] A. Fujimori and F. Minami, Phys. Rev. B 30, 957 (1984).
- [12] A. E. Bocquet, T. Mizokawa, T. Saitoh, H. Namatame, and A. Fujimori, Phys. Rev. B 46, 3771 (1992).
- [13] J. C. Slater and G. F. Koster, Phys. Rev. 94, 1498 (1954).
- [14] W. A. Harrison, Electronic Structure and the Properties of Solids (Dover, New York, 1989).
- [15] L. F. Mattheiss, Phys. Rev. B 5, 290 (1972).
- [16] T. Mizokawa and A. Fujimori, Phys. Rev. B 48, 14150 (1993).
- [17] K. Okada and A. Kotani, J. Phys. Soc. Jpn. 60, 772 (1991).
- [18] F. M. F. de Groot, J. C. Fuggle, B. T. Thole, and G. A. Sawatzky, Phys. Rev. B 42, 5459 (1990).
- [19] P. H. Citrin, P. Eisenberger, and D. R. Hamann, Phys. Rev. Lett. 33, 965 (1974).
- [20] M. O. Krause and J. H. Oliver, J. Phys. Chem. Ref. Data 8, 329 (1979).
- [21] H. Namatame, A. Fujimori, H. Takagi, S. Uchida,

F. M. F. de Groot, and J. C. Fuggle, Phys. Rev. B 48, 16917 (1993).

- [22] S. Hüfner, *Photoelectron Spectroscopy* (Springer-Verlag, Berlin, 1995).
- [23] A. Ino, T. Mizokawa, A. Fujimori, K. Tamasaku, H. Eisaki, S. Uchida, T. Kimura, T. Sasagawa, and K. Kishio, Phys. Rev. Lett. **79**, 2101 (1997).
- [24] J. Matsuno, A. Fujimori, Y. Takeda, and M. Takano, Europhys. Lett. 59, 252 (2002).
- [25] A. Fujimori, A. Ino, J. Matsuno, T. Yoshida, K. Tanaka, and T. Mizokawa, J. Electron Spectrosc. Relat. Phenom. 124, 127 (2002).
- [26] J. J. Yeh and I. Lindau, At. Data Nucl. Data Tables 32, 1 (1985).
- [27] H. Höchst, P. Steiner, G. Reiter, and S. Hüfner, Z. Phys. B 42, 199 (1981).