Thermal conductivity of R_2 CuO₄, with R = La, Pr and Gd

K. Berggold^{a,*}, T. Lorenz^a, J. Baier^a, M. Kriener^a, D. Senff^a, S. Barilo^b

and A. Freimuth^a

^a II. Physikalisches Institut, Universität zu Köln, 50937 Köln, Germany

^bInstitute of Solid State & Semiconductor Physics, Belarussian Academy of Sciences, Minsk 220072, Belarus

Abstract

We present measurements of the in-plane (κ_{ab}) and out-of-plane (κ_c) thermal conductivity of Pr₂CuO₄ and Gd₂CuO₄ single crystals. The anisotropy gives strong evidence for a large contribution of magnetic excitations to κ_{ab} , i.e. for a heat current within the CuO₂ planes. However, the absolute values of κ_{mag} are lower than previous results on La₂CuO₄. These differences probably arise from deviations from the nominal oxygen stoichiometry. This has a drastic influence on κ_{mag} , which is shown by an investigation of a La₂CuO_{4+ δ} polycrystal.

 $Key\ words:$ Thermal conductivity, low-dimensional quantum spin systems PACS: 74.72.-h, 66.70.+f, 75.10.Jm

One peculiarity of low-dimensional spin systems is the possibility of large contributions to the heat transport by magnetic excitations. This has been found in 1D systems like spin ladders, [1] whereas the situation in 2D is less clear. The CuO_2 planes in La_2CuO_4 are a good realization of a 2D antiferromagnetic Heisenberg square lattice with a large exchange constant $J \approx$ 1400 K.[2] The thermal conductivity of La₂CuO₄ shows an unusual behavior.[3] For a heat current along the c direction one low-temperature maximum is present, as it is expected for an insulator. The heat is carried by acoustic phonons, and for high temperatures Umklapp scattering yields an approximate 1/T behavior of κ_c . However, for a heat current parallel to the CuO₂ planes a second broad maximum arises in addition to the low-temperature maximum. This can be interpreted in terms of an additional contribution to the heat transport by magnetic excitations. Depending on the crystals, values of $\kappa_{\text{mag}}^{(300\text{ K})} \approx 15...24 \text{ W/Km}$ are reported. [3,4,5] However, a double peak of κ could also arise from a suppression acting in a certain temperature window.[6] This requires an additional scattering mechanism, e.g. due to a structural instability, which is present in La₂CuO₄.[7] Such a structural instability is not present in the nearly iso-structural compound Sr₂CuO₂Cl₂, but still there is a second maximum of κ_{ab} .[8] This gives evidence for a magnetic origin of the second maximum and suggests that a magnetic contribution to κ_{ab} could be a common feature of all single-layered insulating cuprates. In order to investigate this, we studied κ of R_2 CuO₄, with $R = \Pr$, Gd. Both compounds have a very similar CuO₂ square lattice and exchange constant as La₂CuO₄.[9] However, for $R = \Pr$ the structure is stable down to lowest temperatures, whereas for R = Gd a structural phase transition occurs at 685 K.[10]

Fig. 1a shows κ_{ab} and κ_c for Pr₂CuO₄. For κ_c we observe one low-temperature maximum and a 1/T behavior (solid line) above about 70 K. For κ_{ab} , however, a pronounced shoulder occurs at high temperatures, which leads to an anisotropy $\kappa_{ab}/\kappa_c \approx 2$ at room temperature, whereas the heights of the low-temperature maxima differ only by 20%. For Gd₂CuO₄ (Fig. 1b), κ_c can also be described well by phonons. For κ_{ab} a second broad maximum arises at high temperatures. The

 $^{^{*}}$ Corresponding author. Tel: +49-221-470-2911 fax: +49-221-470-6708

Email address: berggold@ph2.uni-koeln.de (K. Berggold).



Fig. 1. Panel a) and b): κ_{ab} and κ_c for $\rm Pr_2CuO_4$ and $\rm Gd_2CuO_4$. The phononic behavior of the out-of-plane measurements at high temperatures is confirmed with 1/T fits (lines). Panel c): κ of a $\rm La_2CuO_{4+\delta}$ polycrystal, see text.

anisotropy at room temperature $\kappa_{ab}/\kappa_c \approx 3$ is even larger than for Pr₂CuO₄. The low-temperature maxima differ by about 25% in height. They are shifted in temperature, which is likely to be caused by sheet defects, which are more efficient for κ_c . This anisotropic behavior, which occurs in both compounds independently from the presence of a structural phase transition, gives further evidence that a magnetic contribution to κ_{ab} is a general feature of these cuprates. We estimate the magnetic contribution at room temperature from the difference $\kappa_{mag} = \kappa_{ab} - \kappa_c$. This assumes that the phononic anisotropy is not too big, what is reasonable, since the low-temperature maxima for the different directions differ much less than the room-temperature values. In this way, we get $\kappa_{\text{mag}}^{(300 \text{ K})} \approx$ 6 W/Km for Pr_2CuO_4 and $\approx 11 \text{ W/Km}$ for Gd_2CuO_4 .

The different values of $\kappa_{\text{mag}}^{(300 \text{ K})}$ raise the question, what determines the size of κ_{mag} . Because J does not differ too much, it is reasonable to assume that the differences mainly arise from different scattering of the heat-carrying excitations. Possible scattering mechanisms are magnon-magnon, magnon-phonon and magnon-hole scattering. Because of the similar magnetic subsystem for all these compounds, we do not expec that magnon-magnon scattering is very different. Whether a different magnon-phonon scattering is present, is difficult to judge at the present stage of the available data. Thus, we concentrate on the study of magnon-hole scattering. The antiferromagnetic order in La₂CuO_{4+ δ} is suppressed drastically by hole doping. To investigate the increase of the magnon-hole scattering, we measured κ of a La₂CuO_{4+ δ} polycrystal (Fig. 1c), which was annealed either in oxygen $(T_N = 250 \text{ K})$ or in vacuum $(T_N = 317 \text{ K})$. For $T_N =$ 317 K a pronounced high-temperature maximum is present. The magnitude of this maximum is lower than observed in single crystals, which partly arises from the averaging $\kappa = 1/3\kappa_c + 2/3\kappa_{ab}$ in a polycrystal. Moreover, T_N is still lower than the maximum value $T_N^{\rm max}\,\approx\,325\,{\rm K}.[11]$ Weak oxygen doping is also the most probable reason for the different $\kappa_{\rm mag}^{\rm (300\,K)}$ in single crystals. [3,4,5] On our Pr₂CuO₄ and Gd₂CuO₄ crystals we determined $T_N = 250 \,\mathrm{K}$ and $295 \,\mathrm{K}$ from neutron scattering and magnetic susceptibility data, respectively. For Gd₂CuO₄ we are not aware of higher T_N values, but for Pr_2CuO_4 significantly larger values up to $T_N \approx 270 \,\mathrm{K}$ are reported.[9] This may explain the low value of κ_{mag} for Pr_2CuO_4 . However, T_N is not solely determined by the oxygen content, but also depends e.g. on the magnetic anisotropy. Thus, no direct conclusion concerning the hole content can be drawn from a comparison of T_N for R_2 CuO₄ with different R.

In conclusion, we have measured κ_{ab} and κ_c of $\Pr_2 CuO_4$ and $Gd_2 CuO_4$. The temperature dependence of κ_{ab} and the anisotropy κ_{ab}/κ_c give evidence for a magnetic contribution to κ_{ab} and suggest that this behavior is a common feature of single-layered cuprates. The magnetic contribution is suppressed drastically by charge-carrier doping, which was shown on a La₂CuO_{4+ δ} polycrystal.

This work was supported by the Deutsche Forschungsgemeinschaft through SFB 608.

References

- [1] A. V. Sologubenko et al., Phys. Rev. Lett. 84, 2714 (2000).
- [2] M. A. Kastner et al., Rev. Mod. Phys. 70, 897 (1998).
- [3] Y. Nakamura *et al.*, Physica C **185-189**, 1409 (1991).
- [4] J.-Q. Yan et al., Phys. Rev. B 68, 104520 (2003).
- [5] C. Hess et al., Phys. Rev. Lett. 90, 197002 (2003).
- [6] M. Hofmann et al., Phys. Rev. Lett. 87, 047202 (2001).
- [7] M. Braden et al., Z. Physik B 94, 29 (1994).
- [8] M. Hofmann et al., Phys. Rev. B 67, 184502 (2003).
- D. Johnston, Normal-state magnetic properties of singlelayer cuprate high-temperature superconductors and related materials (Elsevier Science B.V., 1997).
- [10] M. Braden et al., Europhys. Lett. 25, 625 (1994).
- [11] C. Y. Chen et al., Phys. Rev. B 43, 392 (1991).