Thermopower of $Ce_x R_{1-x}B_6(R = La, Pr and Nd)$

Moo-Sung KIM, ⁺Yuki NAKAI, ⁺Hideki TOU, ⁺Masafumi SERA, ⁺Fumiroshi IGA, ⁺Toshiro TAKABATAKE and ^{*}Satoru KUNII

Dept. of Physics, University of Michigan, Ann Arbor, Michigan 48109, USA

⁺ Dept. of Quantum Matter, ADSM, Hiroshima University, Higashi-Hiroshima 739-8530, Japan

*Dept. of Physics, Tohuku University, Sendai 980-8678, Japan

(Received)

The thermopower, S, of $\operatorname{Ce}_x R_{1-x} B_6$ ($R = \operatorname{La}$, Pr , Nd) was investigated. S with a positive sign shows a typical behavior observed in the Ce Kondo system, an increase with decreasing temperature at high temperatures and a maximum at low temperatures. The S values of all the systems at high temperatures are roughly linearly dependent on the Ce concentration, indicating the conservation of the single-impurity character of the Kondo effect in a wide xrange. However, the maximum value of S, S_{\max} , and the temperature, T_{\max} , at which S_{\max} is observed exhibit different x dependences between $\operatorname{Ce}_x \operatorname{La}_{1-x} B_6$ and $\operatorname{Ce}_x R_{1-x} B_6$ ($R = \operatorname{Pr}$, Nd). In $\operatorname{Ce}_x \operatorname{La}_{1-x} B_6$, T_{\max} , which is ~ 8 K in CeB₆, decreases with decreasing x and converges to ~ 1 K in a very dilute alloy and S_{\max} shows an increase below $x \sim 0.1$ after decreasing with decreasing x. In $\operatorname{Ce}_x R_{1-x} B_6$ ($R = \operatorname{Pr}$, Nd), T_{\max} shows a weak x dependence but S_{\max} shows a roughly linear decrease in x. These results are discussed from the standpoint of the chemical pressure effect and the Ce-Ce interaction. S in the long-range ordered phase shows very different behaviors between $\operatorname{Ce}_x \operatorname{Pr}_{1-x} B_6$ and $\operatorname{Ce}_x \operatorname{Nd}_{1-x} B_6$.

KEYWORDS: CeB₆, Ce_x $R_{1-x}B_6$, thermopower, Kondo effect, RKKY interaction

1. Introduction

For more than two decades, much attention has been given in studying the coexistence and competition between the single-site Kondo effect and the intersite exchange interaction.^{1,2} Although the single-impurity Kondo problem is well understood by now, the Kondo lattice problem still remains to be clarified. The ground state of the Kondo lattice system is determined by the competition between two energy scales, the Kondo temperature, $T_{\rm K}$, and the intersite interaction between the Kondo impurities. Experimental studies for Ce-La and other systems have been performed extensively to clarify how the ground state is varied from the single site to the lattice system. However, its mechanism still remains to be clarified. In this respect, the two-impurity Kondo problem which concerns the RKKY interaction between two Kondo impurities is one of the important themes in the field of heavy-electron physics.³⁻⁶)

In the Kondo systems, the electrical resistivity, ρ , has been studied in detail, both experimentally and theoretically. The thermopower, S, has also been studied by many groups. In many of the Kondo systems, S exhibits an increase with decreasing temperature, a maximum around $T_{\rm K}$ and then a decrease down to lower temperature. When $T_{\rm K}$ is rather high, a sign change is often observed at low temperatures. Although several mechanisms have been proposed, $^{7-11)}$ the understanding of the above characteristics of S is still controversial. The effect of the crystalline electric field (CEF) on S has also been studied.^{12–15)} A shoulder or maximum due to the CEF effect often masks the characteristics of the ground state. In order to clarify the thermopower of the Kondo system, it is important to avoid the ambiguity from the CEF effect. In this sense, $Ce_x La_{1-x} B_6$ is a good material be-

1

cause the CEF Γ_8 quartet ground state is well separated from the excited Γ_7 doublet state and $T_{\rm K}$ is low.¹⁶ When $T_{\rm K}$ is comparable to the intersite interaction between the Kondo impurities, a rich variety of interesting ground states appear. CeB_6 is one of the typical examples with such an interesting ground state. CeB_6 is famous for the existence of the unusual antiferro-quadrupolar (AFQ) ordered phase II dominated by the AF octupolar (AFO) and AF exchange interactions.^{17–19}) For the last several decades, how the character of the Kondo effect is varied by the substitution of La ions in $Ce_x La_{1-x} B_6$ has been studied.^{20–22)} For $Ce_x La_{1-x} B_6$, the $\ln T$ dependence of ρ at high temperatures is independent of Ce concentration, indicating that the single-impurity Kondo effect is conserved at high temperatures. Recently, differentiating from the Kondo effect in La-doped Ce compounds, we have studied how the Kondo effect is affected in the localized magnetic system using $Ce_x R_{1-x} B_6(R = Pr)$, Nd).^{23–25)} PrB_6 exhibits two successive phase transitions at $T_{\rm Cm} = 4.2$ K and $T_{\rm IC} = 7$ K.²⁶) The commensurate (C) magnetic ordered state is realized below $T_{\rm Cm}$ and the incommensurate (IC) one below T_{IC} . It is suggested that the O_{xy} -type AFQ interaction plays an important role in the C phase from the similarity of the noncollinear magnetic structure with an easy axis along the twofold one to that in phase III of CeB_6 .^{26, 27} Recently, we reported the results for $Ce_{0.7}Pr_{0.3}B_6^{(23)}$. The AFQ and magnetic ordered phases coexist and ρ exhibits the destruction of the Kondo singlet state in the magnetic long-rangeordered (LRO) phase in this compound. These indicate the strong Ce-Pr coupling in $Ce_{0.7}Pr_{0.3}B_6$. NdB₆ exhibits a type-I AF magnetic structure below $T_{\rm N}$ = 8 K where the O_2^0 -type FQ interaction plays an important role.^{28,29)} Recently, we reported the following results of the xdependent physical properties of $Ce_x Nd_{1-x}B_6$.^{24, 25)} ρ

per Ce ion is nearly independent of Ce concentration at high temperatures as was observed in $Ce_x La_{1-x} B_6$, indicating that the Kondo effect at high temperatures has a single-impurity character. Namely, the Kondo effect at high temperatures is hardly affected by the surrounding Nd ions. The magnetic phase diagram of $Ce_x Nd_{1-x}B_6$ shows that the AFQ ordering does not coexist with the magnetic ordering for x < 0.8, which differs from the case of $Ce_{0.7}Pr_{0.3}B_6$.²³⁾ For $x \le 0.88$, two successive magnetic phase transitions appear at $T_{\rm N}^{\rm H}$ and $T_{\rm N}^{\rm L,24,25}$ For x <0.5, the LRO phase at the higher transition temperature $T_{\rm N}^{\rm H}$ is mainly induced by Nd ions and the Kondo singlet state survives below $T_{\rm N}^{\rm H}$. However, at the lower transition temperature $T_{\rm N}^{\rm L}$, the Ce ions themselves contribute to the formation of the magnetic order and the Kondo singlet state is destroyed below $T_{\rm N}^{\rm L}$.

We have two purposes in the present work. The first is to clarify the mechanism of the competition between the Kondo effect and the intersite interaction between the Ce ions and how the ground state changes from the dilute Kondo system to the lattice system in $\text{Ce}_x \text{La}_{1-x} B_6$. This system is one of the best for clarifying the S of the Kondo system both experimentally and theoretically because CeB_6 has a well-separated CEF Γ_8 ground state with low Kondo temperature. The second is to clarify how S is affected by the R(=Pr, Nd) doping in CeB_6 where Ce ions are surrounded by the magnetic R ions.

2. Experimental Details

Most of the samples used in the present experiments are the single-crystalline but several polycrystalline samples, namely, $\text{Ce}_x \text{La}_{1-x} \text{B}_6(x = 0.01, 0.03, 0.2, 0.9)$ and $\text{Ce}_x \text{Pr}_{1-x} \text{B}_6(x = 0.03, 0.1)$, are also used. The details of the preparation of the single-crystalline $\text{Ce}_x R_{1-x} \text{B}_6(R = \text{La}, \text{Nd} \text{ and } \text{Pr})$ were described in a previous report.³⁰⁾

The thermopower measurement was performed from 1.5 to 300 K by a usual differential method in zero magnetic field. The sample was suspended between two copper blocks across which $1 \sim 5\%$ of the measurement temperature was set in a temperature gradient. The thermoelectric voltage was measured through gold wires fixed on the sample. The absolute thermopower of the gold wires used in the present experiment was caliblated against pure lead using the thermopower data of Roberts.³¹

3. Experimental Results

3.1 Thermopower of $Ce_x R_{1-x} B_6(R = La, Pr, Nd)$ in paramagnetic region

Figure 1 shows the temperature dependence of the thermopower, S, of $\operatorname{Ce}_{x}R_{1-x}B_{6}(R = \text{La}, \text{Pr and Nd})$ in the form of S vs ln T.

Figure 2 shows the x dependences of S_{max} , T_{max} , S(20 K) and S(50 K) of $\text{Ce}_x \text{R}_{1-x} \text{B}_6(R = \text{La}, \text{Pr}, \text{Nd})$. Here, S_{max} is the maximum value of S. T_{max} is the temperature at which S takes a maximum. S(20 K) and S(50 K) are the S values at T = 20 K and 50 K, respectively.

In CeB₆, S with a positive sign exhibits an increase with decreasing temperature and a large peak of ~ 60 μ V/K at T ~ 8 K, indicating the existence of the Kondo effect. With decreasing temperature, two anomalies are



Fig. 1. Temperature dependence of S of $Ce_x R_{1-x}B_6$ (R= (a) La, (b) Pr and (c) Nd).

observed at $T_{\rm Q} = 3.3$ K and $T_{\rm N} = 2.3$ K and a change of sign is observed below $T_{\rm N}$, which are in good agreement with previous reports.^{32–34)} It is noted that a tiny peak is observed at $T_{\rm N}$ which was not reported before.

Here, we mention the overall characteristic behaviors of the S of $\operatorname{Ce}_x R_{1-x} \operatorname{B}_6(R = \operatorname{La}, \operatorname{Pr} \text{ and } \operatorname{Nd})$ in a paramagnetic region at high temperatures. In all the alloy systems, S exhibits similar behaviors in which S increases with decreasing temperature in a high-temperature region and the magnitude of S is roughly proportional to the Ce concentration. S(20 K) and S(50 K) for three systems show a roughly inear decrease with a decrease in x value. This is similar to the single-impurity character of the Kondo effect found in electrical resistivity, ρ .^{21,24} Thus, the experimental results indicate that S at high temperatures seems to be estimated as a summation of S induced by the independent Kondo scattering on each Ce site.

With a decrease in Ce concentration, different behaviors are observed between $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$ and $\operatorname{Ce}_x R_{1-x} \operatorname{B}_6(R = \operatorname{Pr}, \operatorname{Nd})$ at low temperatures. In



Fig. 2. x dependences of $S_{\max}(\bullet)$, S at T=20 K(\blacktriangle) and 50 K(\blacktriangledown), and $T_{\max}(\circ)$ for Ce_x R_{1-x} B₆. (a) R=La, (b) R=Pr and (c) R=Nd. All lines represent guides to the eyes.

 $Ce_x La_{1-x} B_6$, although S_{max} monotonically decreases down to $x \sim 0.1$, it does not converge to zero but increases largely in a very dilute x region. T_{max} decreases from ~ 8 K for x = 1.0 to ~ 2 K for x = 0.1. For x < 0.03, $S_{\rm max}$ is not observed down to the lowest temperature studied in the present experiment. However, the S values of these dilute samples are consistent with the previously reported results that a very large maximum in S was found at around $T \sim 1$ K in more dilute compounds of $Ce_x La_{1-x} B_6(x = 0.0025, 0.005, 0.01, and 0.02)$.³⁵⁾ Filled and open squares for very dilute samples in Fig. 2(a)represent the S_{max} and T_{max} of the results from ref. 35. From the present and reported results, with a decrease in Ce concentration, the T_{\max} of $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$ seems to converge to $T_{\rm K} \sim 1$ K in a very dilute region, which is expected from the theoretical study of S for the Kondo compounds.^{7,10} However, the results for $Ce_x R_{1-x} B_6(R)$ = Pr, Nd) are very different from those for $Ce_x La_{1-x} B_6$. The S_{max} of $\text{Ce}_x R_{1-x} B_6(R = \text{Pr}, \text{Nd})$ decreases rather linearly with decreasing x and converges to zero with a decrease in Ce concentration, and T_{max} shows a weak xdependence both in $Ce_x Pr_{1-x}B_6$ and $Ce_x Nd_{1-x}B_6$, although it exhibits a small increase with decreasing x; from ~ 8 K to ~ 9 K in $Ce_x Pr_{1-x}B_6$ and from ~ 8 K to ~ 11 K in $\operatorname{Ce}_x \operatorname{Nd}_{1-x} B_6$. The S of $\operatorname{Ce}_x \operatorname{La}_{1-x} B_6$ in a small



Fig. 3. Temperature dependences of S (symbols) and ρ (solid lines) for Ce_xLa_{1-x}B₆ ($x \leq 0.25$). The ρ data for x = 0.25 is cited from ref. 22.

x region at low temperatures is very different from those of $\operatorname{Ce}_x R_{1-x} B_6$ ($R = \operatorname{Pr}$, Nd). This difference comes from the existence or nonexistence of the LRO phase transition at several Kelvins.

Figure 3 shows the S and ρ of $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$ ($x \leq 0.25$) below 10 K. For x = 0.25, ρ shows a maximum at $T \sim 1$ K. On the other hand, S_{\max} locates at $T \sim 4$ K at which ρ still exhibits a logarithmic increase with decreasing temperature. For x = 0.1, S shows a maximum at ~ 2 K and a precursor of a maximum a slightly below 2 K for x =0.03. In both samples, only a logarithmic increase is observed in ρ in this temperature region. It should be noted that although the magnitude of ρ is roughly proportional to the Ce concentration, that of S does not exhibit such a proportional behavior in this temperature region.

Figure 4 shows the temperature dependences of the ρ and S of LaB₆. The residual resistivity ρ_0 of LaB₆ is as small as ~ 0.2 $\mu\Omega$ cm, and ρ shows an increase with increasing temperature above ~ 50 K. As for S, its magnitude is very small in the entire temperature region. A small temperature dependence is observed below ~ 50 K, but S is almost constant above ~ 50 K.

In order to estimate the Ce contribution to S, usually the Nordheim-Gorter rule: $S \cdot \rho = S_{\text{La}} \cdot \rho_{\text{La}} + S_{\text{Ce}} \cdot \rho_{\text{Ce}}$, is used. In the present case, as $S_{\text{La}} \cdot \rho_{\text{La}}$ is very small in the entire temperature region, the observed S in $\text{Ce}_x \text{La}_{1-x} B_6$ could be estimated roughly as the contribution from the Ce ions.

3.2 x dependences of T_{max} and long-range-ordering (LRO) temperatures

Figure 5 shows the x dependences of T_{max} and the LRO temperatures, T_{LRO} , of $\text{Ce}_x R_{1-x} B_6$ (R = La, Pr, Nd). T_{max} is shown by a dashed line in all the systems. The results on the LRO temperatures for R = La and Nd are cited from refs. 22 and 24, respectively. The result for R = Pr is obtained from the present result. Here, we note



Fig. 4. Temperature dependences of ρ (thin line) and S (thick line) of LaB₆.

that the x dependence of T_{max} is found to show roughly the same tendency as that of T_{LRO} .

In Ce_xLa_{1-x}B₆, $T_{\rm Q}$ is rapidly suppressed by La doping and disappears at around $x \sim 0.7$. The suppression rate of $T_{\rm N}$ which is changed to $T^{\rm IV-I}$ at $x \sim 0.8$ is smaller than that of $T_{\rm Q}$ and seems to disappear at around $x \sim$ $0.3.^{22}$ However, even below $x \sim 0.3$, the effect of the Ce-Ce interaction remains, as is seen in a broad maximum of ρ at $T \sim 1$ K for x = 0.25 in Fig. 3.

In $\operatorname{Ce}_x \operatorname{Pr}_{1-x} \operatorname{B}_6$, for $0.88 \leq x \leq 1$, T_{Q} decreases, but T_{N} increases with decreasing x. With a further decrease in Ce concentration below $x \leq 0.88$, two successive magnetic phase transitions, T_{IC1} and T_{IC2} , appear, and both transition temperatures increase monotonically with decreasing x. The T_{Cm} of PrB_6 is rapidly suppressed by a small amount of Ce doping. Recently, we have reported the magnetic phase diagram of $\operatorname{Ce}_{0.7}\operatorname{Pr}_{0.3}\operatorname{B}_6$ and showed that the quadrupolar ordering coexists with the magnetic ordering.²³⁾ This indicates that both Ce and Pr ions contribute to the formation of the LRO states and the Ce-Pr coupling in $\operatorname{Ce}_x \operatorname{Pr}_{1-x}\operatorname{B}_6$ differs strongly from the weak Ce-Nd coupling in $\operatorname{Ce}_x \operatorname{Nd}_{1-x}\operatorname{B}_6$ as will be discussed later.

In $\operatorname{Ce}_x \operatorname{Nd}_{1-x} \operatorname{B}_6$,²⁴⁾ for $0.88 \le x \le 1$, the *x* dependences of T_{Q} and T_{N} are similar to those of $\operatorname{Ce}_x \operatorname{Pr}_{1-x} \operatorname{B}_6$. With a further decrease in Ce concentration, two magnetic LRO phases appear below $T_{\mathrm{N}}^{\mathrm{H}}$ and $T_{\mathrm{N}}^{\mathrm{L}}$ for $0.3 \le x \le 0.88$. $T_{\mathrm{N}}^{\mathrm{L}}$ shows a decrease with decreasing *x* and seems to disappear at $x \sim 0.3$, which is the same value at which phase IV disappears in $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$.

3.3 Low-temperature behavior of S of $Ce_x R_{1-x} B_6$

In order to observe the evolution of the Kondo effect and LRO with the change of Ce concentration in $\operatorname{Ce}_{x}R_{1-x}B_{6}(R = \operatorname{Pr} \text{ and } \operatorname{Nd})$, we show the temperature dependence of S at low temperatures in an expanded scale in Figs. 6 and 7, respectively.

First, we briefly mention the results for $\text{Ce}_x \text{La}_{1-x} \text{B}_6$. A decrease in S is observed below T_{LRO} for $x \ge 0.75$. Although such a decrease is not observed for $x \le 0.6$, it is



Fig. 5. x dependences of T_{max} (dashed line) and LRO temperatures (symbols) of $\text{Ce}_x R_{1-x} B_6(R = \text{La}, \text{Pr} \text{ and Nd})$ at H=0. The LRO temperatures for R = La and Nd are cited from refs. 22 and 24, respectively.

because their T_{LRO} is lower than the lowest temperature studied in the present experiment.

Next, we mention the results for $\operatorname{Ce}_{x}\operatorname{Pr}_{1-x}\operatorname{B}_{6}$. For x = 0.9, only one anomaly is found at ~ 2.8 K because T_{Q} is very close to T_{N} in this sample. For $0.3 \leq x \leq 0.7$, S shows a decrease below T_{IC1} and T_{IC2} . The decrease in S below T_{IC1} is much more pronounced than that below T_{IC2} . A clear decrease below T_{IC1} and T_{IC2} indicates that Ce ions lose their character as the Kondo scattering center and contribute to the IC1 or IC2 magnetic ordering as localized ions. The concave curvature below T_{IC1} or T_{IC} becomes more pronounced below x = 0.3, which is very different from no anomaly at $T_{\mathrm{N}}^{\mathrm{H}}$ in $\operatorname{Ce}_{x}\operatorname{Nd}_{1-x}\operatorname{B}_{6}(x \leq 0.5)$.

For $\operatorname{Ce}_x \operatorname{Nd}_{1-x} \operatorname{B}_6$, with a decrease in Ce concentration from x = 1 down to 0.9, the sharp drop at T_{N} moves up to a slightly higher temperature, while the anomaly at T_{Q} oppositely moves down to lower temperatures. As x is decreased through $x \sim 0.88$, new LRO phases appear at $T_{\mathrm{N}}^{\mathrm{L}}$ and $T_{\mathrm{N}}^{\mathrm{H},25}$ For x = 0.6 and 0.7, the LROs at $T_{\mathrm{N}}^{\mathrm{L}}$ and $T_{\mathrm{N}}^{\mathrm{H}}$ exhibit sharp and weak changes in slope, respectively. These behaviors of S at $T_{\mathrm{N}}^{\mathrm{L}}$ and $T_{\mathrm{N}}^{\mathrm{H}}$ are consistent with the results on ρ , which exhibits a sudden drop at $T_{\mathrm{N}}^{\mathrm{L}}$





Fig. 6. Temperature dependence of S below T=10 K for $\operatorname{Ce}_x\operatorname{Pr}_{1-x}\operatorname{B}_6$. For clarity, the origin of the vertical axis is shifted. Each horizontal line indicates the origin of the vertical axis for each compound. Arrows indicate the LRO transition temperatures.

and a lax decrease at $T_{\rm N}^{\rm H,\,24)}$ On the other hand, S for x=0.5 shows a clear anomaly at $T_{\rm N}^{\rm L}$ but no anomary at $T_{\rm N}^{\rm H}$. These behaviors at $T_{\rm N}^{\rm L}$ and $T_{\rm N}^{\rm H}$ are consistent with the results on ρ , which shows a clear decrease at $T_{\rm N}^{\rm L}$ but no anomaly at $T_{\rm N}^{\rm H}$. Thus, the present results also suggest that the nature of the LRO state below $T_{\rm N}^{\rm H}$ is changed below and above $x \sim 0.5$. It is noted that the magnetic susceptibility and specific heat show clear anomalies at $T_{\rm N}^{\rm H}$ for x=0.5.

4. Discussion

In the high-temperature region, the magnitude of S originating from the Kondo effect is roughly proportional to the Ce concentration in all the alloy systems. This suggests that the impurity Kondo character is conserved and the Ce-Ce or Ce-R(R = Pr, Nd) interaction is negligible at high temperatures.

On the other hand, at low temperatures, very different x dependences of S_{max} and T_{max} are observed between $\text{Ce}_x \text{La}_{1-x} \text{B}_6$ and $\text{Ce}_x R_{1-x} \text{B}_6 (R = \text{Pr}, \text{Nd})$. The maximum of S is often used to estimate the T_{K} of a dilute Kondo system. It is reported that the dilute compounds $\text{Ce}_x \text{La}_{1-x} \text{B}_6 (x = 0.0025 \sim 0.02)$ exhibit a large peak slightly below T_{K} ,³⁵⁾ consistent with the theoretical study.⁷⁾ However, in CeB_6 , T_{max} is observed at ~ 8 K, which is much higher than the T_{K} of the dilute $\text{Ce}_x \text{La}_{1-x} \text{B}_6$ alloys. The present results show that T_{max} exhibits a large variation as a function of x. On the other hand, it was reported that $T_{\text{K}} \sim 1$ K is almost constant

Fig. 7. Temperature dependence of S below T=10 K for $\operatorname{Ce}_x\operatorname{Nd}_{1-x}\operatorname{B6}$. For clarity, the origin of the vertical axis is shifted. Each horizontal line indicates the origin of the vertical axis for each compound. Arrows indicate the LRO transition temperatures, which are cited from ref. 24.

independent of x in $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6^{(21)}$ However, strictly speaking, it has not been necessarily verified.

As the possible origin of S_{\max} , the entrance into the coherent Kondo state is considered. However, this possibility is ruled out by comparing the results of $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$ with those of $\operatorname{Ce}_x R_{1-x} \operatorname{B}_6(R = \operatorname{Pr}, \operatorname{Nd})$. In $\operatorname{Ce}_x R_{1-x} \operatorname{B}_6$, being different from $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$, T_{\max} exhibits a small increase from 8 K to ~ 10 K with decreasing x. In $\operatorname{Ce}_x R_{1-x} \operatorname{B}_6(R = \operatorname{Pr}, \operatorname{Nd})$ where Ce ions are surrounded by the magnetic ions, it is difficult to expect that the entrance into the coherent Kondo state is conserved at the same temperature as ~ 8 K.

Next, we discuss the possibility that S_{max} appears at $T_{\rm K}$, namely, the possibility that $T_{\rm max} \sim T_{\rm K}$ in $Ce_x R_{1-x} B_6$. Generally, T_K is varied with the change of the effect of chemical pressure in the alloy systems. The effect of chemical pressure on the Kondo effect is important for discussing the physical properties of the alloy systems. Such a chemical pressure effect was discussed in $\operatorname{Ce}_{x}(\operatorname{La}, Y)_{1-x}\operatorname{Cu}_{2.05}\operatorname{Si}_{2}$ in detail.^{14,15} It is known that $T_{\rm K}$ is enhanced under pressure, which is a result of the enhancement of the mixing between the 4f and conduction electrons. In the alloy systems, the difference of the ionic radius of the doped rare-earth ion from that of the mother compound induces the chemical pressure effect. When x decreases, the negative pressure effect is expected in $Ce_x La_{1-x} B_6$ and the positive one in $\operatorname{Ce}_{x} R_{1-x} \operatorname{B}_{6}(R = \operatorname{Pr}, \operatorname{Nd})$. On the other hand, in a large x



Fig. 8. Lattice constant dependence of T_{\max} of $\operatorname{Ce}_x \operatorname{R}_{1-x} \operatorname{B}_6(R = \operatorname{La}(\blacksquare), \operatorname{Pr}(\Box) \text{ and } \operatorname{Nd}(\Delta)).$

region, the effect of pressure on the Ce-Ce interaction becomes larger in addition to the single-ion pressure effect. The effect of pressure on the Ce-Ce interaction consists of two different mechanisms. One is to form the coherent Kondo state and the other is to increase the Ce-Ce interaction as a localized system which suppresses the Kondo effect.

Experimental results are as follows. T_{max} decreases in $\operatorname{Ce}_{x}\operatorname{La}_{1-x}\operatorname{B}_{6}$ but slightly increases in $\operatorname{Ce}_{x}R_{1-x}\operatorname{B}_{6}(R)$ Pr, Nd) with decreasing x. This tendency could be explained by the consideration that $T_{\rm K}$ is enhanced when the average lattice constant decreases. However, such a consideration seems to be unacceptable, when we consider the relationship between T_{max} and the lattice constants of $Ce_x R_{1-x} B_6$ as follows. Here, we show the lattice constant dependence of $T_{\rm max}$ in Fig. 8. $T_{\rm max}$ shows a large increase with a decrease in lattice constant in a small x region of $Ce_x La_{1-x} B_6$ and its rate of increase becomes smaller as x approaches 1. The slope of $T_{\rm max}$ vs lattice constant seems to change at around $x \sim 0.4$. This suggests that the slope of $T_{\rm max}$ becomes small when the LRO state appears at low temperatures. The T_{max} of $\text{Ce}_x R_{1-x} B_6$ increases with a decrease in lattice constant, but the slope of $Ce_x R_{1-x}B_6$ is smaller than that of $Ce_x La_{1-x} B_6$. The slope of T_{max} differs between $\operatorname{Ce}_{x}\operatorname{Pr}_{1-x}\operatorname{B}_{6}$ and $\operatorname{Ce}_{x}\operatorname{Nd}_{1-x}\operatorname{B}_{6}$. The T_{\max} values of these two systems are not scaled by the lattice constant. That for $Ce_x Pr_{1-x}B_6$ is slightly smaller than that for $\operatorname{Ce}_x \operatorname{Nd}_{1-x} B_6$. Thus, it is difficult to consider that $T_{\rm max} \sim T_{\rm K}$.

We expect another mechanism for the x dependence of T_{max} , which may originate from the difference of Pr and Nd ions of these two systems. Here, we note that the x dependence of T_{max} shows roughly the same tendency as that of T_{LRO} as shown in Fig. 5. In $\text{Ce}_x \text{La}_{1-x} \text{B}_6$, T_{max} decreases with decreasing x. The Ce-Ce interaction is suppressed with decreasing x because of the increase in the Ce-Ce distance. It is possible to associate T_{max} with the temperature at which the effect of the Ce-Ce inter-

action begins to appear in the macroscopic properties. In CeB₆, below ~ 10 K, ρ exhibits a deviation from the In T dependence at high temperatures.²¹⁾ This may be due to the suppression of the Kondo effect by the Ce-Ce interaction. This temperature of ~ 10 K roughly coincides with $T_{\rm max}$ in CeB₆. A similar relationship between the T_{max} and the temperature at which the deviation of ρ from the ln T dependence in the high-temperature region is also observed in $Ce_x La_{1-x} B_6$ in Fig. 1(b) of ref. 21. With decreasing Ce concentration in $Ce_x La_{1-x} B_6$, the Ce-Ce interaction is suppressed, which may suppress $T_{\rm max}$. Thus, the appearance of $S_{\rm max}$ may be a result of the competition between the Kondo effect and the Ce-Ce interaction. However, in $\operatorname{Ce}_{x} R_{1-x} \operatorname{B}_{6}(R = \operatorname{Pr}, \operatorname{Nd}), T_{\max}$ shows a small increase with decreasing x, different from the roughly linear x dependence in $Ce_x La_{1-x} B_6$. The clear difference between $\operatorname{Ce}_{x}\operatorname{La}_{1-x}\operatorname{B}_{6}$ and $\operatorname{Ce}_{x}R_{1-x}\operatorname{B}_{6}(R)$ = Pr, Nd) is the nonexistence or existence of the magnetic ions between Ce ions. When the interaction between the rare-earth ions is that of the RKKY type, we expect the suppression of the Ce-Ce interaction in $Ce_{x}La_{1-x}B_{6}$ with decreasing Ce concentration because of the increase in Ce-Ce distance. On the other hand, in $\operatorname{Ce}_{x}R_{1-x}B_{6}(R=\operatorname{Pr},\operatorname{Nd}), R \text{ ions exist between Ce ions.}$ The experimental result that T_{max} does not depend so much on x in $\operatorname{Ce}_{x} R_{1-x} \operatorname{B}_{6}(R = \operatorname{Pr}, \operatorname{Nd})$ suggests that the strength of the Ce-Ce interaction is not markedly reduced by the exsitence of the magnetic R ions.

As for the results for $Ce_x La_{1-x} B_6$ for $0.1 \le x \le 0.25$, there exists another question why T_{\max} is much higher than the temperature at which ρ exhibits a maximum, which was shown in Fig. 3. The maximum of ρ may originate from the growth of the Ce-Ce interaction as mentioned above. It is also possible to associate S_{\max} with the growth of the Ce-Ce interaction. These suggest that the effect of the growth of the Ce-Ce interaction is more sensitive for S than for ρ .

Finally, we discuss S in the LRO state. In the case of $\operatorname{Ce}_{x}\operatorname{La}_{1-x}\operatorname{B}_{6}$, a clear decrease is observed in S below $T_{\rm Q}$, $T_{\rm N}$ or $T^{\rm IV-I}$. Such a decrease originates from the destruction of the Kondo singlet state accompanied by the LRO induced by Ce ions themselves. In $Ce_x Pr_{1-x}B_6$, S shows a clear decrease below $T_{\rm LRO}$. This suggests that the Kondo singlet state on the Ce site is destroyed below $T_{\rm LBO}$ and both Ce and Pr ions equally contribute to the formation of the LRO state. This indicates that the Ce-Pr coupling is strong in $Ce_x Pr_{1-x}B_6$. On the other hand, in $\operatorname{Ce}_x \operatorname{Nd}_{1-x} B_6$, although a similar anomaly of S accompanied by the LRO is observed for x > 0.6, an anomaly is difficult to recognize at $T_{\rm N}^{\rm H}$ for $x \leq 0.5$. This indicates that the electronic state of the Ce ion below $T_{\rm N}^{\rm H}$ is different below and above $x \sim 0.5$, where the x dependence of $T_{\rm N}^{\rm H}$ is changed as is shown in Fig. 5. For $x \ge 0.6$, the Kondo singlet state is destroyed below $T_{\rm N}^{\rm H}$. For $x \leq 0.5$, the Kondo state survives below $T_{\rm N}^{\rm H}$ and is destroyed below $T_{\rm N}^{\rm L}$. In our previous papers,^{24,25)} we reported that the LRO state below $T_{\rm N}^{\rm L}$ is formed by Ce ions themselves but that below $T_{\rm N}^{\rm H}$ is mainly formed by Nd ions and we discussed that the Kondo effect survives between $T_{\rm N}^{\rm L}$ and $T_{\rm N}^{\rm H}$. The present results support these considerations.



Fig. 9. Conjectured temperature dependence of magnetic ordered moment on Ce site in (a) $\operatorname{Ce}_x \operatorname{Pr}_{1-x} \operatorname{B}_6$ and (b) $\operatorname{Ce}_x \operatorname{Nd}_{1-x} \operatorname{B}_6$ with $0.3 \leq x \leq 0.5$ below LRO temperatures. See the text for details.

From these results, we conjecture the temperature dependence of the ordered moment on the Ce site below the T_{LRO} of $\text{Ce}_x \text{R}_{1-x} \text{B}_6(R = \text{Pr}, \text{Nd})$ as shown in Figs. 9(a) and 9(b), respectively. In $\text{Ce}_x \text{Pr}_{1-x} \text{B}_6$, as both Ce and Pr ions equally contribute to the LRO, the ordered moment on the Ce site shows a normal behavior as shown in Fig. 9(a). However, in $\text{Ce}_x \text{Nd}_{1-x} \text{B}_6(0.3 \leq x \leq 0.5)$, the effect of the ordered Nd ions on Ce ions is small and the Kondo singlet state on the Ce site survives below T_{N}^{H} . As the Kondo singlet state is expected to be destroyed at very low temperatures, the temperature dependence of the ordered moment on the Ce site is expected as that shown in Fig. 9(b).

At present, we do not know why such a large difference in behavior is observed between $\text{Ce}_x \text{Pr}_{1-x} B_6$ and $\text{Ce}_x \text{Nd}_{1-x} B_6$ below T_{LRO} .

5. Conclusion

In summary, we have measured the thermopower, S, of $\operatorname{Ce}_{x} R_{1-x} \operatorname{B}_{6}(R = \operatorname{La}, \operatorname{Pr}, \operatorname{Nd})$ in a wide range of the Ce concentration. At high temperatures, the impurity Kondo behavior is observed in the S of all the alloy systems, as was observed in the electrical resistivity of $Ce_x La_{1-x} B_6$. At low temperatures, S exhibits a maximum at T_{max} in all the alloy systems, but their temperature dependences differ from each other. In $Ce_x La_{1-x} B_6$, both S_{\max} and T_{\max} decrease with decreasing x, but S_{\max} increases below $x \sim 0.1$. T_{max} seems to converge to the $T_{\rm K} \sim 1 \text{ K}$ of very dilute $\operatorname{Ce}_x \operatorname{La}_{1-x} \operatorname{B}_6$. In $\operatorname{Ce}_x R_{1-x} \operatorname{B}_6(R)$ = Pr, Nd), $T_{\rm max}$ shows a weak x dependence but $S_{\rm max}$ seems to converge to zero in a sample with very small x value. The x dependnce of T_{\max} is consistent with the chemical pressure effect in the alloy systems but is not explained only by this effect. As another origin of the xdependence of T_{max} , we proposed the effect of the Ce-Ce interaction. In $Ce_x La_{1-x} B_6$, the Ce-Ce interaction is suppressed with decreasing x, but in $\operatorname{Ce}_{x} R_{1-x} B_{6}(R)$ = Pr, Nd), it is conserved by the existence of the R ions between Ce ions. T_{max} is higher than the temperature at which ρ exhibits a maximum for 0.1 < x <0.25, which suggests that the effect of the Ce-Ce interaction for S appears at higher temperatures than for ρ . In the LRO state, very different behaviors are observed between $\operatorname{Ce}_{x}\operatorname{Pr}_{1-x}\operatorname{B}_{6}$ and $\operatorname{Ce}_{x}\operatorname{Nd}_{1-x}\operatorname{B}_{6}$. In $\operatorname{Ce}_{x}\operatorname{Pr}_{1-x}\operatorname{B}_{6}$, S is rapidly suppressed below the LRO temperature, indicating the suppression of the Kondo singlet state and the strong Ce-Pr coupling. On the other hand, in $\operatorname{Ce}_x \operatorname{Nd}_{1-x} \operatorname{B}_6(x \leq 0.5)$, S is not affected by the magnetic ordering mainly induced by Nd ions, indicating the survival of the Kondo singlet state and the weak Ce-Nd interaction in this system.

Acknowledgments

The present work was supported by a COE Research (13E2002) from the Ministry of Education, Culture, Sports, Science and Technology of Japan. MSK was financially supported by the Japan Society for the Promotion of Science. The low-temperature measurements were supported by the Cryogenic Center of Hiroshima University.

- S. Doniach: in Valence Instabilities and Related Narraw Band Phenomena, ed. by R. D. Parks (Plenum, New York, 1977) p. 169.
- B. A. Jones, C. M. Varma and J. W. Wilkins: Phys. Rev. Lett. 61 (1988) 125.
- C. Jayaprakash, H. R. Krishna-murthy and J. W. Wilkins: Phys. Rev. Lett. 47 (1981) 737.
- M. Lavagna and M. Cyrot, Solid State Commun. 55 (1985) 555.
- 5) O. Sakai and Y. Shimizu: J. Phys. Soc. Jpn. **61** (1992) 2333.
- 6) P. Schlottmann: Phys. Rev. B **62** (2000) 10067.
- N. E. Bickers, D. L. Cox and J. W. Wilkins: Phys. Rev. Lett. 54 (1985) 230.
- N. E. Bickers, D. L. Cox and J. W. Wilkins: Phys. Rev. B 36 (1987) 2036.
- 9) K. Fischer, Z. Phys.: Condens. Matter 76 (1989) 315.
- V. Zlatić, B. Horvatić, I. Milat, B. Coqblin, G. Czycholl and C. Grenzebach: Phys. Rev. B 68 (2003) 104432.
- 11) V. Zlatić and R. Monnier: Phys. Rev. B 71 (2005) 165109.
- 12) A. K. Bhattacharjee and B. Coqblin: Phys. Rev. B 13 (1976) 3441.
- 13) S. Maekawa, S. Kashiba, M. Tachiki and S. Takahashi: J. Phys. Soc. Jpn. 55 (1986) 3194.
- 14) M. Očko, D. Drobac, B. Buschinger, C. Geibel and F. Steglich: Phys. Rev. B 64 (2001) 195106.
- 15) M. Očko, C. Geibel and F. Steglich: Phys. Rev. B 64 (2001) 195107.
- 16) E. Zirngiebl, B. Hillebrands, S. Blumenroder, G. Guntherodt, M. Loewenhaupt, J. M. Carpenter, K. Winzer and Z. Fisk: Phys. Rev. B **30** (1984) R4052.
- 17) J. M. Effantin, J. Rossat-Mignod, P. Burlet, H. Bartholin, S. Kunii and T. Kasuya: J. Magn. Magn. Mater. 47-48 (1985) 145.
- 18) O. Sakai, R. Shiina, H. Shiba and P. Tahlmeier: J. Phys. Soc. Jpn. 66 (1997) 3005.
- 19) M. Sera and S. Kobayashi: J. Phys. Soc. Jpn. 68 (1999) 1664.
- 20) K. Samwer and K. Winzer: Z. Phys. B 25 (1976) 269.
- 21) N. Sato, A. Sumiyama, S. Kunii, H. Nagano and T. Kasuya: J. Phys. Soc. Jpn. 54 (1985) 1923.
- 22) S. Kobayashi, M. Sera, M. Hiroi, N. Kobayashi and S. Kunii: J. Phys. Soc. Jpn. 69 (2000) 926.
- 23) S. Kishimoto, A. Kondo, M-S. Kim, H. Tou, M. Sera and F. Iga: J. Phys. Soc. Jpn. 74 (2005) 2913.
- 24) S.Kobayashi, Y.Yoshino, S. Tsuji, M. Sera and F. Iga: J. Phys. Soc. Jpn. 72 (2003) 25.
- 25) Y. Yoshino, S. Kobayashi, S. Tsuji, H. Tou, M. Sera, F. Iga, Y. Zenitani and J. Akimitsu: J. Phys. Soc. Jpn. 73 (2004) 29.
- 26) P. Burlet, J. M. Effantin, J. Rossat-Mignod, S. Kunii and T. Kasuya: J. Phys. (Paris) C 8 (1988) 459.
- 27) S. Kobayashi, M. Sera, M. Hiroi, T. Nishizaki, N. Kobayashi and S. Kunii: J. Phys. Soc. Jpn. 70 (2001) 1721.
- 28) C. M. McCarthy and C. W. Thompson: J. Chem. Solid. 41 (1980) 1319.

- 29) S. Awaji, N. Kobayashi, S. Sakatsume, S. Kunii and M. Sera: J. Phys. Soc. Jpn. 68 (1999) 2518.
- 30) F. Iga, N. Shimizu and T. Takabatake: J. Magn. Magn. Mater. 177-181 (1998) 337.
- 31) R. B. Roberts: Philos. Mag. 36 (1977) 91.
- 32) D. Jaccard and J. Flouquet: J. Magn. Magn. Mater. 47&48 (1985) 45.
- 33) Y. Peysson, C. Ayache, B. Salce, S. Kunii and T. Kasuya: J.

Magn. Magn. Mater. 59 (1986) 33.

- 34) C. Marcenat, J. Jaccard, J. Sierro, J. Flouquet, Y. Onuki and T. Komatsubahara: J. Low Temp. Phys. 78 (1990) 261.
- 35) H. J. Ernst, H. Grühl, T. Krug and K. Winzer: Proc.17th Int. Conf. Low-Temperature Physics, eds. by U. Eckern, A. Schmid, W. Weber and H. Wühl (North-Holland, Amsterdam, 1984), p. 137.