β -NMR of Isolated ⁸Li⁺ Implanted into a Thin Copper Film

Z. Salman,^{1,*} A.I Mansour,² K.H. Chow,^{2,†} M. Beaudoin,³ I. Fan,² J. Jung,² T.A. Keeler,⁴

R.F. Kiefl,^{1,4,5} C.D.P. Levy,¹ R.C. Ma,² G.D. Morris,¹ T.J. Parolin,⁶ D. Wang,⁴ and W.A. MacFarlane⁶

¹TRIUMF, 4004 Wesbrook Mall, Vancouver, BC, V6T 2A3, Canada

²Department of Physics, University of Alberta, Edmonton, Canada T6G 2G7

³Advanced Materials and Process Engineering Lab, UBC, Vancouver, BC, V6T 1Z4, Canada

⁴Department of Physics and Astronomy, University of British Columbia, Vancouver, BC, V6T 1Z1, Canada

 $^{5}Canadian$ Institute for Advanced Research

⁶Department of Chemistry, University of British Columbia, Vancouver, BC, V6T 123, Canada

(Dated: January 26, 2020)

Depth-controlled β -NMR was used to study highly spin-polarized ⁸Li⁺ in a Cu film of thickness 100 nm deposited onto a MgO substrate. The positive Knight Shifts and spin relaxation data show that ⁸Li⁺ occupies two sites at low temperatures, assigned to be the substitutional (S) and octahedral (O) interstitial sites. Between 50 to 100 K, there is a site change from O to S. The temperature dependence of the Knight shifts and spin-lattice relaxation rates at high temperatures, i.e. when all the Li are in the S site, is consistent with the Korringa Law for a simple metal.

PACS numbers: 76.60.-k,61.72.Ww,74.25.Ha,74.62.Dh

Nuclear magnetic resonance (NMR) is a powerful tool for investigating the microscopic magnetic behavior in solid state systems. However, conventional NMR is often not sensitive enough to investigate thin film structures and generally cannot be used to study thick conducting samples. Recently, a high field, beta-detected ⁸Li⁺ nuclear magnetic resonance (β -NMR) spectrometer with depth control was developed at TRIUMF in Vancouver. Canada. This novel instrument utilizes ⁸Li⁺ (spin 2, lifetime 1.21 s) as the radioactive nuclear spin probe and provides enough sensitivity to allow NMR studies of thin metal structures to be carried out[1]. These measurements are aimed at better characterizing the behavior of ⁸Li⁺ as a prototypical impurity in metals and to enable investigations of finite-size effects in these materials. Furthermore, they establish the basis for future studies of other systems consisting of metal layers such as magnetic multilayers [2].

Using the TRIUMF β -NMR spectrometer, we recently carried out a detailed high field, depth resolved, ⁸Li⁺ β -NMR study of a 50 nm Ag film[1]. Two β -NMR resonances were observed at low temperatures which had Knight Shifts of +120(12) ppm and +212(15) ppm, implying that ⁸Li⁺ sits in two different high symmetry sites in the FCC lattice. Although these shifts are small, the ability to apply high magnetic fields allowed the two signals to be easily resolved at all temperatures. Above ≈ 100 K, the ⁸Li⁺ makes a transition from the 212 ppm site to the 120 ppm site, suggesting that the the 212 ppm signal is due to ${}^{8}\text{Li}^{+}$ residing in the octahedral (O) site and the 120 ppm signal is due to ${}^{8}\text{Li}^{+}$ in the substitutional (S) site. The site assignments were based on comparing the temperature dependence of the S and Osignals with other β -NMR[3] and channeling[4] experiments in similar systems. For example, for ¹²B in Cu, β -NMR cross-relaxation measurements clearly show that

boron occupies the O site at low temperatures, but moves to the S site at high temperatures [5]. The temperature dependences of the Knight Shifts and spin-lattice relaxation rates (i.e. $1/T_1$) were consistent with the Korringa Law, implying that the ⁸Li⁺ senses a free-electron like local electronic susceptibility in the thin Ag film.

Will similar behavior be observed for ⁸Li⁺ implanted into thin films of other "simple" FCC elemental metals such as Cu? In this paper, we experimentally investigate if such expectations are valid by carrying out β -NMR studies of isolated ⁸Li⁺ in a thin Cu film. In addition, since the host atoms in Cu have nuclear spin 3/2 and a relatively large quadrupole moment, this study lays down groundwork for the development of general techniques that can provide information on the local structure of the ⁸Li⁺ site in thin films and near interfaces, such as "cross-relaxation" [5, 6, 7]. We find that similar to Ag[1] and (a preliminary study in) Au[8], ⁸Li⁺ occupies two sites in Cu at low temperatures with Knight Shifts of +120(3) and +182(3) ppm, attributed to the S and O sites respectively. A transition from the 182 ppm site to the 120 ppm site occurs between 50 and 150 K. The spin lattice relaxation rate at high temperatures follows a Korringa law as expected for a simple metal. These measurements will provide a useful reference for future β -NMR and β -NQR experiments on samples that use Cu as a thin capping layer, a substrate, or as part of a multilayered structure.

In the NMR of metals, an important experimental quantity is the relative shift δ of the resonance frequency ν with respect to the Larmor frequency ν_0 of the nucleus in an external magnetic field H_0 , i.e. $\delta = (\nu - \nu_0)/\nu_0$. In many "simple" metals, δ is the Knight shift (K); it is independent of temperature and is a consequence of the Fermi contact interaction of the nuclear spin with the weak Pauli spin paramagnetism of the conduction

electrons[9]. A second important experimental quantity is the spin-lattice relaxation rate $1/T_1$ of the nucleus. Under the aforementioned conditions where the contact hyperfine interaction dominates, the random spin-flip scattering of the conduction electrons from the nucleus leads to a linear temperature dependence of the $1/T_1$ rate, and hence a product T_1T that is independent of temperature. Furthermore, the so-called Korringa Law is satisfied: $(T_1TK^2)/X = 1$ where $X = (\gamma_e/\gamma_n)^2(h/8\pi^2k_B)$, with γ_e and γ_n denoting the gyromagnetic ratios of the electron and nucleus respectively. In the case of ⁸Li⁺, the nuclear probe that is of relevance in this paper, $\gamma_n = {}^8 \gamma = 6.3015$ MHz/T, and hence $X = 1.2022 \times 10^{-5}$ s·K.

Our current β -NMR studies are on a Cu film of thickness 100 nm grown via thermal evaporation at a rate of 0.7 nm/s from a 99.999% purity Cu source in a pressure of 10^{-7} Torr onto a MgO substrate. A low energy (30.6 keV) beam of highly polarized ⁸Li⁺ is produced at the Isotope Separator and Accelerator (ISAC) facility at TRIUMF and implanted into the sample^[1, 10, 11]. A large nuclear polarization ($\approx 70\%$) of the ⁸Li⁺ is generated in-flight using a collinear optical pumping method. The β -NMR spectrometer resides on a high voltage platform which allows the implantation energy of the ⁸Li⁺ to be varied between 1 - 30 keV when a suitable positive bias is applied to the platform. These implantation energies correspond to an average depth from 3 to 100 nm. as calculated using TRIM.SP[12]. In β -NMR the nuclear polarization, i.e. the quantity of interest, is monitored by detecting the β s that are emitted preferentially opposite to the direction of the ⁸Li⁺ polarization at the time of decay (i.e. parity violation). The emitted betas are detected using plastic scintillation counters forward and backward to the initial ⁸Li⁺ polarization. The experimentally observed asymmetry A(t) of the β countrates is proportional to the ⁸Li⁺ nuclear spin polarization. In our experiment, we are interested in measuring the magnetic resonance signal and the spin-lattice relaxation rate $1/T_1$: (1) The magnetic resonance is detected by monitoring the *time-averaged* nuclear polarization as a function of the frequency ν of a small perpendicular radiofrequency (RF) magnetic field ($\sim 10^{-4}$ T). The resonance condition is satisfied when ν is equal to the Larmor frequency of ⁸Li⁺ in the internal field. On resonance, there is a reduction in the nuclear spin polarization; hence, A(t) and consequentially $A(\nu) = \langle A(t) \rangle$ decreases. (2) The spinlattice relaxation rate $1/T_1$ is measured with the RF off. The beam is admitted for 0.5 s every 15 s, and the evolution of the asymmetry A(t) is measured. Recall that $1/T_1$ is the rate at which the asymmetry relaxes from its initial value at t = 0 to its equilibrium value (i.e. zero polarization).

First, we discuss the resonance data. By implanting at the full energy (30.6 keV), a significant fraction of the ${}^{8}\text{Li}^{+}$ stops in the cubic insulator MgO, providing an *in*-



FIG. 1: (color online) Representative resonance signals of ${}^{8}\text{Li}^{+}$ in the Cu/MgO sample in an applied field of 4.1 T. Each spectrum was obtained at an implantation energy of 10.6 keV, except the bottommost one, which was obtained at the full implantation energy of 30.6 keV. The three vertical dashed lines indicate the peak frequencies of the MgO, S and O signals. The zero shift in frequency is taken to be that in MgO at room temperature. The long-dashed lines indicate the S and O contributions of the signal at each temperature.

situ reference of its Larmor frequency in the applied field ν_{MaO} (see Fig. 1). This is true because the Knight shift of the ⁸Li⁺ in an insulator should be zero, and we also expect the chemical shift to be small[13]. In Fig. 1, the zero frequency shift corresponds to $\nu_{MqO} = 25.83994(5)$ MHz. Then, at each temperature, the implantation energy is reduced to 10.6 keV, a value chosen so that all of the ⁸Li⁺ stops in the Cu film; representative spectra at a number of temperatures in an applied field of 4.1 T are shown in Fig. 1. The following qualitative features are apparent: At all temperatures, resonances are observed that are positively shifted from zero, demonstrating that we are able to detect the Knight Shifts due to ⁸Li⁺ in the thin Cu film. At low temperatures, the lineshape is noticeably asymmetric. In order to better understand the origin of this asymmetry, we examined the shapes of the signal with the ⁸Li⁺ forward and backward polarized, i.e. with ⁸Li⁺ initially (primarily) in the m = +2 and m = -2 state (in our instrument, this can be done by changing the sense of rotation of the circularly polarized pumping light). We find that the lineshape is skewed towards higher frequencies in both situations. This establishes that the asymmetric lineshape is not due to unresolved quadrupole effects since the existence of such interactions would result in a skewness towards high frequencies in one instance and a skewness towards lower



FIG. 2: (color online) Temperature dependences of the normalized amplitudes for an applied field of 4.1 T.

frequencies in the other instance[14]. Hence, these measurements rule out a model where the resonance is due to ${}^{8}\text{Li}^{+}$ stopping in a single non-cubic site since such a center should experience a significant quadrupole interaction. Therefore, the asymmetric line at low temperatures indicates that ${}^{8}\text{Li}^{+}$ occupies two inequivalent cubic sites, and each site is characterized by a different positive Knight shift. However, the shifts are not large enough to be clearly resolved. As the temperature is raised, the line becomes more symmetric and the peak frequency shifts to lower values. This indicates that a change in site has occured.

The resonance signals at all temperatures can be fit to a sum of two Gaussians:

$$A(\nu) = A_b + \frac{A_S}{W_S \sqrt{\frac{\pi}{2}}} \exp\left[-2\frac{(\nu - \nu_S)^2}{W_S^2}\right] + \frac{A_O}{W_O \sqrt{\frac{\pi}{2}}} \exp\left[-2\frac{(\nu - \nu_O)^2}{W_O^2}\right], \quad (1)$$

where W_S and W_O are the widths and ν_S and ν_O are the peak frequencies. These four parameters are assumed to be the same at all temperatures. The remaining parameters A_b (baseline term), A_S , and A_O were allowed to vary with temperature. In anticipation of our assignment of the sites, discussed below, the subscripts S and O are used to denote the substitutional and octahedral sites respectively. The fitted widths are $W_S = 3.205 \pm 0.006$ kHz and $W_O = 4.33 \pm 0.02$ kHz (the error estimates are entirely statistical^[15]). The Knight Shifts[16] can be obtained from the fitted values of ν_S and ν_O , as well as ν_{MqO} , to be $K_S = +120 \pm 3$ ppm and $K_O = +182 \pm 3$ ppm. These values are indicated as vertical dashed lines in Fig. 1. The normalized amplitudes are shown in Fig. 2, demonstrating that, as the temperature is increased, there is a thermally activated transition from the O to the S site. Note that the amplitudes do not add up to unity. Possible explanations include : (i) insufficient RF power to saturate the S and O lines and (ii) the existence of very broad lines due to

⁸Li⁺ stopping in sites of non-cubic symmetry, and would hence have significant quadrupolar interaction.

Our results for ⁸Li⁺ in Cu are similar to that obtained in the Ag film studied recently[1]. For example, the measured low temperature Knight Shifts in Cu are similar to those in the Ag film [1] of 120 ppm and 212 ppm. There, the sites were attributed to ⁸Li⁺ located in the substitutional (S) and octahedral (O) sites respectively. As discussed in the introduction, such an assignment was made by comparing the data with the "typical" temperature dependence seen for light radioactive impurities in metals, and for ${}^{12}B$ in Cu in particular[5]. By analogy, in Cu, we make an assignment of the 120 ppm signal to the S site and the 182 ppm signal to the O site. As Fig. 2 indicates, ⁸Li⁺ makes a transition from the 182 ppm site to the 120 ppm site between ≈ 50 to 100 K. This is likely a consequence of a thermally activated transition of the interstitial ⁸Li⁺ to a nearby vacancy created during the implantation process. It is worthwhile pointing out that Ohsumi *et al.* [17] also assigned their high temperature site to the S site after considering the β -NMR linewidths of ${}^{8}\text{Li}^{+}$ in a single crystal of Cu[17]. However, some of their conclusions are different from ours. They propose that $\approx 30\%$ of the ⁸Li⁺ stops in an O site. In addition, they were not able to detect any changes from 11 K to 300 K that could be attributed to a site change. The reasons for the discrepancies with our observations are not clear, but could partly be due to the fact that their studies were conducted at significantly lower applied field, and hence are even less able to resolve two closely spaced lines. It would require the development of powerful spectroscopic techniques such as cross-relaxation to unambiguously establish the location of ${}^{8}\text{Li}^{+}$ at all temperatures.

The linewidths of the ⁸Li⁺ resonance signals in Cu are significantly larger than those in Ag[1]. The dominant broadening mechanism of the β -NMR signals is from the dipolar broadening by the host spins[18]. Hence, the larger linewidths in Cu compared to Ag are expected since the nuclear moments of the Cu host atoms are about an order of magnitude greater than those of Ag[19]. Furthermore, the lattice constant of Cu (0.361 nm) is smaller than that of Ag (0.408 nm). The fitted linewidths to Eq. 1 imply that the second moments of the lines are 3.08 kHz^2 and 5.63 kHz^2 for the S and the O sites respectively. The former is comparable to the prediction of 1.44 kHz^2 for ⁸Li⁺ in an undistorted S site[17]. The extra broadening may be partly due to the higher RF power used[20] here compared to Ref. 17 (~ 3 times higher).

We now discuss the spin relaxation data of ⁸Li⁺ in the Cu film. The inset in Fig. 3 shows examples of the asymmetry A(t); it is phenomenologically well-described at all temperatures by a single exponential relaxation function with decay rate $1/T_1$. The temperature dependence of the $1/T_1$ rates are shown in Fig. 3, and are obtained in applied magnetic fields of 4.1 T and 6.5 T. The $1/T_1$ values are the same at these two fields, as expected if



FIG. 3: (color online) The temperature dependence of $1/T_1$ at 4.1 T (black circles) and 6.55 T (red stars). The straight line is a best fit to the data above 100 K through the origin while the dashed line is the calculated effective relaxation rate (see text).

the dominant relaxation mechanism at these fields is Korringa relaxation. The resonance data described above have shown that at high temperatures (above ≈ 100 K), all the ⁸Li⁺ are in the S site; here, the $1/T_1$ rates are due to the S site only. They are linear with temperature, and are described by $(T_1T)^{-1} = (1.059 \pm 0.026) \times 10^{-3}$ $s^{-1} \cdot K^{-1}$. By combining this value with the experimentally determined K_S of +120 ppm we obtain a Korringa ratio of $T_1TK^2/X = 1.13 \pm 0.05$, close to the value of unity expected from the Korringa law. This agreement implies that ⁸Li⁺ senses a local susceptibility that is freeelectron like. Note that at low temperatures, there is significant occupation of both the S and O sites and the effective $1/T_1$ rates consist of contributions from ⁸Li⁺ in both these locations. For comparison, the dashed line in Fig. 3 shows the calculated effective rates obtained by using the resonance amplitudes from Fig. 2, the relaxation rates of the S site at high temperatures, and the Knight shifts of the S and O sites. The calculations are in reasonable agreement with the measured results. The deviation at low temperature is most probably due to an additional site with a broad line that was not observed in our resonance measurements, but contributes to A(t).

By comparison, Ohsumi *et al.*[17] have reported the $(T_1T)^{-1}$ values for ⁸Li⁺ in Cu at 20 K, 100 K, and 280 K. They found that this quantity is nearly independent of temperature with an average value of $(2.4 \pm 0.1) \times 10^{-3}$ s⁻¹·K⁻¹. They did not report a value for the Korringa ratio since measurements of the Knight Shifts were not carried out. Our value of the Korringa ratio of 1.13 ± 0.05 is somewhat smaller than that of ^{63,65}Cu in Cu of 1.9 [21].

We briefly point out that our preliminary studies in a Cu crystal have shown that $1/T_1$ is independent of the magnetic field above ≈ 0.07 T, but is highly field dependent below this value. For example, at 200 K, the phenomelogical $1/T_1$ rates change from the constant value at

We thank R. Abasalti, B. Hitti, S.R. Kreitzman, and D. Arseneau for technical assistance and NSERC for support. A. MacDonald collected and fitted some data.

- * Current address: Clarendon Laboratory, Department of Physics, Oxford University, Parks Road, Oxford OX1 3PU, UK
- [†] Electronic address: kimchow@phys.ualberta.ca
- [1] G.D. Morris *et al.*, Phys. Rev. Lett. **93**, 157601 (2004).
- [2] T. A. Keeler et al., Physica B 374-375C, 79 (2006).
- [3] H. Ackermann et al. in Hyperfine Interactions of Radioactive Nuclei edited by J. Christiansen, Topics in Current Physics Vol. 31 (Springer, Berlin, 1983), p. 291.
- [4] H. Hoffsass and G. Lindner, Phys. Rep. 201, 121 (1991).
- [5] B. Ittermann et al., Phys. Rev. Lett. 77, 4784 (1996).
- [6] M. Füllgrabe *et al.*, Phys. Rev. B 64, 224302 (2001), and references therein.
- [7] K.H. Chow, B. Hitti, R.F. Kiefl, in *Identification of Defects in Semiconductors*, edited by M. Stavola, Semiconductors and Semimetals vol. 51A (Academic Press, New York, 1998), p. 137; B.E. Schultz *et al.*, Phys. Rev. B **72**, 33201 (2005); B.E. Schultz *et al.*, Phys. Rev. Lett. **95**, 86404 (2005); K.H. Chow *et al.*, Phys. Rev. Lett. **87**, 216403 (2001); K.H. Chow *et al.*, Phys. Rev. B **51**, 14762 (1995).
- [8] W.A. MacFarlane et al., Physica B 326, 213 (2003).
- [9] C. P. Slichter, *Principles of Magnetic Resonance*, 3rd ed. (Springer, Berlin, 1990).
- [10] R.F. Kiefl *et al.*, Physica B **326**, 189 (2003).
- [11] Z. Salman *et al.*, Phys. Rev. B **70**, 104404 (2004); Z. Salman *et al.*, Phys. Rev. Lett. **96**, 147601 (2006).
- [12] W. Eckstein, Computer Simulation of Ion-Solid Interactions (Springer, Berlin, 1991).
- [13] e.g. C.P. Grey and N. Duprè, Chem. Rev. **104**, 4493 (2004); Z. Xu and J.F. Stebbins, Sol. St. Nucl. Mag. Reson. **5**, 103 (1995).
- [14] e.g. see W.A. MacFarlane *et al.*, Physica B **326**, 209 (2003).
- [15] The correlation coefficients between the different parameters are low, e.g. -0.0042 and -0.32746 between the centers and the widths of the resonances, respectively. This indicates the model used is not overparameterized.
- [16] The assumption that ν_S and ν_O are independent of temperature ignores the influence of lattice contraction on the Knight Shifts. From analogy with ⁸Li⁺ in Ag[1], we believe this will be a small effect.
- [17] F. Ohsumi et al., Hyp. Interact. 121, 419 (1999).
- [18] J.H. van Vleck, Phys. Rev. **74**, 1168 (1948).
- [19] Cu has two isotopes with a nuclear spin I = 3/2: ⁶³Cu (abundance 69.2%) and ⁶⁵Cu (abundance 30.8%) with

gyromagnetic ratios 11.33 MHz/T and 12.10 MHz/T respectively. By contrast, Ag has two isotopes with a nuclear spin I = 1/2: ¹⁰⁷Ag (abundance 51.8%) and ¹⁰⁹Ag (abundance 48.2%) with gyromagnetic ratios -0.173 MHz/T and -0.1992 MHz/T respectively.

- [20] A. Abragam, The Principles of Magnetic Resonance (Oxford University Press, 1961) p. 45.
- [21] G.C. Carter, L.H. Bennett, and D.J. Kahan, *Metallic Shifts in NMR* (Pergamon, Oxford, 1977).
- [22] A.G. Anderson and A.G. Redfield, Phys. Rev. 59, 583 (1959).
- [23] R.S. Hayano *et al.*, Phys. Rev. B **20**, 850 (1979).