Topological Order in the Vortex Glass Phase of High-Temperature Superconductors

Jan Kierfeld^(1,2), Thomas Nattermann⁽¹⁾, and Terence Hwa⁽²⁾

⁽¹⁾ Institut für Theoretische Physik der

 Universität zu Köln, D-50937 Köln, Germany
 ⁽²⁾ Department of Physics, University of California at San Diego, La Jolla, CA 92093-0319

(Received: December 11, 1995)

The stability of a vortex glass phase with quasi-long-range positional order is examined for a disordered layered superconductor. The role of topological defects is investigated using a detailed scaling argument, supplemented by a variational calculation. The results indicate that topological order is preserved for a *wide range* of parameters in the vortex glass phase. The extent of the stability regime is given in terms of a simple Lindemann-like criterion.

PACS numbers: 74.60.Ge, 05.20.-y

It is well-known that the Abrikosov flux lattice in a type-II superconductor is unstable to point disorder beyond the Larkin length [1]. The nature of the flux array at larger scales has been a subject of intense studies [2]. It has been conjectured that the flux array is collectively pinned, forming a vortex glass (VG) phase [3–6] with zero linear resistivity at low temperatures. This conjecture is supported by a number of experiments on disordered samples of high- T_c superconductors [7–10], where a continuous transition to a phase with zero linear resistivity was found upon cooling. On the other hand, Bitter-decoration [11], neutron scattering [12], and μ SR [13] experiments on weakly-disordered samples have all indicated some *long-range order* of the flux array, a characteristic usually incompatible with a glass. A common interpretation for the observation of a flux *lattice* is a crossover effect due to the large Larkin lengths in weakly disordered samples. In this article, we investigate a different possibility, that the flux array may maintain its positional long-range order much beyond the Larkin length, in spite of pinning by point disorders.

Such a possibility is indeed realized in a model of *dislocation-free* flux line array in random media [5,14]. This model is very similar to the randomly-pinned charge-density waves and the random-field XY model which have been studied extensively in the past decades [14–17]. A variety of approximate methods have been used to obtain the conclusion that point disorders lead to a glass phase with only logarithmic fluctuations in the transverse displacement of the flux array. This implies the existence of quasi-long-range positional order in the glass phase of the dislocation-free flux array [14].

Recently, Giamarchi and LeDoussal suggested [14,18] that such a topologically-ordered glass may actually exist as a *stable* thermodynamic phase for some range of parameters in the cuprate superconductors. A related numerical study of the random field-XY model by Gingras and Huse [19] further supported this scenario. However, the issue of spontaneous formation of topological defects (i.e., dislocation loops) involves complicated interplay between elasticity and disorders, and has so far not been addressed *quantitatively*. In this article, we investigate this issue by studying a model of flux lines confined in the planes of a layered superconductor [Fig. 1]. Our model allows for the formation of dislocation loops and is amenable to analytic studies. We first present a detailed scaling argument, which yields suppression of large dislocation loops at finite fugacities. This result is then supplemented by a variational calculation, from which we obtain a Lindemann-like criterion giving the size of the stability regime for the topologically-ordered VG. Similar behaviors are expected in the usual experimental situation of flux lines perpendicular to the layers.



FIG 1: Flux line array in a layered superconductor in a parallel magnetic field.

We consider a strongly layered impure superconductor in a parallel magnetic field [see Fig. 1]. The superconducting layers provide a sufficiently strong confining potential for the (Josephson-like) vortex lines which exist in the interlayer spacing. We shall exclude the possibility of the lines crossing the superconducting layers. [For fields parallel to the ab-planes of the Bi-compound, typical vortex kink energies are of the order $10^3(1-T/T_c)^{\circ} K$.] This amounts to limiting the vortex displacement field from two components in an isotropic sample to one component (i.e., parallel to the layers). For simplicity we focus our study mostly on the *dilute* limit where the inter-vortex spacings l_{\perp} (inter-layer), l_{\parallel} (intra-layer) exceed the magnetic penetration depths λ_{ab} , λ_c respectively. The implications of our results on the dense limit are straightforward and will be discussed below.

A well-established analytic description for a *single* layer of vortex lines (for length scales exceeding l_{\parallel}) is given by the Hamiltonian [3]

$$\beta \mathcal{H}_{2\mathrm{D}}[\phi_j, W_j] = \int_{\mathbf{r}_{\parallel}} \left\{ \frac{K}{2} (\nabla_{\parallel} \phi_j)^2 - W_j[\phi_j(\mathbf{r}_{\parallel}), \mathbf{r}_{\parallel}] \right\},$$
(1)

where $\phi_j(\mathbf{r}_{\parallel})$ describes the in-plane displacement of the vortex lines in the j^{th} layer and K is an (isotropized) inplane elastic constant. Pinning effects due to point disorder are described by the random potential $W_j[\phi_j(\mathbf{r}_{\parallel}), \mathbf{r}_{\parallel}]$, with the second moment

$$\overline{W_j[\phi_j, \mathbf{r}_{\parallel}]W_j[\phi'_j, \mathbf{r}'_{\parallel}]} = g_0^2 \cos[\phi - \phi']\delta^2(\mathbf{r}_{\parallel} - \mathbf{r}'_{\parallel}), \quad (2)$$

where the overbar denotes disorder average, g_0 characterizes the (bare) strength of the random potentials, and the cosine captures the *discrete* nature of the vortex lines [5]. With many layers stacked next to each other, the Hamiltonian for the whole system is

$$\beta \mathcal{H} = \sum_{j} \left\{ \beta \mathcal{H}_{2\mathrm{D}} + \int_{\mathbf{r}_{\parallel}} V_{j} [\phi_{j+1}(\mathbf{r}_{\parallel}) - \phi_{j}(\mathbf{r}_{\parallel})] \right\}, \quad (3)$$

where $\overline{W_j W_{j'}} = \delta_{j,j'} \overline{W_j W_j}$ since the bare random potentials in different layers are uncorrelated, and the interaction has the form

$$V_j[\phi] = -\mu \cos[\phi]. \tag{4}$$

The expression (4) can be regarded as the repulsive magnetic interaction energy between the lowest harmonics of density fluctuations between vortex lines in "adjacent" layers, a valid approximation in the dilute limit [20]. The coupling constant μ is related to the shear modulus of the flux line lattice. The main feature of (4) is that it goes beyond the elastic approximation, as it allows for dislocation loops between adjacent layers [see Fig. 2].



FIG 2: Elastic rearrangement of each planar flux array can be represented by a number of vortex *loops*. An example is shown on the left (shaded region). Aligned vortex loops in successive layers form a vortex *sheet* as shown on the right. The boundary of the sheet (dark loop on top) is a *dislocation loop*.

In what follows, we first study the phase diagram of the system in terms of the parameters μ and K. If the vortex layers are uncoupled, i.e., $\mu = 0$, then each layer undergoes separately a glass transition at a critical value $K_c = 1/4\pi$ [3,16], with a vanishing linear resistivity in the low temperature phase $(K > K_c)$ and ohmic behavior in the high temperature phase $(K < K_c)$ [21,22]. The physical range of interest corresponds to $K \gg K_c$. When coupling the layers together via Eq. (4), a competition arises between the tendency of vortex lines in each layer to lower their free energy by adapting to the disorder in their own layer, against the tendency to minimize the interlayer coupling by bringing neighboring vortex layers into registry. The limit of very weak coupling ($\mu \ll 1$) may be studied using perturbation theory; it is straightforward to find that weak coupling is irrelevant at large scales.

In the limit of very large coupling $\mu \to \infty$, the interaction potential $V[\phi]$ may be replaced by the quadratic form, $\frac{\mu}{2}\phi^2$, which describes an elastic (i.e., dislocationfree) coupling in the direction perpendicular to the layers. This is just the anisotropic (and one-component) version of the VG considered previously in Refs. [5,14,15]. After introducing a continuum description in terms of $\mathbf{r} = (\mathbf{r}_{\parallel}, r_{\perp})$ and rescaling $r_{\perp} = (j \cdot l_{\perp}) \sqrt{\mu l_{\perp}^2/K}$, we get an isotropic 3D *elastic* Hamiltonian

$$\beta \mathcal{H}_{3\mathrm{D}} = \int d^3 \mathbf{r} \left\{ \frac{\gamma}{2} (\nabla \phi)^2 - W[\phi(\mathbf{r}), \mathbf{r}] \right\}$$
(5)

with an effective elastic constant $\gamma = \sqrt{\mu K}$ and a random potential $W[\phi(\mathbf{r}), \mathbf{r}]$ with $\overline{W[\phi, \mathbf{r}]}W[0, 0] = g^2 \cos[\phi]\delta^3(\mathbf{r})$, where $g^2 = g_0^2 \sqrt{\mu/K}$. From various methods including position-space RG [15], functional RG [14], and the variational Ansatz with replica-symmetry breaking [14,17], one finds that the system (5) forms a glass phase with

$$\overline{\langle [\phi(\mathbf{r}) - \phi(\mathbf{r}')]^2 \rangle}_{3\mathrm{D}} = 2A \log \left(|\mathbf{r} - \mathbf{r}'|/\ell \right) \tag{6}$$

beyond the positional correlation length $\ell \sim \gamma^2/g^2$, with A being a universal number of O(1). [In this model, ℓ is equivalent to the Larkin length, although in more realistic models including higher harmonics of density fluctuations, ℓ exceeds the Larkin length [23].]The logarithmic fluctuation in displacement leads to quasi-long-range order and an (algebraic) Bragg peak at reciprocal lattice vector $2\pi/l_{\parallel}$. This phase has since been referred to as the "Bragg glass" [14]. In 3D, there is a large elastic energy cost, of the order $(\gamma/2) \int d^3 \mathbf{r} \langle (\nabla \phi)^2 \rangle_{3D} \sim \gamma L$, for logarithmic fluctuations in a volume of the order L^3 . This energy is compensated by the disorder energy gained from the anomalous displacement of the flux array. Thus

$$\Delta E \sim \gamma L \tag{7}$$

gives the sample-to-sample free energy fluctuation of the Bragg glass. Also, due to the existence of a statistical symmetry [24,25], it is known that the disorder-averaged responses of the system to various elastic deformations are identical to those of the pure elastic system, i.e., Eq. (5) with W = 0. In particular, there is a non-zero response to shear.

Given the above properties of the Bragg glass, which exists so far only in the unphysical limit $\mu \to \infty$, our first task is to determine whether it can persist at a finite μ , i.e., whether the system is stable to the *spontaneous* formation of dislocation loops on length scales much larger than the correlation length. To investigate this possibility, we divide the system into two halves (within which the layers are elastically coupled), and allow dislocation loops to form in the contact plane, say between the j_0^{th} and $(j_0 + 1)^{\text{th}}$ layers. Analytically, this is implemented by using the following interaction energy in Eq. (3):

$$V'_{j}[\phi] = \frac{\mu}{2}\phi^{2} \quad \text{if} \quad j \neq j_{0}$$
$$= -\mu' \cos[\phi] \quad \text{if} \quad j = j_{0}, \tag{8}$$

where $\mu' \approx \mu$ approximates (4). It is instructive to consider arbitrary values of μ' . Let us compare the free energy difference between the completely coupled and completely decoupled limit. If the two halves of the system are decoupled, then each forms a Bragg glass, and the configuration of the flux array in each half is *individually* optimized. But if the two halves are tied together, then the constraint across the contact plane forces a global reoptimization of the flux array, resulting in a *higher* free energy for each half. The typical free energy increase due to the constraint is given by the sample-to-sample free energy fluctuation of the Bragg glass, $\Delta E \sim \gamma L$. The expression (7) is used here because each half of the system must be *completely* re-optimized given the constraint, as if the configuration of the random potential has been completely changed. The difference in the optimal configuration of the flux array in each half resulting from the constraint at j_0 can be described by a collection of "vortex sheets" such as the one depicted in Fig. 2. The boundary of a vortex sheet is a dislocation loop; it describes phase mismatches across the contact plane.

To find whether or not the two half systems actually couple for a given μ' , it is necessary to balance the cost in disorder energy due to coupling with the *reduction* in interaction energy due to phase matching. The latter can be readily computed for small μ' using (6). One finds $\mu' \int_{L^2} d^2 \mathbf{r}_{\parallel} \overline{\langle \cos[\phi_{j_0+1} - \phi_{j_0}] \rangle_{3D}} \sim \mu' \ell^A L^{2-A} \lesssim L$ since $A \geq 1$ [14]. As the disorder energy cost to coupling, $\Delta E \sim \gamma L$, exceeds the interaction energy to be gained at small μ' and large L, the two half systems will remain decoupled. In the large (but finite) μ' limit of interest, the perturbative result is no longer valid. Since the energy cost of phase mismatch is large there, we consider the stability of a *single* optimally-configured dislocation loop of extent $L \gg \ell$ at the contact plane of the two half systems that are otherwise elastically coupled [Fig. 2]. The energy cost of the core of the dislocation loop due to the inter-layer interaction is extensive. For a stretched circular loop of linear size L, we expect $E_{\rm core} \sim \mu' \ell L$. Here, ℓ appears as the "thickness" of the loop because the flux array is elastically coupled at smaller scales at low temperatures [26]. More generally, if we allow the dislocation loop to take on fractal shapes, say with the total loop length scaling as L^D for $L \gg \ell$ (D > 1 being the fractal dimension), then the core energy becomes $E_{\rm core} \sim \mu' \ell^{2-D} L^D$. On the other hand, the disorder energy *qained* from the formation of a dislocation loop of size L is just the energy gained from the formation of a vortex sheet $E_{sheet}(L)$, resulting from the *elastic* deformation of the half-system [see Fig. 2]. $E_{sheet}(L)$ clearly cannot exceed $\Delta E(L)$ which is the disorder energy gained from *complete* optimal elastic rearrangement of the half-system at scale L. Assuming scaling of vortex sheet energies, $E_{sheet}(L) \sim \gamma' L^{\omega}$, it follows that $\omega \leq 1$.

The actual value of the exponent ω depends on the structure of the dislocation loop we allow, i.e., on the fractal dimension D. We expect that the upper bound $(\omega = 1)$ may only be reached if the structure of the associated vortex sheet is similar to those occurring naturally in complete elastic rearrangement of the half system. The latter can be deduced as follows: Denote the difference in the configuration before/after rearrangement by $\varphi(\mathbf{r})$. The vortex sheets are then the equal- φ contours of $\varphi(\mathbf{r})$, and the associated dislocation loops are the contours of $\varphi(\mathbf{r}_{\parallel}, r_{\perp} = j_0 l_{\perp})$. The relationship between a rough "landscape" and the fractal geometry of its contours have recently been examined [27]. For a logarithmically-rough landscape φ [see Eq. (6)], an exact calculation yields D = 3/2 [27–29]. Thus, we expect $\omega \leq 1$ for D = 3/2, and $\omega < 1$ for D < 3/2. The total energy of the dislocation loop

$$E_{\text{loop}} = E_{\text{core}}(L) - E_{\text{sheet}}(L) \sim \mu' \ell^{2-D} L^D - \gamma' L^{\omega(D)}$$
(9)

does not admit a stable solution with $L \gg \ell$ for large $\mu' \approx \mu$. Hence the Bragg glass is stable to the spontaneous formation and proliferation of large dislocation loops. This conclusion is further supported by a systematic renormalization-group analysis, the details of which will be given elsewhere [30]. The possibility of a marginally stable Bragg glass for weakly-disorder sample was first suggested in Ref. [14], based on the assertions that $\Delta E \sim gL$ and $E_{\text{core}} \sim cL$, where g is the bare disorder strength which can be made arbitrary small and c is a

given number [26]. The above analysis indicates that the dislocation loops are much more *strongly suppressed* at low temperatures by the anomalously large core energy.

Next, we investigate the extent of the stability regime for the Bragg glass. As already shown, the Bragg glass cannot exist in the limit of very weak inter-layer coupling. We expect the maximum possible extent of the stability regime to be the point where the disorder is so strong that the correlation length ℓ becomes of the order of the average vortex spacing a. Beyond this point, a topologically-ordered flux array cannot even form at the smallest scale, and the entire collective pinning picture breaks down. To find the actual size of the stability regime for the layered system (3), we consider quasi two-dimensional in-plane fluctuations i.e., on the shortest scale in the direction perpendicular to the layers. Analytically, we apply a variational treatment, with the variational Hamiltonian obtained by replacing the interaction potential $V_j[\phi]$ in (3) by the quadratic form $\widetilde{V}_j[\phi] = \frac{\mu}{2}\phi^2$. \widetilde{V} describes an elastic (i.e., dislocation-free) coupling in the direction perpendicular to the layers. The parameter $\tilde{\mu}$ has the meaning of an effective shear modulus and may be determined self-consistently within the variational treatment. The minimization of the variational free energy with respect to $\tilde{\mu}$ yields the self-consistency equation

$$\widetilde{\mu} = \mu \overline{\langle \cos[\phi_{j+1}(\mathbf{r}_{\parallel}) - \phi_j(\mathbf{r}_{\parallel})] \rangle}_{\widetilde{\mathcal{H}}}.$$
(10)

This is evaluated using a Gaussian approximation which can be justified [30] in a controlled fashion and should be reasonably accurate. $\overline{\langle \phi \phi \rangle}_{\widetilde{\mathcal{H}}}$ contains contributions from (i) the quasi 2D VG regime $\overline{\langle \phi \phi \rangle}_{2D}$ which dominates for $\tilde{\mu} \approx 0$; (ii) the 3D VG regime $\overline{\langle \phi \phi \rangle}_{3D}$; and (iii) thermal fluctuations on scales smaller than the correlation length ℓ for large $\tilde{\mu}$. Using Eq. (6) for $\overline{\langle \phi \phi \rangle}_{3D}$, and using $\overline{\langle \phi \phi \rangle}_{2D} = 2(1+\alpha) \log(L)$ (where $\alpha \approx (l_{\parallel}g_0/K)^4$ from Refs. [14,17]), the following results are obtained [31]: The self-consistency equation has a stable solution with nonzero shear modulus only for [32] $\mu > \mu_c = c^2 K/\ell^2$. For $\mu < \mu_c$, the system "melts" into a stack of decoupled 2D VG's, distinguished from the Bragg glass by a vanishing shear modulus $\tilde{\mu} = 0$ [33]. The transition at $\mu = \mu_c$ is first order, with a jump in $\tilde{\mu}$ [30]. Our variational calculation yields a prefactor $c \approx 5$ which depends very weakly on temperatures, as long as we are away from the melting temperature of the pure system [30].

It is illustrative to express μ and K in terms of the correlation length [of the anisotropic system (3)] in the \perp -direction, $\ell_{\perp} \equiv \sqrt{\mu l_{\perp}^2/K}\ell$. The above stability condition becomes

$$\ell_{\perp} > c \cdot l_{\perp}.\tag{11}$$

Thus, we find the Bragg glass to be very stable, reaching within a factor of 10 of the maximum extent of stability (i.e., $\ell \approx l$) beyond which the very concept of collective pinning breaks down! As variational calculations tend to under-estimate fluctuations, we expect the actual value of c to be somewhat larger. Nevertheless, the condition (11) appears to be quite general, and may be viewed as the disordered-analog of the Lindemann criterion.

Applying this Lindemann-like criterion, we can expect the following low-temperature behaviors for the usual experimental situation of flux lines perpendicular to the CuO planes; a detailed account including the relevance to recent experiments will be given elsewhere [30]. (a) In the dilute limit, the Bragg glass phase is stable if the transverse correlation length $\ell(B)$ exceeds (a few times) the inter-vortex spacing l(B). (b) The same conclusion is obtained in the dense limit $[\lambda \gg l]$ if $\ell \gtrsim \lambda$. (c) In the opposite limit of $l \lesssim \ell \ll \lambda \to \infty$, the long-ranged magnetic interaction leads to a much stronger glass phase, with $\Delta E \sim L^2$ [14], if the dislocation loops are forbidden. This however provides a much larger disorder energy to be gained from the formation of dislocation loops [i.e.,Eq. (9) with $\omega = 2$], leading to the proliferation of large loops. This regime may belong to the universality class of the (long-ranged) Gauge glass [34], or it may simply be a viscous line liquid. (d) For the physical case of finite λ 's, dislocation loops can form at scales λ and below, and we expect the system to remain topologicallyordered at large scales.

In summary, we find strong evidence supporting the existence of a topologically-ordered vortex glass for the layered superconductors. The stability regime is surprisingly large and is given by a Lindemann-like criterion. Beyond this regime, the system is dominated by *strong disorders*, and its properties are not known. It may simply *melt* into a viscous line liquid, or it may form another type of glass phase [14].

We are grateful to many helpful discussions with D. S. Fisher, T. Giamarchi, J. Kondev, P. Le Doussal, D. R. Nelson, L. H. Tang, and I. Lyuksyutov. TH acknowledges the support of A.P. Sloan Foundation and an ONR Young Investigator Award through ONR-N00014-95-1-1002. TN acknowledges the hospitality of Harvard University where part of the work was done, as well as the financial support of the Volkswagen Foundation.

- [1] A.I. Larkin, Sov. Phys. JETP **31**, 784 (1970).
- [2] G. Blatter et al, Rev. Mod. Phys. 66, 1125 (1995).
- [3] M.P.A. Fisher, Phys. Rev. Lett. **62**, 1415 (1989).
- [4] M.V. Feigelman et al, Phys. Rev. Lett. 63, 2303 (1989).
- [5] T. Nattermann, Phys. Rev. Lett. 64, 2454 (1990); K.
 H. Fischer and T. Nattermann, Phys. Rev. B 43, 10372 (1991).

- [6] D.S. Fisher, M.P.A. Fisher and D.A. Huse, Phys. Rev. B 43, 130 (1991).
- [7] R. H. Koch *et al.*, Phys. Rev. Lett. **63**, 1511 (1989).
- [8] P. L. Gammel et al., Phys. Rev. Lett. 66, 953 (1991).
- [9] H. Safar et al., Phys. Rev. Lett. 68, 2672 (1992).
- [10] N.-C. Yeh et al., Phys. Rev. B 47, 6146 (1993); ibid. 6150 (1993); ibid. 8308 (1993); ibid. 49, 4384 (1994).
- [11] C. A. Murray et al., Phys. Rev. Lett. 64, 2312 (1990).
- [12] R. Cubitt et al., Nature 365, 407 (1993).
- [13] S. L. Lee *et al.*, Phys. Rev. Lett. **71**, 3862 (1993).
- [14] T. Giamarchi and P. Le Doussal, Phys. Rev. Lett. 72, 1530 (1994); Phys. Rev. B 52, 1242 (1995).
- [15] J. Villain and J.F. Fernandez, Z. Phys. B 54, 139 (1984).
- [16] J. L. Cardy and S. Ostlund, Phys. Rev. B 25, 6899 (1982).
- [17] S. E. Korshunov, Phys. Rev. B 48, 3969 (1993).
- [18] T. Giamarchi and P. Le Doussal, Phys. Rev. Lett. 75, 3372 (1995).
- [19] M. Gingras and D. A. Huse, preprint (1995).
- [20] L. V. Mikheev and E. B. Kolomeisky, Phys. Rev. B 43, 10431 (1991).
- [21] Y. Y. Goldschmidt and B. Schaub, Nucl. Phys. B251, 77 (1985).
- [22] Y. C. Tsai and Y. Shapir, Phys. Rev. Lett. 69, 1773 (1992).
- [23] We are grateful to T. Giamarchi and P. Le Doussal for pointing this out.
- [24] U. Schulz, J. Villain, E. Brezin, and H. Orland, J. Stat.

Phys. 51, 1 (1988).

- [25] T. Hwa and D. S. Fisher, Phys. Rev. Lett. 72, 2466 (1994).
- [26] The dependence of $E_{\rm core}$ on the Larkin length has since been independently recognized by the authors of Ref. [14]; (T. Giamarchi and P. Le Doussal, private communication).
- [27] J. Kondev and C. Henley, Phys. Rev. Lett. 74, 4580 (1995).
- [28] H. Saleur and B. Duplantier, Phys. Rev. Lett. 58, 2325 (1987).
- [29] The result D = 3/2 is actually obtained only for Gaussian-distributed φ 's. It is however believed to hold for a broad class of distributions; (J. Kondev, private communication).
- [30] J. Kierfeld and T. Hwa, (unpublished).
- [31] Qualitatively similar results are obtained using $\langle \phi \phi \rangle_{2D} \sim \log^2(L)$ as found in [16], provided that we are in the low temperature regime $K \gg K_c$.
- [32] The microscopic length scale which appears in the calculation is actually the 2D correlation length $\ell_{\rm 2D} = K/g_0$. However at $\mu = \mu_c$, $\ell_{\rm 2D} \sim \ell/\sqrt{c}$ [30].
- [33] The behaviors for $\mu \leq \mu_c$ are probably peculiar to the specific model (3) considered and are not the focus of this study.
- [34] D. A. Huse and H. S. Seung, Phys. Rev. B 42, 1059 (1990); J. D. Reger et al, ibid. 44, 7147 (1991); M. Gingras, *ibid.* 45, 7547 (1992).