Phase transition curves for mesoscopic superconducting samples

H.T. Jadallah, J. Rubinstein and P. Sternberg

Abstract. We compute the phase transition curves for mesoscopic superconductors. Special emphasis is given to the limiting shape of the curve when the magnetic flux is large. We derive an asymptotic formula for the ground state of the Schrödinger equation in the presence of large applied flux. The expansion is shown to be sensitive to the smoothness of the domain. The theoretical results are compared to recent experiments.

PACS numbers: 74.70, 74.72

In their classical experiment, Little and Parks [12] considered the transition between normal and superconducting phases in cylindrical shells. They discovered that the phase boundary in the T - H plane, where T is the temperature and H is the applied magnetic field, is oscillatory. When the thickness of the shell is very small relative to the coherence length, the period is approximately the fundamental flux quantum $\phi_o = h/e^*c$, where $e^* = 2e$ is the charge of the Cooper pair. Taking into account the effect of the finite thickness of the ring, it can be shown theoretically [10] and verified experimentally (e.g. [12],[13]) that the oscillations in the T - H line are superimposed on a parabolic background. The situation becomes more complex if the circular symmetry of the shell is broken [3], but the T - H line is still oscillatory.

The classical literature on the subject assumes that the superconducting sample is multiply connected, typically with a ring-like geometry. Nevertheless, an oscillatory T - H line is also obtained for simply connected domains. This has been shown experimentally by Buisson et al. [6] who considered a small disc. Later Moshchalkov et al. [13] and Bruyndoncx et al. [5] measured the transition temperature T as a function of the applied flux for a mesoscopic square. Both groups reported an oscillatory phase boundary superimposed on a linear background. The heuristic reasoning for the oscillations is that as the flux increases, the wave function concentrates near the boundary, and the sample appears effectively as a thin ring. This gives rise to a topological quantization constraint on the phase of the wave function and hence the Little Parks oscillations. The analogy with the experiments in thin shells is not perfect, though. In the case of a simply connected sample under strong fields, the radius of the 'effective' ring is not fixed. Rather it shrinks as the applied field increases.

We shall show here that the base T - H curve is parabolic for small fluxes, linear for large fluxes, and that its precise shape depends on the smoothness of the domain. We compute the T - H curve for arbitrary mesoscopic two dimensional samples Ω . A constant magnetic field of magnitude H is applied in the direction orthogonal to the plane. We pay particular attention to the asymptotic limit in which the flux is large. Near the phase transition, the induced magnetic field is negligible and the wave function is well-approximated by the solution to the linearized Ginzburg Landau equation

$$\frac{1}{2m}(ih\nabla + \frac{e^*}{c}A)^2\Psi = \alpha\Psi,\tag{1}$$

(where ∇ is the two-dimensional gradient operator) with nonreflecting boundary conditions at $\partial\Omega$ the boundary of Ω . Here A is the magnetic vector potential satisfying $\nabla \times A = H\hat{z}$, m is the effective electron mass, $\alpha = \frac{\hbar^2}{2m\xi_0^2} \frac{T-T_c}{T_c}$, where ξ_0 is the coherence length at T = 0 and T_c is the critical temperature in the absence of magnetic field. Since we are interested in finding the relation between T and H, the problem is mathematically equivalent to computing the ground state of the Schrödinger equation for a particle under a magnetic field. The strong field asymptotics can also be shown to be equivalent to evaluating the critical magnetic field H_{c3} for materials with large Ginzburg Landau parameter [1], [4].

We denote by ϕ the applied flux measured in units of ϕ_0 . When $\phi \gg 1$ we expect $|\Psi|$ to be very small except at a boundary layer whose nondimensional thickness is $O(\phi^{-\frac{1}{2}})$. The detailed structure of Ψ and the asymptotic expansion of α depend upon the geometry and smoothness of Ω .

It is convenient to scale the domain Ω canonically through a similarity transformation that preserves its shape while changing its area to 2π . The new domain will be denoted by $\tilde{\Omega}$ so that we must solve the non-dimensionalized problem

$$(i\nabla + \phi A_N)^2 \Psi = \mu \Psi \text{ in } \hat{\Omega},$$

where A_N satisfies $\nabla \times A_N = 1\hat{z}$. When the domain is smooth (i.e. has no corners), the leading order term in the expansion for T is linear in the flux: $\frac{T_c-T}{T_c} \sim \frac{\xi_0^2}{R^2} \mu_0 \phi$. Here $R = (|\Omega|/2\pi)^{\frac{1}{2}}$, and μ_0

is determined by the eigenvalue problem

$$\psi_{\eta\eta} + (\mu_0 - (\eta - \mu_0^{1/2})^2)\psi = 0, \quad \psi_\eta(0) = 0, \quad \lim_{\eta \to \infty} \psi(\eta) = 0, \quad \psi(0) = 1.$$
(2)

This equation was introduced by Saint-James and deGennes [14] in their work on nucleation of superconductivity near a half plane.

Higher order terms in the expansion are computed through a careful boundary layer analysis. In general the wave function concentrates near the point of the boundary where the curvature κ is maximal. It decays exponentially fast away from this point both tangentially along the boundary of Ω (on a lengthscale of $O(\phi^{-1/8}R)$) and radially into the interior of Ω (on a lengthscale of $O(\phi^{-1/2}R)$) [4]. The expansion for μ takes the form

$$\frac{T_c - T}{T_c} = \frac{\xi_0^2}{R^2} (\mu_0 \phi + \mu_1 \phi^{1/2} + \mu_2 \phi^{1/4} + \dots).$$
(3)

Here $\mu_1 = -\frac{\kappa}{3I_0}$ and $\mu_2 = \frac{1}{I_0} \left(\frac{-\sqrt{\mu_0}\kappa_{ss}}{6}\right)^{1/2}$, where $I_0 = \int_0^\infty \psi^2$ and κ and κ_{ss} are evaluated at the point of maximum curvature (with κ_{ss} assumed to be strictly negative there). Solving (2) numerically we obtain $\mu_0 = 0.59$ and $I_0 = 1.312$.

In the special case where Ω is a disc, the wave function has radial symmetry. In fact, it is possible to obtain an explicit solution to the linearized problem in terms of Kummer functions [2]. However it is still beneficial to write down the asymptotic expansion because it captures simple geometric characteristics of the domain. We thus obtain

$$\frac{T_c - T}{T_c} = \frac{\xi_0^2}{R^2} (0.59\phi + \mu_1 \phi^{1/2} + f(\phi) + \dots),$$
(4)

where $f(\phi)$ is an O(1) oscillatory function of ϕ that approaches a periodic function as $\phi \to \infty$. We note that a rigorous mathematical treatment of this problem within the context of nonlinear bifurcation theory has been carried out in [1].

When Ω is a square, the curvature function is singular and the previous expansion is no longer valid. Our computations on the linearized eigenvalue problem indicate that the wave function now concentrates near the corners. A simple analysis shows that the leading order term in the expansion for T is

$$\frac{T_c - T}{T_c} \sim \frac{\xi_0^2}{R^2} \mu_c \phi \text{ for } \phi >> 1.$$
(5)

The coefficient μ_c is the ground state for the Schrödinger operator $(i\nabla + A_N)^2$ in the quarterplane. The eigenvalue can be estimated by an upper bound derived from the Rayleigh quotient [8]. Surprisingly the upper bound computed in [8] is much lower than our numerical computation (see below).

Expansions of the phase transition curve T(H) for low values of the flux follow from regular perturbation theory. Let p be the solution of Poisson equation $\nabla^2 p = 1$ in $\tilde{\Omega}$ with homogeneous Dirichlet boundary conditions, and set $\zeta_0 = -\frac{1}{2\pi} \int_{\tilde{\Omega}} p$. To leading order in ϕ we find

$$\frac{T_c - T}{T_c} \sim \frac{\xi_0^2}{R^2} \zeta_0 \phi^2.$$
 (6)

For example, we obtain $\zeta_0 = 0.25$ for a disc, and $\zeta_0 = 0.22$ for a square.

In Figure 1 we present the numerical computations of the values of $\frac{R^2}{\xi_0^2} \frac{T_c-T}{T_c\phi}$ as a function of ϕ for a square (solid line) and for a disc (arrows) with the same area where ϕ lies in the range [0, 16]. The results are in perfect agreement with our theory for low ϕ . It is observed that superconductivity nucleates for a square at a higher temperature than for a disc. Our asymptotic results indicate that the nucleation in a square will be at higher temperature than for *any* smooth domain in the large flux regime. From our numerical calculations we estimate $\mu_c = 0.55$. As was mentioned above this is about twice the estimate of [8]. We cannot explain this large discrepancy. We point out, however that Kato et al. [11] have solved numercially the time dependent Ginzburg Landau equation in a square and studied the existence of superconductivity above H_{c2} . They expected to get the behavior predicted in [14]. Instead they found what they called an 'anomalous phenomena', which, formulated in our notation, is equivalent $0.5 < \mu_c < 0.555$. This value is in agreement with our results.

We compare our expansions with experimental results. We will make a least-squares fit of the experimental data to an expansion of the form

$$\frac{T_c - T}{T_c} \sim \frac{\xi_0^2}{R^2} \mu_e^0 \phi, \ \phi \gg 1,$$
(7)

and

$$\frac{T_c - T}{T_c} \sim \frac{\xi_0^2}{R^2} \zeta_e \phi^2, \quad \phi \ll 1.$$
(8)

To determine the coefficients μ_e^0 and ζ_e from a given experiment we need to know ξ_0 and the actual

size of the domain. Therefore it is interesting to note the ratio $\delta = \mu_e^0 / \zeta_e$ is independent of both ξ_0 and the domain scale. It is controlled solely by the shape of the domain.

We first consider the experiment of Buisson et al. [6] who studied the T-H line for an aluminum disc of radius 7.2 μm . For a disc we obtain the theoretical value of the ratio defined above to be $\delta_0 = .59/\zeta_0 = 2.36$. The experimental value is found to be $\delta_e = 2.26$.

It has been suspected [6],[2] that some of the anomalies in the experiment were caused by the contact leads that modified the spherical geometry. Motivated by the theoretical expansion (4) we shall test this hypothesis by assuming

$$\frac{T_c - T}{T_c} \sim \frac{\xi_0^2}{R^2} (\mu_e^0 \phi + \mu_e^1 \phi^{1/2}), \ \phi \gg 1.$$
(9)

In particular, we wish to estimate the coefficient of the $\phi^{1/2}$ term in the expansion (9) since this term depends linearly on the maximal curvature. We used the value $\xi_0 = 0.2 \ \mu m$ obtained [6] from the low ϕ expansion. We found that the radius of curvature at the nucleation point is 6.5 $\mu m \pm 0.8 \ \mu m$ which is in reasonable agreement with the actual radius of 7.2 μm . Thus we conclude that at least at the high ϕ regime the results were not affected by the contact leads.

Moshchalkov et al. [13] performed a similar experiment with a $1 \times 1 \ \mu m$ aluminum square. They used fluxes of up to 4 flux quanta. The experimental data was fitted to the numerical solution of the associated eigenvalue problem for a disc with area 1. For this purpose they chose $\xi_0 = 0.1 \ \mu m$. A similar comparison was later performed in [2]. A recent experiment from the same laboratory [5] provides more extensive data. In this experiment a $2 \times 2 \ \mu m$ square was used. The authors measured the phase transition curve for fluxes of up to 16 flux quanta and again compared the data to the expected theoretical values for a disc of comparable area.

We shall compare the data of [5] for the square to the asymptotic theoretical formulas (5) and (6). Again this comparison is complicated by the need to estimate the value of ξ_0 . As a first attempt, we estimate the value of ξ_0 by comparing the experimental data for low values of ϕ to the theoretical expansion (6) and obtain $\xi_0 = 0.095 \ \mu m$. However, using this value, the experimental results [5] predict $\mu_e^0 > 0.81$ in the large ϕ expansion (7). This is way above even the theoretical value for the disc. In fact, there is no ξ_0 that allows one to accurately match the theoretical curve to the experimental data. To demonstrate this point, we note that our theory gives the estimate $\delta = 2.5$, while the experimental estimate is $\delta = 3.7$. (Our estimate of δ is based upon our numerical evidence that μ_c from expansion (5) is approximately 0.55) We point out that other laboratories have recently reported [16], [7], [6] values for ξ_0 for aluminum near 0.2 μm .

One plausible explanation for the deviation lies in the importance of the nonlocal effects due to the electric contacts [15]. In the low ϕ regime the coherence length is large compared to the size of the square, so that wave function, and thus the transition temperature, are affected by the neighborhood of the square. Indeed Figure 3 of [15] indicates that the electric contacts do affect the phase transition curve for low ϕ , and their effect diminishes as ϕ increases. Therefore, we shall estimate ξ_0 using the high ϕ data. We thus obtain $\xi_0 = 0.1195 \ \mu m$. The circles in Figure 1 corresponds to the experimental data of [5] with this choice of ξ_0 . The nonlocal effect was apparently less pronounced in [6] since their domain was 10 times larger.

An examination of the three curves in Figure 1 reveals that while the experimental curve lies well below the theoretical curves, the *location of the peaks* in the experimental curve perfectly match the location of the peaks of the theoretical curve for the square. On the other hand, the experimental peaks deviate considerably from the theoretical peaks for the *disc*. Bruyndoncx et al. [5] introduced the notion of 'effective square area' (which is smaller than the true geometrical area) in order to obtain a fit between the experimental data and the theory for the disc. We have shown here that the actual experimental peaks are in perfect agreement with the theory for the square. We also point out that while the experimental slope for low ϕ (near 0.5) is about 0.13 (well below the theoretical 0.22 value), the experimental curve steepens just before the first peak (ϕ near 1.7), and the local slope is about 0.19. It still remains to explain the deviation between the experimental and theoretical curves for intermediate values of ϕ , both in actual values and in the amplitude of the oscillations. A possible explanation is in the way in which the transition temperature is defined. Bruyndoncx et al. [5] set it to be the temperature for which the resistivity drops to half the normal value. As the applied flux increases, the temperature drops, and the uncertainty interval shortens.

To summarize, we have developed general formula (3), (4) and (5) for the asymptotic transition line in mesoscopic superconducting samples in the limit of large flux. We further derived a formula (6) for the asymptotics of that curve in the limit of low flux. In the large flux limit and for smooth domains, our formula captures the universal linear base curve that relates to the fact that the wave function concentrates near the boundary which appears locally as a half plane. It also contains terms proportional to fractional powers of the applied flux that depend on universal parameters and on the local geometry of the sample's surface. In the special case of a disc our formula resolves an oscillatory dependence of T upon ϕ . We have also shown that a square sample exhibits a different behavior from smooth domains already at the linear leading order term. Finally we used the new theory to analyze recent experiments.

Acknowledgement We are grateful to V. Bruyndoncx and O. Buisson for sharing with us a wealth of experimental data, and to J. Berger for bringing refs. [8] and [11] to our attention.

References

- [1] P. Bauman, D. Phillips and Q. Tang, Arch. Rat. Mech. Anal. 142, 1, 1998.
- [2] R. Benoist and W. Zwerger Z. Phys. **B103**, 377 (1997).
- [3] J. Berger and J. Rubinstein, Phys. Rev. Lett. **75**, 320 (1995).
- [4] A. Bernoff and P. Sternberg, J. Math. Phys. **39**, 1272, (1998).
- [5] V. Bruyndoncx, J.G. Rodrigo, T. Puig, L. Van Look, V.V. Moshchalkov and R. Jonckheere, preprint.
- [6] O. Buisson, P. Gandit, R. Rammal, Y.Y. Wang and B. Pannetier, Phys. Lett. 150, 36 (1990).
- [7] D. Davidovich et al. Phys. Rev. B 55, 6518 (1997).
- [8] V.M. Fomin, J.T. Devreese and V.V. Moshchalkov, Europhys. Lett. 42, 553 (1998).
- [9] P.G. de Gennes Superconductivity in metals and Alloys, Addison Wesley (1989).
- [10] R.P. Groff and R.D. Parks, Phys. Rev. **176**, 567 (1968).
- [11] R. Kato, Y. Enomoto and S. Maekawa, Phys. Rev. B 47, 8016 (1993).
- [12] W.A. Little and R.D. Parks, Phys. Rev. Lett 9, 9 (1962).

- [13] V.V. Moshchalkov, L. Gielen, C. Strunk, R. Jonckheere, X. Qiu, C. Van Haesendonck and Y. Bruynserade, Nature (London) 373, 319 (1995).
- [14] D. Saint-James and P.G. deGennes, Phys. Lett. 7, 306 (1963).
- [15] C. Strunk, V. Bruyndoncx, V.V. Moshchalkov, C. Van Haesendock, Y. Bruynserase and R. Jonckheere, Phys. Rev. B 54, R12701, (1996).
- [16] X. Zhang and J.C. Price, Phys. Rev. B 55, 3128 (1997)

H.T.J: Department of Mathematics, Indiana University, Bloomington, IN 47405, USA. E-mail: hjadalla@indiana.edu

J.R.: Department of Mathematics, Technion, Haifa 32000, Israel. E-mail: koby@math.technion.ac.il. Research supported in part by the U.S.-Israel Binational Science Foundation, by the Israel Science Foundation and by the Posnansky Research Fund in high temperature superconductivity.

P.S.: Department of Mathematics, Indiana University, Bloomington, IN 47405, USA. E-mail: sternber@indiana.edu. Research supported in part by the N.S.F. under grant DMS-9322617 and a U.S.-Israel Binational Science Foundation Grant.

