

# The anomaly of the oxygen bond-bending mode at $320\text{ cm}^{-1}$ and the additional absorption peak in the c-axis infrared conductivity of underdoped $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ single crystals revisited by ellipsometric measurements

C. Bernhard<sup>1</sup>, D. Munzar<sup>1,2</sup>, A. Golnik<sup>1\*</sup>, C.T. Lin<sup>1</sup>, A. Wittlin<sup>3</sup>, J. Humlíček<sup>2</sup>, and M. Cardona<sup>1</sup>

*1) Max-Planck-Institut für Festkörperforschung, Heisenbergstrasse 1,  
D-70569 Stuttgart, Germany*

*2) Department of Solid State Physics and Laboratory of Thin Films and  
Nanostructures, Faculty of Science, Masaryk University, Kotlářská  
2, CZ-61137 Brno, Czech Republic*

*3) Institute of Physics, Polish Academy of Sciences, Aleja Łótnikow 32,  
PL-02-668, Poland*

(January 6, 2018)

## Abstract

We have performed ellipsometric measurements of the far-infrared c-axis dielectric response of underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  single crystals. Here we report a detailed analysis of the temperature-dependent renormalization of the oxygen bending phonon mode at  $320\text{ cm}^{-1}$  and the formation of the additional absorption peak around  $400\text{--}500\text{ cm}^{-1}$ . For a strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal with  $T_c=52\text{ K}$  we find that, in agreement with previous reports based on conventional reflection measurements, the gradual onset of both features occurs well above  $T_c$  at  $T^*\sim 150\text{ K}$ . Contrary to some of these reports, however, our data establish that the phonon anomaly and the

formation of the additional peak exhibit very pronounced and steep changes right at  $T_c$ . For a less underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal with  $T_c=80$  K, the onset temperature of the phonon anomaly almost coincides with  $T_c$ . Also in contrast to some previous reports, we find for both crystals that a sizeable fraction of the spectral weight of the additional absorption peak cannot be accounted for by the spectral-weight loss of the phonon modes but instead arises from a redistribution of the electronic continuum. Our ellipsometric data are consistent with a model where the bilayer cuprate compounds are treated as a superlattice of intra- and inter-bilayer Josephson-junctions.

PACS Numbers: 74.25.Gz, 74.25.Kc, 74.50.+r, 74.72.Bk

## I. INTRODUCTION

It was early recognized that some of the infrared active c-axis phonon modes of the high- $T_c$  cuprate superconductors (HTSC) exhibit rather strong changes (so-called ‘phonon anomalies’) in the vicinity of the superconducting transition [1]. The most pronounced phonon anomalies have been observed for those compounds which contain two (or three) closely spaced  $\text{CuO}_2$  layers per unit cell, like the bilayer compounds  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  (Y-123) [2,3],  $\text{YBa}_2\text{Cu}_4\text{O}_8$  (Y-124) [4] and  $\text{Pb}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$  [5], or the trilayer system  $\text{Tl}_2\text{Ba}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$  [6]. In Y-123 and Y-124 the most pronounced renormalization occurs for the so-called oxygen bond-bending mode at  $320\text{ cm}^{-1}$  which involves the in-phase vibration of the O(2) and O(3) oxygen ions of the  $\text{CuO}_2$  planes against the Y-ion which is located in the center of the bilayer and against the ions of the CuO chains [7]. The renormalization of the  $320\text{ cm}^{-1}$  mode is accompanied by the formation of an additional broad absorption peak in the frequency range between  $400$  to  $500\text{ cm}^{-1}$  at low temperature. The effects are most spectacular for strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5-6.6}$  with  $T_c \sim 50\text{-}60\text{ K}$ . Here the phonon mode at  $320\text{ cm}^{-1}$  softens by almost  $20\text{ cm}^{-1}$  and loses most of its spectral weight which is transferred to the additional broad peak. As the hole doping of the  $\text{CuO}_2$  planes increases, the anomaly of the  $320\text{ cm}^{-1}$  phonon mode becomes less pronounced. Simultaneously, the additional peak shifts towards higher frequencies and becomes considerably weaker.

Evidently, there exists an intimate relationship between the strong anomaly of the oxygen bond-bending mode at  $320\text{ cm}^{-1}$  and the formation of the additional absorption peak. The underlying mechanism, however, is yet unknown and the subject of an ongoing discussion [1,8,9].

Recently van der Marel and coworkers have proposed a very interesting explanation for the additional absorption peak [10,11]. They assumed that the  $\text{CuO}_2$  planes of underdoped HTSC are not coherently coupled, not even the closely spaced planes of the bilayers. From this point of view a bilayer superconductor like Y-123 can be treated as a stack of two-dimensional superconducting layers which forms a superlattice of intra- and inter-bilayer

Josephson-junctions. The dielectric response of such a superlattice of Josephson junctions exhibits two zero-crossings corresponding to two longitudinal Josephson-plasmons: the inter-bilayer and the intra-bilayer one. In addition, it has a pole corresponding to the so called ‘transverse optical Josephson plasmon’ [10]. Van der Marel have suggested that the additional absorption peak discussed above may correspond to this transversal resonance. Very recently they have confirmed their suggestion by more quantitative considerations regarding the doping dependence of the peak position [11]. Some of us have shown that this model can be extended to account not only for the presence of the additional peak but also for the related phonon anomalies [12]. The essential idea consists in including the local electrical fields acting on the ions that participate in the phonon modes. In particular, the model has allowed us to explain the details of the anomaly of the  $320\text{ cm}^{-1}$  phonon mode in Y-123. This has been shown to arise from a dramatic change of the local electrical field acting on the in-plane O(2)- and O(3)-ions caused by the onset of inter- and intra-bilayer Josephson effects.

The verification of the existence of intra-bilayer Josephson plasmons, may have rather far reaching consequences. The finding that even the closely-spaced  $\text{CuO}_2$  layers are only weakly (i.e. Josephson) coupled along the c-axis would favor models which predict that the electronic ground state of the  $\text{CuO}_2$  planes is unconventional, involving charge confinement to the planes and incoherent coupling between the planes in the normal state [13]. So far, the existence of the Josephson plasma resonance has been firmly established only for the case of  $\text{CuO}_2$  planes (or pairs of planes) that are separated by insulating layers much wider than the in-plane lattice constant. Such examples are the studies of the c-axis transport [14,15], the microwave absorption [16] or the FIR c-axis conductivity [17–19]. Even two different longitudinal plasma modes have been recently observed in the  $T^*$  phase  $\text{SmLa}_{1-x}\text{Sr}_x\text{CuO}_4$  which has two kinds of blocking layers: the fluorite type  $\text{Sm}_2\text{O}_3$  layers and the rocksalt-type  $(\text{La,Sr})_2\text{O}_3$  layers [20].

In order to establish the above interpretation of the anomalies in the c-axis conductivity of underdoped Y-123, two points have to be clarified which have not been discussed in our

previous communication [12]. Firstly, according to the model of the superlattice of inter- and intra-bilayer Josephson junctions (lets call it a Josephson-superlattice-model) the phonon anomalies should become very pronounced only below  $T_c$ , while they can appear somewhat above  $T_c$  for the strongly underdoped and most anisotropic samples as a result of pairing fluctuations within the bilayers. From the previous experimental results it was not clear whether this is the case. Reflectance measurements performed on strongly underdoped Y-123 single crystals rather seemed to indicate that the anomaly of the  $320\text{ cm}^{-1}$  phonon sets in well above  $T_c$  at a temperature  $T^* \gg T_c$  and proceeds without any noticeable change at  $T_c$  [3,9]. The temperature dependence of the phonon anomaly rather seemed to resemble [3,21] that of the spin-lattice relaxation rate  $(T_1T)^{-1}$  or the Knight shift observed in NMR experiments, both of which are determined by the to the so-called ‘spin-gap phenomenon’, i.e., by a gradual and incomplete depletion of the low energy spin excitations. These speculations are supported by Zn substitution experiments: the Zn substitution is known to suppress the spin-gap effect [22] and it has also been shown to remove the anomaly of the  $320\text{ cm}^{-1}$  phonon mode and the additional absorption peak [9]. Second, the model predicts that the additional peak should acquire a considerable part of its spectral weight (SW) from the electronic background, to be more specific from the superconducting condensate [12]. This prediction is not consistent with Ref. [2] where it has been suggested that the SW of the additional peak is fully accounted for by the spectral-weight loss ( $\Delta SW$ ) of the phonon modes at  $320$  and  $560\text{ cm}^{-1}$ .

In the following we report an ellipsometric study of the far-infrared (FIR) c-axis dielectric response of two underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  single crystal: one strongly underdoped ( $\delta \approx 0.5$ ,  $T_c = 52\text{ K}$ ), the other moderately underdoped ( $\delta \approx 0.25$ ,  $T_c = 80\text{ K}$ ). In particular, we present a detailed analysis of the anomaly of the oxygen bond-bending mode at  $320\text{ cm}^{-1}$  and of the additional absorption peak. In case of the strongly underdoped crystal our ellipsometric measurements establish that the temperature-evolution of the phonon anomaly and the additional absorption peak exhibits a two-step behavior with a smooth onset at  $T^* \sim 150\text{ K} \gg T_c = 52\text{ K}$  followed by a sudden and steep change right at  $T_c = 52\text{ K}$ . For the

moderately underdoped crystal the onset of the anomaly occurs in the vicinity of  $T_c$ . For both crystals our data establish that the absorption peak obtains only some part of its spectral weight from the phonon system while a substantial part (at least 40-50%) arises from the electronic background.

## II. EXPERIMENTAL TECHNIQUE

### A. Sample preparation

The  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  single crystals with typical dimensions of  $2 \times 2 \times (0.5-1)$  mm<sup>3</sup> have been grown in Y-stabilized  $\text{Zr}_2\text{O}$  crucibles [23]. For the ellipsometric measurements we used only crystals with a smooth and shiny as-grown surface containing the c-axis. A strongly oxygen deficient crystal has been prepared by sealing it in an evacuated quartz tube together with a large amount of Y-123 powder whose oxygen content has been previously adjusted to  $\delta \approx 0.5$  (by annealing in 0.1%  $\text{O}_2$  in Ar at 530° C and subsequently quenching into liquid nitrogen). The quartz-ampule containing the crystal and the powder was annealed at 500 °C for 10 days and subsequently slowly cooled to room temperature. A second, moderately underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal has been prepared by annealing in a flowing oxygen gas stream at 550 °C and subsequent rapid quenching. The critical temperature  $T_c$  and the transition width  $\Delta T_c$  (10 to 90% of the diamagnetic shielding) have been determined by DC-magnetization measurement in zero-field-cooled (zfc) and field-cooled (fc) mode ( $H_{ext}=5$  Oe) using a commercial SQUID magnetometer. Figure 1 shows the temperature-dependent volume susceptibility,  $\chi_V$ , for the  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal with  $T_c=52$  K and  $\Delta T_c=3$  K (open circles) and the  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal with  $T_c=80$  K and  $\Delta T_c=4$  K (solid squares).

### B. Technique of far-infrared ellipsometry

The quantity measured in ellipsometry [24] is the complex reflectance ratio

$$\tilde{\rho}(\omega, \Phi) = \tilde{r}_p(\omega, \Phi) / \tilde{r}_s(\omega, \Phi), \quad (1)$$

where  $\Phi$  is the angle of incidence (in our experiment  $80^\circ$  with a beam divergence of  $\pm 1.7^\circ$ ) and  $\tilde{r}_p$  and  $\tilde{r}_s$  are the complex Fresnel reflection coefficients for light which is polarized parallel ( $p$ ) and perpendicular ( $s$ ) to the plane of incidence, respectively. The dielectric function is extracted from  $\tilde{\rho}(\omega, \Phi)$  by inverting the Fresnel equations:

$$\tilde{\epsilon}(\omega) = [(1 - \tilde{\rho}(\omega, \Phi)) / (1 + \tilde{\rho}(\omega, \Phi))]^2 \tan^2 \Phi \sin^2 \Phi + \sin^2 \Phi. \quad (2)$$

This inversion assumes an isotropic sample. For an anisotropic sample, in general, different elements of the dielectric tensor can contribute to  $\tilde{\rho}(\omega, \Phi)$ . The formal inversion according to Eq. (2) then yields only a so-called pseudodielectric function [25]. For the case of  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ , which is an almost uniaxial and strongly anisotropic material with metallic behavior of  $\tilde{\epsilon}_{a,b}(\omega)$  and insulating behavior of  $\tilde{\epsilon}_c(\omega)$ , it was previously shown that the pseudodielectric function represents a very good approximation for  $\tilde{\epsilon}_c$  when the measurement is performed with the  $c$ -axis in the plane of incidence [26].

The technique of ellipsometry provides significant advantages over conventional reflection methods: i) it does not require the determination of the absolute intensity of the reflected light (no reference problem) and ii) the complex dielectric function  $\tilde{\epsilon} = \epsilon_1 + i\epsilon_2$  is obtained directly, no Kramers-Kronig transformation and thus no extrapolation of the reflectivity towards zero and infinite frequency is needed [27,28].

The ellipsometric measurements have been performed at the U4IR beamline of the National Synchrotron Light Source (NSLS) at Brookhaven National Laboratory (BNL), using a home-built setup attached to a Nicolet Fast-Fourier Spectrometer [27,28]. The high brilliance of the synchrotron light source enables us to perform very accurate ellipsometric measurements in the far-infrared range even on samples with comparably small ac-faces of  $0.5 \times 1 \text{ mm}^2$ . Since only relative intensities are required, the ellipsometric measurements are very reproducible and the data taken at a given temperature before and after thermal cycling or several days of measurement coincide to within the noise level.

### III. RESULTS

#### 1. Strongly underdoped $YBa_2Cu_3O_{6.5}$

Figure 2 shows the real part of the far-infrared (FIR) c-axis conductivity  $\sigma_c(\omega, T)$  of the strongly underdoped  $YBa_2Cu_3O_{6.5}$  crystal with  $T_c=52$  K for (a)  $T=300, 200$ , and  $150$  K and (b)  $T=150, 110, 60, 45, 35$  and  $4$  K. At room temperature the six infrared-active phonon modes at  $155, 190, 280, 320, 560$  and  $630$   $\text{cm}^{-1}$  are superimposed on a weak and almost featureless electronic background. As the temperature is lowered below room-temperature, the electronic background decreases continuously and develops the so-called normal-state gap (NS gap) or pseudogap which is a well known feature of the underdoped cuprate superconductors [2,29–32]. Evidently, this NS-gap starts to develop at some rather high temperature,  $T^{NG} \geq 300$  K. Its characteristic frequency scale  $\omega_{NG}$  is fairly large and it even exceeds the measured spectral range, i.e.,  $\omega_{NG} > 700$   $\text{cm}^{-1}$  [31,32]. Figure 2 shows that the gradual onset of the renormalization of the oxygen bond-bending mode at  $320$   $\text{cm}^{-1}$  and the additional broad peak at  $410$   $\text{cm}^{-1}$  occurs around  $T^* \sim 150$  K, i.e., well below  $T_{NG} \geq 300$  K but also well above  $T_c=52$  K. However, the most important feature that is evident in Fig. 2b is that both, the anomaly of the  $320$   $\text{cm}^{-1}$  phonon mode and the formation of the additional absorption peak at  $410$   $\text{cm}^{-1}$ , exhibit very pronounced and steep changes right at  $T_c=52$  K. This finding implies that both effects are related to the superconducting transition rather than to the NS-gap or to the spin-gap phenomenon as has been previously suggested [3,9]. The gradual onset of the anomalies at  $T^* \gg T_c$  may be due to superconducting pairing fluctuations (especially within the bilayers) which become particularly pronounced for strongly underdoped and thus very anisotropic samples. We do not attempt here to comment on the rather controversial question of whether the NS-gap and/or the spin gap are also somehow related to the superconducting pairing fluctuations.

We have performed a more quantitative data analysis by fitting to the complex dielectric function in the spectral range  $250 < \omega < 700$   $\text{cm}^{-1}$  a sum of modified Lorentzian functions



$\epsilon(\omega) = S \cdot (\omega_o^2 + i\Gamma \cdot Q) / ((\omega_o^2 - \omega^2) - i\omega \cdot \Gamma)$  which represent the contributions of the phonon modes at 280, 320, 560 and 630  $\text{cm}^{-1}$ . This modified Lorentzian function which is obtained by mixing the real- and the imaginary parts of the usual Lorentzian function (it basically corresponds to a Fano-like function) allows one to perform Kramers-Kronig consistent fits of asymmetric phonon lineshapes [2,3]. In agreement with previous reports [2,3], we find that only the phonon modes at 560 and 630  $\text{cm}^{-1}$  are very asymmetric and that the asymmetry  $Q$  of these modes increases with decreasing temperature. In order to describe the flat electronic background and the additional broad absorption peak in a Kramers-Kronig consistent way we have also included a sum of seven broad Lorentzian oscillators which have been located between 250 and 700  $\text{cm}^{-1}$  and whose half-widths have been limited to values between 150 and 500  $\text{cm}^{-1}$ .

In our opinion this fitting procedure does not allow one to obtain an appropriate description of the phonon contribution since it assumes that all the ions participating in the phonon modes experience the same (average) electric field. Instead, as motivated in Ref. [12], we suggested that the local electric fields acting on the ions exhibit significant deviations from the average field as a result of the extremely weak electronic coupling between the individual  $\text{CuO}_2$  planes of underdoped cuprates. We have shown that the spectacular anomaly of the 320  $\text{cm}^{-1}$  phonon mode, and also the asymmetry and the SW changes of the phonon modes at 560 and 630  $\text{cm}^{-1}$ , can be explained by such local field effects, in particular, by the changes of the local electrical fields caused by the onset of Josephson-effects within the intra- and inter-bilayer junctions [12]. In the present paper we nevertheless apply the simpler fitting procedure using modified Lorentzian functions in order to obtain the temperature dependence of the parameters of the phonon modes which can be readily compared with previous results.

Figure 3 shows the temperature dependence of (a) the oscillator strength  $S$ , (b) the eigenfrequency  $\omega_o$ , and (c) the half-width  $\Gamma$  of the oxygen bond-bending mode at 320  $\text{cm}^{-1}$ . It is evident from Fig. 3a and 3b that the changes of  $S$  and  $\omega_o$  set in rather gradually around  $T^* \sim 150$  K. The temperature dependences of both quantities, however, exhibit a sudden

and steep change around  $T_c=52$  K. This finding contrasts with the previous reports that the renormalization of the  $320\text{ cm}^{-1}$  phonon mode does not exhibit any noticeable change around  $T_c$  [3,9]. In agreement with the previous reports we find that the half-width  $\Gamma$  of the  $320\text{ cm}^{-1}$  mode starts to decrease only below  $T_c=52$  K [1–3,33]. For  $T^*>T>T_c$  it even tends to increase, but this small increase may be an artifact of our fitting procedure. Figure 4 displays the electronic background including the additional peak around  $400\text{ cm}^{-1}$  which has been obtained by subtracting the contributions of the phonon modes at  $280$ ,  $320$ ,  $560\text{ cm}^{-1}$  and  $630\text{ cm}^{-1}$ . The formation of the additional peak show in Fig. 4 follows a similar temperature dependence like the anomaly of the  $320\text{ cm}^{-1}$  phonon mode. The broad peak gradually develops below  $T^*\sim 150$  K and suddenly increases in magnitude below  $T_c=52$  K. Evidently, the peak position does not change much as a function of temperature. Below  $T_c$  the peak is very pronounced and therefore hardly affected by the subtraction of the phononic contribution. The frequency of the maximum decreases slightly from  $410\text{ cm}^{-1}$  at  $5\text{ K}$  to  $395\text{ cm}^{-1}$  at  $45\text{ K}$ . Above  $T_c$  the peak becomes rather weak as compared to the phonon mode at  $320\text{ cm}^{-1}$ . We therefore cannot reliably determine its position. Nevertheless it is evident that it remains close to  $400\text{ cm}^{-1}$ . Note that within the Josephson-superlattice-model the peak position is expected to decrease only by about  $30\text{ cm}^{-1}$  as the temperature is increased above  $T_c$ . The position of the transverse plasmon is determined mainly by the intra-bilayer Josephson-frequency which for strongly underdoped samples has been suggested [12] not to exhibit any pronounced changes at  $T_c$  since the pairing fluctuations within the individual bilayers persist far above the macroscopic critical temperature  $T_c$ .

Figure 5 shows a comparison of the temperature dependence of the spectral weight of the additional  $410\text{ cm}^{-1}$  peak,  $SW^{410}$ , (solid squares) with the spectral weight loss of the  $320\text{ cm}^{-1}$  phonon mode,  $\Delta SW^{320}$ , (open circles). The value of  $\Delta SW^{320}$  has been calculated according to the formula  $\Delta SW = \pi^2 c \cdot \epsilon_o \cdot [S(175\text{ K}) - S(T)] \cdot \nu_o^2$  using the oscillator strenghts  $S(T)$  and the eigenfrequencies  $\nu_o$  given in Fig. 3a and 3b. The error bar indicates the upper limit for the spectral weight loss of the apical oxygen mode at  $560\text{ cm}^{-1}$ . The inset of Fig. 5 illustrates how we have estimated the spectral weight of the additional peak  $SW^{410}$  (shaded

area) by integrating the conductivity between 220 and 680  $\text{cm}^{-1}$  (open circles) and subtracting the contribution of a linear electronic background (solid line). Note that our assumption of a linear electronic background conductivity is supported by the high temperature data for  $T > T^* = 150 \text{ K}$  (see Fig. 4a) and by the data for less strongly underdoped samples where the additional peak is comparably weak and appears only below  $T_c$  (see Ref. [31,32] and discussion below). It is evident from Fig. 5 that the spectral weight losses of the phonon modes at 320 and 560  $\text{cm}^{-1}$  account only for some fraction of the spectral weight of the additional absorption peak at 410  $\text{cm}^{-1}$ . We estimate that at least 40-50 % of the spectral weight of the additional absorption peak does not arise from the phonon subsystem but instead seems to arise from the electronic continuum. Such a redistribution of the electronic spectral weight towards the additional absorption peak is predicted by the Josephson-superlattice-model where the transverse Josephson plasmon acquires a sizeable fraction of the spectral weight of the SC condensate [11,12]. This means that some fraction of the spectral weight removed in the FIR-regime does not appear in the delta-function at zero frequency which describes the inductive response of the superfluid condensate but is instead shifted to the additional absorption peak representing the transversal Josephson plasmon. In fact, our choice of the linear electronic background (solid line) is rather conservative. Also shown in the inset is a fit with a Lorentzian plus a linear electronic background conductivity (dashed lines) which gives a somewhat larger value of  $\text{SW}^{410} \approx 16.000 \text{ } \Omega^{-1}\text{cm}^{-2}$  at  $T=5 \text{ K}$ . The result of this fit agrees surprisingly well with the prediction of the Josephson-superlattice model that the SW of the bare transverse Josephson-plasmon (neglecting the interaction with the phonons and the consequent redistribution of the spectral weight of the 320  $\text{cm}^{-1}$  phonon mode,  $\Delta\text{SW}^{320}(5K) \approx 5000 \text{ } \Omega^{-1}\text{cm}^{-2}$ ) should be around 10.000  $\Omega^{-1}\text{cm}^{-2}$  [12].

It has been reported previously that the spectral weight of the additional absorption peak can be fully accounted for by the spectral weight loss of the phonon modes at 320 and 560  $\text{cm}^{-1}$  [2]. We note that this discrepancy between the conclusions of [2] and ours does not arise from any significant differences in the experimental data but rather originates from the difference in the estimate of the electronic background. It seems that Homes et

al. obtained a lower spectral weight of the additional absorption peak by introducing an electronic background which develops a gap-like feature around  $280\text{ cm}^{-1}$  (see for example Fig. 10 of Ref. [2]). They argued that this gap feature is related to the NS gap. Our recent ellipsometric data, however, do not support such an interpretation because they show that the onset frequency of the NS gap,  $\omega_{NG}$ , is significantly larger: it increases from  $\omega_{NG} \approx 650\text{ cm}^{-1}$  for slightly underdoped samples to  $\omega_{NG} \gg 700\text{ cm}^{-1}$  for strongly underdoped samples. We have also shown that the temperature at which the signatures of the normal state NS-gap start to appear increases rather rapidly on the underdoped side and even exceeds room temperature for strongly underdoped samples [31,32] (see also Fig.2). Note that recent ARPES- and tunneling experiments yield a similar temperature- and doping dependence of the NS-gap (even the absolute values of the gap size agree reasonably well) [34–37]. This fact allows us to conclude that the characteristic energy- and temperature scales of the additional absorption peak and the NS-gap (and also their doping dependence) are very different which makes it rather unlikely that both have a common origin.

## 2. Moderately underdoped $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$

We have also performed FIR ellipsometric measurements on a less strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  sample with  $T_c=80\text{ K}$ . Figure 6 shows its c-axis conductivity  $\sigma_c(\omega, T)$  at different temperatures between 300 and 10 K. The anomaly of the oxygen bond-bending mode at  $320\text{ cm}^{-1}$  is significantly weaker than that of the strongly underdoped sample. The additional absorption peak is located at higher frequencies (around  $480\text{ cm}^{-1}$ ) and it is less pronounced. Figure 7 shows the temperature dependence of (a) the oscillator strength  $S$ , (b) the eigenfrequency  $\omega_o$  and (c) the half-width  $\Gamma$  of the  $320\text{ cm}^{-1}$  phonon mode which have been obtained using the fitting procedure outlined above. It can be seen that the onset of the anomaly of the  $320\text{ cm}^{-1}$  mode occurs now close to the superconducting transition (i.e.,  $T^* \lesssim 100\text{ K}$ ). A similar result has been previously obtained from conventional reflection measurements on weakly underdoped Y-123 crystals [3]. The formation of the NS-gap, as

evidenced from the gradual suppression of the electronic background conductivity, can be seen to set in at a significantly higher temperature  $T_{NG} \gtrsim 200$  K and the characteristic frequency scale of the NS-gap still exceeds the measured spectral range,  $\omega_{NG} > 700$   $\text{cm}^{-1}$ . These findings supports our point of view that the anomaly of the 320  $\text{cm}^{-1}$  mode and the formation of the additional absorption peak are not directly related to the mechanism that is responsible for the NS-gap [31,32]. Figure 8 shows the electronic background including the additional absorption peak which has been obtained by subtracting the contributions of the phonon modes at 280, 320, 570  $\text{cm}^{-1}$  and 620  $\text{cm}^{-1}$  (as described above). Figure 9 shows the estimated T-dependences of the spectral weight of the additional peak at 480  $\text{cm}^{-1}$  (once more assuming a linear electronic background) and of the spectral weight loss ( $\Delta\text{SW}$ ) of the phonon mode at 320 as estimated from the change in its oscillator strength according to:  $\Delta\text{SW} = \pi^2 c \cdot \epsilon_o \cdot [S(120\text{K}) - S(T)] \cdot \nu_o^2$ . In analogy to the strongly underdoped sample, a sizeable fraction of the spectral weight of the absorption peak does not seem to arise from the phonon subsystem.

### A. Summary

In summary, we have performed ellipsometric measurements of the FIR c-axis conductivity of underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  single crystals. In particular, we have studied the temperature dependence of the spectacular anomaly of the oxygen bond-bending mode at 320  $\text{cm}^{-1}$  and of the additional absorption peak. For the strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal with  $T_c = 52$  K the gradual onset of the anomaly of the 320  $\text{cm}^{-1}$  phonon mode and the growth of the additional absorption peak around 400  $\text{cm}^{-1}$  occur around  $T^* \sim 150$  K, i.e., well below the onset temperature of the NS-gap,  $T_{NG} \gtrsim 300$  K, but also well above  $T_c = 52$  K. Most remarkably, however, we find that both anomalies exhibit a very pronounced and marked change right at  $T_c = 52$  K. For a less strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal with  $T_c = 80$  K both anomalies start to appear in the vicinity of the superconducting transition,  $T^* \sim T_c = 80$  K while the signatures of the NS-gap appear already below  $T_{NG} \gtrsim 200$  K. Our

measurements thus establish that both anomalies are related to the superconducting transition. For strongly underdoped and thus very anisotropic samples, the gradual onset of the anomalies may occur well above  $T_c$  due to superconducting pairing fluctuations within the individual bilayers, but there is always a steep and sudden increase of both anomalies when the macroscopically coherent superconducting state forms at  $T_c$ . This implies that the anomalies are not related to the NS-gap in the c-axis conductivity nor to the spin-gap phenomenon as observed in NMR- and NQR-measurements both of which exhibit no noticeable changes at  $T_c$ . For both underdoped crystals a sum-rule analysis of the changes of the spectral weights indicates that the spectral weight of the additional absorption peak is not fully accounted for by the spectral weight loss of the phonon modes at 320 and 560  $\text{cm}^{-1}$ . At least 40-50 % of the spectral weight of the additional absorption peak seems to arise from the electronic background, namely from the superconducting condensate. We have outlined that all the reported features are compatible with a recently proposed model where the bilayer cuprate compounds such as Y-123 are treated as a superlattice of inter- and intra-bilayer Josephson-junctions. The additional absorption peak can be related to the transverse optical plasmon, while the spectacular phonon anomaly can be explained as due to the drastic changes of the local electrical fields acting on the in-plane oxygen ions as the Josephson current sets in below  $T_c$  for the inter-bilayer junctions while below  $T^* \geq T_c$  for the intra-bilayer junctions.

#### IV. ACKNOWLEDGEMENT:

We gratefully acknowledge the support of G.P. Williams and L. Carr at the U4IR beamline at NSLS. We also thank D. Böhme and W. König for technical help and E. Brücher and R.K. Kremer for performing the SQUID measurements. D.M. gratefully acknowledges support by the Alexander von Humboldt Foundation.

## REFERENCES

\* permanent address: IFD, Warsaw University, Hoza 69, 00-681 Warsaw, Poland.

- [1] A. Wittlin, R. Liu, M. Cardona, L. Genzel, W. König, and F. Garcia-Alvarado, *Solid State Commun.* **64**, 477 (1987); A.P. Litvinchuk, C. Thomsen, and M. Cardona, in *Physical Properties of High Temperature Superconductors IV*, edited by D.M. Ginsberg (World Scientific, Singapore, 1994), p.375 and reference therein.
- [2] C.C. Homes, T. Timusk, D.A. Bonn, R. Liang, and W.N. Hardy, *Physica C* **254**, 265 (1995); *Can. J. Phys* **73**, 663 (1995).
- [3] J. Schützmann, S. Tajima, S. Miyamoto, Y. Sato, and R. Hauff, *Phys. Rev. B* **52**, 13665 (1995).
- [4] D.N. Basov, T. Timusk, B. Dąbrowski, J.D. Jorgensen, *Phys. Rev. B* **50**, 3511 (1994).
- [5] M. Reedyk, T. Timusk, Y. W. Hsueh, B.W. Statt, J.S. Xue, and J.E. Greedan, *Phys. Rev. B* **56**, 9129 (1997).
- [6] T. Zetterer, M. Franz, J. Schützmann, W. Ose, H.H. Otto, and K.F. Renk, *Phys. Rev. B* **41**, 9499 (1990).
- [7] R. Henn, T. Strach, E. Schönherr, and M. Cardona, *Phys. Rev. B* **55**, 3285 (1997).
- [8] G. Hastreiter, U. Hoffmann, J. Keller, and K.F. Renk, *Solid State Commun.* **76**, 1015 (1990).
- [9] R. Hauff, S. Tajima, W.J. Jang, and A.I. Rykov, *Phys. Rev. Lett.* **77**, 4620 (1996).
- [10] D. van der Marel and A.A. Tsvetkov, *Czech. Journ. of Phys.* **46**, 3165 (1996).
- [11] M. Grüninger, D. van der Marel, A.A. Tsvetkov, and A. Erb, cond-mat/9903352
- [12] D. Munzar, C. Bernhard, A. Golnik, J. Humlíček, and M. Cardona, cond-mat/9903291
- [13] P.W. Anderson, *The Theory of Superconductivity in the High- $T_c$  Cuprates* (Princeton

- University Press, Princeton, NJ, 1997).
- [14] M. Rapp, A. Murk, R. Semerad, W. Prusseit, Phys. Rev. Lett. **77**, 928 (1996).
  - [15] K. Schlenga, R. Kleiner, G. Hechtfisher, M. Möble, S. Schmidt, P. Müller, Ch. Helm, Ch. Preis, F. Forsthofer, J. Keller, H. L. Johnson, M. Veith, E. Steinbeiß, Phys. Rev. B **57**, 14 518 (1998).
  - [16] Y. Matsuda, M.B. Gaifullin, K. Kumagai, K. Kadowaki, and T. Mochiku, Phys. Rev. Lett. **75**, 4512 (1995); O.K.C. Tsui, N.P. Ong, and J.B. Petterson, Phys. Rev. Lett. **76**, 819 (1996).
  - [17] K. Tamasaku, T. Ito, H. Takagi, S. Uchida, Phys. Rev. Lett. **72**, 3088, (1994).
  - [18] P.J.M. van Bentum, A.M. Gerrits, M.E. Boonamn, A. Wittlin, V.H.M. Dujin, A.A. Menovski, Physica B **211**, 260 (1995).
  - [19] P.J.M. van Bentum, A. Wittlin, M.E.J. Boonman, M. Gross, S. Uchida, and K. Tamasaku, Physica C **293**, 136 (1997).
  - [20] H. Shibata and T. Yamada, Phys. Rev. Lett. **81**, 3519 (1998).
  - [21] A.P. Litvinchuk, C. Thomsen, M. Cardona, J. Karpinski, E. Kaldis, and S. Rusiecki, Z. Phys. **B 92**, 9, (1993).
  - [22] see for example K. Kakurai, S. Shamoto, T. Kiyokura, M. Sato, J.M. Tranquada, and G. Shirane, Phys. Rev. **B 48**, 3485 (1993); G.V.M. Williams, J.L. Tallon, R. Meinhold and A. Janossy, Phys. Rev. **B 51**, 16503 (1995).
  - [23] C.T. Lin, W. Zhou, W.Y. Liang, E. Schönherr, and H. Bender, Physica **C 195**, 291 (1992).
  - [24] R.M.A. Azzam and N.H. Bashara, *Ellipsometry and Polarized Light* (North Holland, Amsterdam, 1977).



- [25] D.E. Aspnes, J. Opt. Soc. Am. **70**, 1275 (1980).
- [26] R. Henn, J. Kircher, M. Cardona, A. Wittlin, V.H.M. Dujin, and A.A. Menovsky, Phys. Rev. **B 53**, 9353 (1996).
- [27] J. Kircher, R. Henn, M. Cardona, P.L. Richards, and G.P. Williams, J. Opt. Soc. Am. **B 14**, 705 (1997).
- [28] R. Henn, C. Bernhard, A. Wittlin, M. Cardona, and S. Uchida, Thin Solid Films **313-314**, 643 (1998).
- [29] S. Tajima, J. Schützmann, S. Miyamoto, I. Terasaki, Y. Sato and R. Hauff, Phys. Rev. **B 52**, 13665 (1997).
- [30] C. Bernhard, R. Henn, A. Wittlin, M. Kläser, Th. Wolf, G. Müller-Vogt, C.T. Lin, and M. Cardona, Phys. Rev. Lett. **80**, 1762 (1998).
- [31] C. Bernhard, D. Munzar, A. Wittlin, W. König, A. Golnik, C.T. Lin, M. Kläser, Th. Wolf, G. Müller-Vogt, and M. Cardona, Phys. Rev. **B 59**, R6631 (1999).
- [32] C. Bernhard, D. Munzar, A. Golnik, M. Kläser, Th. Wolf, C.T. Lin, and M. Cardona, Physica **C 317-318**, 276 (1999).
- [33] A.P. Litvinchuk, C. Thomsen and M. Cardona, Solid. State Commun. **83**, 343 (1992).
- [34] H. Ding, M.R. Norman, T. Yokoya, T. Takeuchi, M. Randeira, J.C. Campuzano, T. Takahashi, T. Mochiku, and K. Kadowaki, Phys. Rev. Lett. **78**, 2628 (1997); Nature **382**, 51 (1996).
- [35] A.G. Loeser, Z.-X. Shen, D.S. Dessau, D.S. Marshall, C.H. Park, P. Fournier, and A. Kapitulnik, Science **273**, 325 (1996).
- [36] M.R. Norman, H. Ding, M. Randeira, J.C. Campuzano, T. Yokoya, T. Takeuchi, T. Takahashi, T. Mochuki, K. Kadowaki, P. Guptasarama, and D.G. Hinks, Phys. Rev. B **57**, 11093 (1998); Nature **392**, 157 (1998).

[37] N. Miyakawa, P. Guptasarma, J.F. Zsadzinski, D.G. Hinks, and K.E. Gray, Phys. Rev. Lett. **80**, 157 (1998).

## V. FIGURE CAPTIONS

Figure 1: Temperature dependence of the zero-field-cooled (zfc) and field-cooled (fc) volume DC-magnetization,  $\chi_V$ , of the  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal (open circles) and the  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal (solid squares). The external field  $H_{ext}=5$  Oe was applied along the c-axis of the platelet shaped crystals. Corrections for demagnetization factors have not been taken into account. The critical temperatures and the transition width (between 10 and 90% of the diamagnetic shielding) are  $T_c=52$  K,  $\Delta T_c=3$  K and  $T_c=80$  K,  $\Delta T_c=4$  K.

Figure 2: Temperature dependence of the real part of the FIR c-axis conductivity of the strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal with  $T_c=52$  K. Spectra are shown for (a)  $T=300$ , 200 and 150 K and (b)  $T=150$ , 60, 45, 35 and 5 K.

Figure 3: Temperature dependence of (a) the oscillator strength  $S$ , (b) the eigenfrequency  $\omega_o$  and (c) the half width  $\Gamma$  of the oxygen bond-bending mode of the strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal ( $T_c=52$  K). The phonon parameters have been obtained by fitting modified Lorentzian functions to the complex dielectric function (as outlined in the text). The dashed line marks the superconducting transition temperature  $T_c=52$  K, the dotted line indicates the gradual onset of the renormalization of the phonon mode around  $T^*\sim 150$  K.

Figure 4: Temperature dependence of the electronic conductivity including the additional absorption peak at  $410\text{ cm}^{-1}$  (presumed to be also of electronic origin) of the strongly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$  crystal with  $T_c=52$  K which has been obtained by subtracting the contributions of the phonon modes at 280, 320, 560 and  $630\text{ cm}^{-1}$ .

Figure 5: Temperature dependence of the spectral weight of the additional absorption peak at  $410\text{ cm}^{-1}$  ( $\text{SW}^{410}$ , solid squares) and the spectral weight loss of the oxygen bond-

bending mode at  $320 \text{ cm}^{-1}$  ( $\Delta\text{SW}^{320}$ , open circles). The inset illustrates how the SW of the additional absorption peak has been obtained. The open circles represent the spectrum at  $T=5 \text{ K}$  obtained after the phonons have been subtracted, the solid line represent the linear background which has been further subtracted in order to obtain  $\text{SW}^{410}$  as indicated by the shaded area. Also shown is a fit with a Lorentzian plus a linear background (dashed lines) which gives a somewhat larger value of  $\text{SW}^{410} \approx 16.000 \text{ } \Omega^{-1}\text{cm}^{-2}$  at  $5 \text{ K}$ . The spectral weight loss of the  $320 \text{ cm}^{-1}$  phonon mode has been calculated according to the formula  $\Delta\text{SW}^{320} = \pi^2 c \cdot \epsilon_o \cdot [S(175\text{K}) - S(T)] \cdot \nu_o^2$  using the oscillator strenght  $S(T)$  and the eigenfrequencies  $\nu_o$  given in Fig. 3a and 3b. The error bar indicates the maximum spectral weight loss at  $T=5\text{K}$  of the phonon mode at  $560 \text{ cm}^{-1}$ .

Figure 6: Temperature dependence of the real part of the FIR c-axis conductivity of the weakly underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal with  $T_c=80 \text{ K}$ .

Figure 7: Temperature dependence of (a) the oscillator strength  $S$ , (b) the eigenfrequency  $\omega_o$  and (c) the half width  $\Gamma$  of the oxygen bond-bending mode of the moderately underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal ( $T_c=80 \text{ K}$ ). The phonon parameters have been obtained by fitting modified Lorentzian functions to the complex dielectric function (as outlined in the text). The dashed line marks the superconducting transition temperature  $T_c=80 \text{ K}$ .

Figure 8: Temperature dependence of the electronic conductivity, including the additional absorption peak around  $480 \text{ cm}^{-1}$ , of the moderately underdoped  $\text{YBa}_2\text{Cu}_3\text{O}_{6.75}$  crystal with  $T_c=80 \text{ K}$  which has been obtained by subtracting the contributions of the phonon modes at  $280, 320, 570$  and  $620 \text{ cm}^{-1}$ .

Figure 9: Temperature dependence of the spectral weight of the additional absorption peak at  $480 \text{ cm}^{-1}$  ( $\text{SW}^{480}$ , solid squares) and the spectral weight loss of the oxygen bond-bending mode at  $320 \text{ cm}^{-1}$  ( $\Delta\text{SW}^{320}$ , open circles). The spectral weight loss of the  $320 \text{ cm}^{-1}$  phonon mode has been calculated according to the formula  $\Delta\text{SW} = \pi^2 c \cdot \epsilon_o \cdot [S(175\text{K}) - S(T)] \cdot \nu_o^2$ , using the oscillator strenghts  $S(T)$  and the eigenfrequencies

$\nu_o$  given in Fig. 7a and 7b. The error bar indicates the maximum spectral weight loss at  $T=5\text{K}$  of the phonon mode at  $570\text{ cm}^{-1}$ .



















